



GRIEKSPoor

THERMAL COATINGS

Product Specification Sheet

TOPCOAT+

300µm 2-layer

Ni based superalloy / Al₂O₃ + Ti₂O₃

Coating construction and composition (2-layer coating system)

Intermediate coating	HP-HVOF	TOPCOAT 177 (Ni-superalloy)	≥ 100µm (max. 3000µm)
Topcoat	Plasma	Al ₂ O ₃ TiO ₂	≥ 200µm (max. 600µm)

Key coating information

Description	International standard	Minimum value	Griekspoor Standard
Tensile Adhesive Strength	ISO 14916	≥ 40 N/mm ²	≥ 50 N/mm ²
Corrosion test	NOV/DNV-C2	No corrosion visible after 500h	>1000h
	Endurance test acc. NBD10300	No permeability after 1000h (ECP-test > -350mV)	>1000h (ECP-test > -150mV)
Corrosion resistance	ISO 9227 AASS ASTM G85	No corrosion after 1000h	>2000h
Porosity		<4%	<3%
Chem. Resistance 1. NaCl (acid) 2. H ₂ SO ₄ (acid) 3. HCl (acid) 4. NaOH (base)		1. Very good 2. Very good 3. Very good 4. Fair/good	
Impact toughness test	NOV/DNV-M1 (0.8kpm)	No cracking outside the impact area, min. energy 0.8kpm (8J)	No cracking outside the impact area, min. energy 0.8kpm (8J)
Rockwell indentation test	NOV/DNV-M2	No or negligible break-out or cracking	No or negligible break-out or cracking
Dynamic bending test 500 x / σ 300 N/mm ²	NOV/DNV-M3	No cracks after bending of minimum of 500 cycles	No cracks after bending of minimum of 500 cycles
Micro hardness	HV0.3	950HV (NOV/DNV>600)	900-1000HV
Macro hardness	HR15N	>75	>85
Operating temp.	---	-40°C ≤ T ≤ 120°C	-40°C ≤ T < 540°C
Wear testing	ASTM G065B		
Surface finish	NEN-EN ISO4287	Ra < 0.5µm Rz < 5.0µm Rpk < 0.2µm	Ra < 0.35µm Rz < 4.0µm Rpk < 0.1µm

Seal advice		1. Good sealing properties (sealing advice on Griekspoortc.com) 2. Advised choice of sealing constructions
Possibility of integrated Linear Positioning Measuring (LPM-system)		Yes, over full capacity Length 23 meters, Diameter approx. 1 meter, Weight 20 tons.
Elasticity		Good

General information

The bond/intermediate coating is a Griekspoor developed nickel based superalloy, designed to withstand the most severe environments in (chemical) corrosion.

TOPCOAT+ is a very economic, wear resistant, and dense coating with very good corrosion and chemical resistance. TOPCOAT+ can be ground to excellent finishes.

Finishing can be very smooth (Ra < 0.15µm) however Griekspoor advises to use an Ra-roughness of 0.2-0.4µm. The advice is to use a "Stepseal" seal construction (see Griekspoortc.com in TOPCOAT section). This seal construction, together with the advised roughness, will guarantee maximum lifetime with optimal sealing properties (no leakage, no stick-slip, low friction, etc.).

This coating is designed to withstand maritime environments where very good wear resistance is required. In extreme severe environments it is advised to choose an intermediate coating of approx. 200µm to increase corrosion resistance.

Typical uses and applications are hydraulic rods/parts, plungers, automotive parts, components for the chemical industry (testing may be needed for the specific environment/situation), electrical insulation, and dielectric applications.