

JOINTWOOD

BY NIAGARA



APRIL 2025 EDITION

CREATED ON 08 APR. 2025 VERSION 01.02

Bevel Back

TECHNICAL MANUAL & INSTALLATION GUIDE





Bevel Back **TECHNICAL MANUAL**
& INSTALLATION GUIDE

GENERAL CONTENTS

Bevel Back spacing from the wall	5
Bevel Back set-out-guide	6

Section 1 General	7
1.1 Scope and general comment	7
1.2 Storage	7
1.3 Handling	7
1.4 Keep dry	7
1.5 Wall underlay	7
1.6 Flashings	7
1.7 Sealants	7
1.8 Air seals	7
1.9 Building preparation	7
1.10 Wall cladding cavities	7
Weatherboard measurement table	7

Section 2 Installation	8
2.1 Jointwood weatherboards fixings and fixing method	8
2.2 Joins	8
2.3 External box corner	8
2.4 Internal box corner	8
2.5 Aluminium window and door jambs	9
2.6 Aluminium window and door sills	9
2.7 Aluminium window and door heads	9
2.8 Timber window and door openings	9

Section 3 Nailing	10
3.1 Nail selection	10
3.2 Nailing schedule	10
3.3 Nailing guidelines	10
3.4 Bevel Back temporary fixing method	10
3.5 Screw Fixing Option	10

Section 4 Painting and Maintenance	11
4.1 Moisture content	11
4.2 Preparation	11
4.3 Top coat selection	11
4.4 Painting	11
4.5 Maintenance	11

Technical Drawings	12 -42
Direct fix	12 - 25
Cavity fix	26 - 42

Jointwood Weatherboards warranty	43
---	-----------


BEVEL BACK DRAWING DIRECTORY

Bevel Back Direct Fix

Foundation Timber	12
Foundation Concrete	12
Door Sill	13
Door Jamb	13
Door Head	13
Window Sill	14
Window Jamb	14
Window Head	15
Soffit	15
External Corner	16
Internal Corner	16
Meter Box Head	17
Meter Box Jamb	17
Meter Box Sill	17
Pipe Penetration	18
Fascia Eaves	18
Apron	18
Parapet Cap	19
Stucco – Below	19
Stucco – Internal Corner	20
Stucco – External Corner	20
Profiled Metal – Above	21
Profiled Metal – Below	21
Profiled Metal – Abutting	22
Profiled Metal – Internal Corner	22
Profiled Metal – External Corner	23
Masonry Veneer – Below	23
Masonry Veneer – Abutting	24
Masonry Veneer – Internal Corner	24
Masonry Veneer – External Corner	25
Water Proof Deck – Above	25
Mid-Floor Junction	25


Bevel Back Cavity Fix

Foundation Timber	26
Foundation Concrete	27
Door Sill	27
Door Jamb	28
Door Head	28
Window Sill	29
Window Sill (Sill Support Bar)	29
Window Jamb	30
Window Head	30
Window Head A	31
Soffit	31
External Corner	32
External Corner Soaker	32
Internal Corner	33
Meter Box Head	33
Meter Box Jamb	34
Meter Box Sill	34
Pipe Penetration	35
Fascia Eaves	35
Apron	35
Parapet Cap	36
Stucco – Below	36
Stucco – Internal Corner	37
Stucco – External Corner	37
Profiled Metal – Above	38
Profiled Metal – Below	38
Profiled Metal – Abutting	39
Profiled Metal – Internal Corner	39
Profiled Metal – External Corner	40
Masonry Veneer – Below	40
Masonry Veneer – Abutting	41
Masonry Veneer – External Corner	41
Masonry Veneer – Internal Corner	42
Water Proof Deck – Above	42
Mid-Floor Junction	42



JOINTWOOD BEVEL BACK SET-OUT GUIDES

187 Bevel Back Weatherboard



GENERAL

1.1 Scope and general comment

These instructions are specific and can be used for buildings that fall within the scope of NZS 3604:2012 Timber Framed Buildings and E2/AS1. Buildings that have Jointwood Bevel Back Weatherboards and have a weathertightness risk score of more than 12 as assessed in E2/AS1 section 3 will require a drained and ventilated cavity.

Jointwood Weatherboards must be fixed to framing that is dry (<20% mc), straight and stable. Flashings as shown in the installation CAD drawings must be used.

All building sites are different and while these instructions are detailed, only those details that apply to your specific building site should be used.

When used in combination, timber framed windows and timber cladding are not covered by E2/AS1 and application for an alternative solution to New Zealand Building Code Clause E2 must be made to the Building Consent Authority.

1.2 Storage

Correct storage of Jointwood Weatherboards prior to installation is critical. Store as follow:

- in a dry well ventilated area
- on a flat surface supported every meter along the length of the product
- clear of the ground by at least 150mm
- protected from the elements including direct sunlight and rain
- if rising damp is likely, place a moisture barrier under the stack
- use inside storage where available

1.3 Handling

Unload Jointwood Weatherboards carefully from truck by hand or use a mechanical lifting device. Never drag boards across the ground. To avoid bending, always carry individual boards on their edge. During handling (cutting, installation etc.) care should be taken to avoid damaging the surface of the board.

1.4 Keep dry

Jointwood Weatherboards are made from kiln dried timber. Timber is hygroscopic and it will absorb moisture in a damp environment and release it in a dry environment. Primers will not stop moisture uptake. If timber absorbs moisture prior to installation, some dimensional swelling may occur, this will disappear when the timber returns to its original moisture content.

If product shows signs of dimensional swelling, allow time for it to dry and return to the manufactured dimensions before installation.

1.5 Wall underlay

Use only underlays that meet the requirements of E2/AS1 Table 23. Underlays are a secondary protective barrier against weathering and must be installed in accordance with E2/AS1 section 9.1.7.

1.6 Flashings

Refer to NZS 3604 section 4 and E2/AS1 Table 20 for durability requirements and E2/AS1 section 9 for flashing design and fabrication details.

As recommended in E2/AS1, window and door suppliers are responsible for head flashings. A layer of kraft paper is required between the flashing and timber framing where the timber has been treated with a copper-based treatment. Check the flashing manufacturer's recommendations in all cases.

1.7 Sealants

All sealants and adhesive sealants must be suitable for exterior use.

1.8 Air seals

Air seals are a barrier that prevent air flowing through the cladding or circulating within the cavity, from entering the building. Air seals are required where a hole or penetration through the external cladding occurs - windows, doors, pipes, meter boxes etc. See E2/AS1 for complete building air seal requirements.

A backing rod of a suitable diameter must be installed in the gap between the window/door reveal, meter box or pipe and the opening frame prior to applying the sealant. Take care not to over fill the space with sealant.

Backing rods and sealants must be used in accordance with the manufacturer's instructions. See E2/AS1 for details.

1.9 Building preparation

NZS 3604 sets out the requirements that timber framing must meet including sizing, spacings, straightness (Table 2.1) and moisture content. All framing must meet these requirements before installation of Jointwood Weatherboards can begin.

Ensure all openings are framed out with the correct clearance between the trimmed opening and the window/door/meter box frame.

1.10 Wall cladding cavities

If the weathertightness risk score is higher than 12 a drained and ventilated cavity will be required between the underlay and Jointwood bevel back weatherboards.

If a cavity is required, structurally fix treated cavity battens to the framing in accordance with BRANZ Bulletin issue 673, (June 2022). Cavity construction, including flashing and vermin proofing, must be in accordance with the requirements as set out in E2/AS1 and NZS 4229.

Jointwood bevel back weatherboard measurement table

Size	Profile	Grade	Cover	Lap	Length	Lm/m2
187 x 18	Bevel Back	Finger Jointed	155mm	32mm	6.1m	6.45

INSTALLATION

2.1 Jointwood Weatherboards fixings and fixing method

Using an tilt fillet, position and fix the bottom Jointwood weatherboards ensuring there is a minimum 50mm overlap below the bottom plate or bearer. The tilt fillet will provide the correct layback angle for the bottom board.

Correct positioning of each successive board (32mm lap) is critical to ensure finishing scribes fit correctly. **Use a precut scribe as a storey rod to assist in this process. (Keep this rod dry at all times to maintain its correct dimensions).**

Each Jointwood weatherboard will be fixed with one nail at every batten or stud, starting in the middle of the board and working to the ends. Single point nailing will allow the board to expand and contract as Equilibrium Moisture Content change occurs. Fixings are to be located 40mm above the lower edge of the board penetrating 35mm into the framing or structural batten.

Use 75 x 3.15 JH hot-dipped galvanised or annular grooved stainless steel nails for fixing either directly into framing or structural battens.

Seal all cut ends with Envira Quick Dry End Seal.

Hand nailing is recommended as nail guns can cause damage to the surface of the board. If a nail gun is used a non-marking attachment should be used to avoid damage to the board surface. Seal then fill with an exterior grade wood filler immediately after nailing. Pre-drill nail holes at all joints and within 50mm of ends.

The top board may have to be cut to suit soffit.

For screwing option refer 3.5

2.2 Joins

Avoid joining Envira weatherboards whenever possible but if joining is unavoidable, only use 45 degree scarf joints directly over studs or Envira structural battens.

Face the overlapping board away from the prevailing weather direction using one fixing through the overlapping board (pre-drill the hole).

All cut ends should be sealed with an exterior Adhesive Sealant before assembling the joint. Joints must be tight (no gaps) and flat. Seek professional advice from Adhesive Sealant manufacturer.

Nails should be hand driven and punched below the surface to allow for one coat of Envira Quick Dry End Seal before filling with an exterior grade wood filler. After filler has dried sand and re-seal.

2.3 External box corner

Using 50 x 2.5mm JH hot-dipped galvanized or annular grooved stainless steel nails, fix the two piece prefabricated external box corner over the Jointwood bevel back weatherboards. Use two nails at each fixing point. There must be a minimum 50mm cover on both faces of the corner.

Fixings must be located 35-40mm above the lower edge of the overlapping board on every fourth board for 142mm wide weather boards and every third board for 187mm wide weatherboards. For nails near the ends of the corner boards pre-drill the nail holes.

Fit a precut Scribe over the weatherboards against the corner boards. Pre-drill holes and using 50 x 2.0mm (40 x 18 scribe) or 30 x 2.0mm (40 x 10 scribe) JH hot-dipped galvanised or annular grooved stainless steel nails, fix the scribe firmly against the box corner. Nail at 450mm centres.

Seal all cut ends with Envira Quick Dry End Seal.

Nails must be hand driven and punched below the surface to allow for filling. Seal then fill with an exterior grade wood filler immediately after nailing.


2.4 Internal box corner

Internal corners, direct or cavity, must have a flashing behind the cladding that provides a minimum 50mm cover to both faces of the corner. Refer to E2/AS1 for full details. Using 50 x 2.5mm JH hot-dipped galvanised or annular grooved stainless steel nails, fix the two piece prefabricated internal box corner over the Jointwood bevel back weatherboards. Use two nails at each fixing point. The internal box corner provides 100mm cover on both faces of the corner.

Fixings must be located 35-40mm above the lower edge of the overlapping board on every third board for 187mm wide weatherboards.

Use two nails at each fixing point. For nails near the ends of the corner boards pre drill the nail holes.

Fit a precut Scribe over the weatherboards. Pre-drill holes and using 50 x 2.0mm (40 x 18) or 30 x 2.0mm (40 x 10) JH hot-dipped galvanised or annular grooved stainless steel nails, fix the scribe firmly against the box corner. Nail at 450mm centres.



Seal all cut ends with Envira Quick Dry End Seal.

Nails must be hand driven and punched below the surface to allow for filling. Seal then fill with an exterior grade wood filler immediately after nailing.

2.5 Aluminium window and door jambs

Window and door openings are a high weathertightness risk area and require particular attention to ensure weathertightness is achieved. All window and door openings must be constructed and trimmed in accordance with E2/AS1. All flashings, air seals, underlay and flexible flashing tapes must be in place.

For flashing details refer to NZS 3604 section 4 and E2/AS1 table 20 for durability requirements and E2/AS1 for flashing design and fabrication details.

As recommended in E2/AS1, window and door suppliers are responsible for head flashings.

The following instructions apply to aluminium windows and doors as set out in E2/AS1 9.1.10 - 9.1.10.8.

All windows must comply with NZS 4211 including consideration of the building location.

The aluminum facing flange must overlap the cladding (Jointwood weatherboard) by at least 10mm for jambs and at least 8mm for sills.

Fit firmly against the flange either an Scribe or a facing board and Scribe combination. Pre-drill holes in the scribe and fix as per nailing schedule section 3.2 using JH hot-dipped galvanised or annular grooved stainless steel nails. Nail at 450mm centres.

Facing board fixings must be located 35-40mm above the lower edge of the overlapping board on every fourth board for 142mm wide weatherboards and every third board for 187mm wide weatherboards. Use two nails at each fixing point. For nails near the ends of the corner boards pre-drill the nail holes.

Direct fixed and cavity fixed cladding applications must have a sill tray flashing a minimum of the full width of the opening.

Seal all cut ends with Envira Quick Dry End Seal.

Nails must be hand driven and punched below the surface to allow for filling. Seal then fill with an exterior grade wood filler immediately after nailing.

Fit air seals around all window and door openings as specified.

2.6 Aluminium window and door sills

Jointwood Bevel Back Weatherboard requires a full width sill tray for direct fixed windows and doors, which meets the requirements of E2/AS1. If a sill (plant on) is to be used, ensure the positioning of the sill does not compromise the sill flashing detail or function. The sill tray must extend at least 8mm behind the line of the aluminium frame.

In a cavity fix application, all doors and windows with a trim opening wider than 600mm require an appropriate sill support bar conforming to EM6, paragraph 9.1.10.5

2.7 Aluminium window and door heads

Direct and cavity fixed aluminium windows and doors require a flashing that meets the requirements of E2/AS1. The flashing must be fitted behind the cladding with a 5mm gap between the bottom edge of the cladding and the horizontal surface of the flashing. If a Head Trim is to be used there must be a 5mm gap between the bottom edge of the head trim and the horizontal surface of the flashing.

2.8 Timber window and door openings

When used in combination, timber framed windows and timber cladding are not covered by E2/AS1 and application for an Alternative Solution to New Zealand Building Code Clause E2 must be made to the Building Consent Authority. Timber window and door installations must include facings boards and scribes when used in combination with the Jointwood Bevel Back Weatherboard.



NAILING

3.1 Nail selection

Selection of proper nails is important.

Use Jolt Head (JH) hot-dipped galvanised or stainless steel annular grooved, for fixing either directly into framing or structural batten.

Do not use plain or electroplated nails. Hot dipped galvanising must meet the requirements of AS/NZS 4680:2006.

Please check for updates on Niagara's website - www.niagara.nz

Download 2D drawing files in PDF, DWG or DXF format online.

Jointwood Bevel Back technical manual

is available for download at www.niagara.nz/brochures

3.2 Bevel back nailing schedule

Timber size (mm)	Component	Recommended minimum nail size	Section
187 x 18	Bevel back direct fixed weatherboard	75 x 3.15	2.1
187 x 18	Bevel back cavity fixed weatherboard	75 x 3.15	2.1
100 x 100	External and internal box corners	50 x 2.50	2.3, 2.4
All sizes	Facing boards	50 x 2.50	2.5
40 x 10	Scribe pre-cut scribe	30 x 2.00	2.3, 2.4, 2.5
40 x 18	Scribe pre-cut scribe	50 x 2.00	2.3, 2.4, 2.5
90 x 42 65 x 42	Sills	75 x 3.15	2.6
40 x 27 18 x 18	Eaves mould	60 x 2.80	2.1
82 x 38	Head trim	60 x 2.80	2.7
50 x 19	Door sill trim	50 x 2.50	
44 x 20	Cavity batten	60 x 2.80	1.10

3.3 Nailing guidelines

Proper application and nailing practices are essential for maximising the product performance and appearance.

All nailing should be over studs with at least 35mm penetration into the frame.

Nailing should be such that it does not restrict normal seasonal movement, so do not nail through overlapping pieces.

Hand nailing is recommended as nail guns can cause damage to the surface of the board. If a nail gun is used a non-marking attachment should be used to avoid damage to the board surface.

Nails are to be countersunk (punched) by 2mm and must be primed immediately then filled to avoid moisture uptake around the nail head*.

Pre-drilling near the ends is recommended as a precaution to avoid the possibility of end splitting.

We recommend the use of scarf joints. **Refer to Section 2.2**

Butt joints can be used without an expansion gap, but these must be flashed. **Refer to Section 2.2**

***Seal all nail holes with Envira Quick Dry End Seal then fill with an exterior grade wood filler. After filler has dried sand and re-seal.**

3.4 Bevel Back Temporary Fixing Method

- Jointwood weatherboards can be brad nailed at the top above the weather groove to temporarily fix the weatherboard in place before face nailing. The brad nails must be galvanised or stainless steel, 32mm long maximum or less, and 2mm diameter or less.
- The brad nail is to be fixed on the **minimum** number of studs necessary to hold the weatherboard in the correct position and no more than one brad nail per stud maximum.
- Pre-drill the Jointwood weatherboard (to avoid splitting) for nail or brad locations within 50mm of the board ends.

3.5 Screw Fixing Option

Jointwood Bevel Back Weatherboards are also able to be fixed by using specifically designed timber weatherboard screws.

These must be either 7G or 8G, length and fixing point is to match the same required when using nail fixings. Screws can be galvanised, or stainless steel if preferred.

Options are:

ECKO T-REX17 8Gx75mm Weatherboard Jolt Screw on both direct and cavity fix.

Simpson Strong-Tie 7Gx75mm Weatherboard Screw on both direct and cavity fix.

All sealing, filling and priming is exactly the same procedure as under 3.3 Nailing guidelines.

PAINTING AND MAINTENANCE

4.1 Moisture content

The primer will not protect against moisture uptake, which can result in dimensional swelling. If swelling or distortion of the timber is evident, the product must be given time to dry out and return to its equilibrium moisture content and manufactured dimensions before any top coats are applied.

4.2 Preparation

- Remove all loose material and dirt.
- Primers will not withstand extended periods exposed to the elements and may require a light sand.
- Sand and spot prime all bare patches or where the factory primer has been damaged.
- Sand smooth and spot prime all filled areas
- Fill all nail holes with an exterior grade wood filler and seal all notches, end cuts and nail holes with a suitable primer/undercoat or end sealing product such as Envira Fast Dry End Seal.

It is the painter's responsibility to ensure all surfaces are correctly prepared prior to painting including ensuring that the primer is well-adhered to the timber substrate and that all surfaces are in a suitable condition before top coating.

It is recommended that at a minimum the top lap of the boards are coated with top coat approximately 50mm down from the top edge.

This will eliminate a primer line showing if the boards move with the seasonal change that can occur. Ideally the boards would receive a full top coat before installation.

4.3 Top coat selection

Use only a premium quality house paint that has a Light Reflective Value (LRV) of 45 or higher and a gloss level of 10 per cent or more.

Note: The higher the gloss level, the higher the durability.

For darker colours, Resene recommends CoolColours™ for use on Envira Weatherboard System that have a total solar reflectance (TSR) rating of 40% or more (TSR rating only applies to cool colours).

4.4 Painting

Jointwood recommends applying an extra coat of Premium OIL BASED primer as an undercoat for enhanced durability. The overall thickness of the paint system should be more than 100 microns DFT.

All preparation and painting must be carried out in a good tradesman-like manner and to the current requirements of AS/NZS 2311 Guide to Painting of buildings and the paint manufacturer's data sheet.

Two top coats of quality house paint should be applied within six weeks of the product being installed. If painting does not occur within six weeks of installation, sanding and repriming will be required.

Paint must be applied with the necessary equipment and experience under the appropriate environmental conditions to ensure that the potential of the paint system is maximised.

Total film build, including primer should exceed 100 Dry Micron.

Do not top coat Jointwood products that have moisture-related dimensional swelling. This will help avoid shrinkage lines that may occur in the top coat as the timber returns to its equilibrium moisture content and manufactured dimensions.

4.5 Maintenance

All new buildings will 'settle' and during this process the integrity of the paint system, no matter what type of substrate it has been applied to, may be compromised resulting in minor touch up work being required. If re-priming is necessary, use only a premium quality primer and the original top coat paint for touch up work.

Like washing your car, cleaning your house will help it maintain its good looks for much longer. Airborne contaminants, including salt deposits, which settle on your paint film, can attack the surface and cause premature breakdown. Annual washing of your home will help maintain the fresh appearance of your paintwork.


The presence of moss, mould and lichen will hold moisture on the surface longer, promoting further growth of these organisms and increasing the risk of damage to the coating and substrate. As with any painted surface, regular inspection and immediate repairs to areas of flaking or cracked paint are essential and will stop the entry of moisture into the substrate.

Particular attention should be paid to areas of high weathertightness risk such as around windows and doors, checking that flashings and sealants are in good condition and performing as required. Repair immediately if the building weathertightness has been compromised.

BEVEL BACK DIRECT FIX


Bevel Back Direct Fix **Foundation Timber**

1001 2D :




Bevel Back Direct Fix **Foundation Concrete**

1002 2D :




Bevel Back Direct Fix **Door Sill**

1003 2D :




Bevel Back Direct Fix **Door Jamb**

1004 2D :



Bevel Back Direct Fix **Door Head**


1005 2D :



FLASHING DIMENSIONS


Bevel Back Direct Fix Window Sill

1006 2D :



Bevel Back Direct Fix Window Jamb


1007 2D :



DATE: 08/04/2025 check for updates and download
2D files in PDF, DWG or DXF format at www.niagara.nz

Bevel Back Direct Fix **Window Head**


1008 2D :



FLASHING DIMENSIONS


Bevel Back Direct Fix **Soffit**

1009 2D :




Bevel Back Direct Fix **External Corner**

1010 2D :




Bevel Back Direct Fix **Internal Corner**

1011 2D :



Bevel Back Direct Fix **Meter Box Head**


1012 2D :



FLASHING DIMENSIONS


Bevel Back Direct Fix **Meter Box Jamb**

1013 2D :



Bevel Back Direct Fix **Meter Box Sill**


1014 2D :



FLASHING DIMENSIONS


Bevel Back Direct Fix **Pipe Penetration**

1015 2D :




Bevel Back Direct Fix **Fascia Eaves**

1016 2D :



Bevel Back Direct Fix **Apron**


1017 2D :



DATE: 08/04/2025 check for updates and download
2D files in PDF, DWG or DXF format at www.niagara.nz


Bevel Back Direct Fix Parapet Cap

1018 2D :




Bevel Back Direct Fix Stucco - Below

1019 2D :




Bevel Back Direct Fix Stucco - Internal Corner

1020 2D :




Bevel Back Direct Fix Stucco - External Corner

1021 2D :




DATE: 08/04/2025 check for updates and download
2D files in PDF, DWG or DXF format at www.niagara.nz

Bevel Back Direct Fix **Profiled Metal - Above**
1022 2D :




Bevel Back Direct Fix **Profiled Metal - Below**
1023 2D :




Bevel Back Direct Fix **Profiled Metal - Abutting**

1024 2D :





Bevel Back Direct Fix **Profiled Metal - Internal Corner**

1025 2D :



Bevel Back Direct Fix **Profiled Metal - External Corner**


1026 2D :



FLASHING DIMENSIONS


Bevel Back Direct Fix **Masonry Veneer - Below**

1027 2D :



Bevel Back Direct Fix **Masonry Veneer - Abutting**


1028 2D :



FLASHING DIMENSIONS

Bevel Back Direct Fix **Masonry Veneer - Internal Corner**


1029 2D :



FLASHING DIMENSIONS


Bevel Back Direct Fix **Masonry Veneer - External Corner**

1030 2D :




Bevel Back Direct Fix **Above Waterproof Deck**

1031 2D :



Bevel Back Direct Fix **Mid-Floor Junction**


1032 2D :



BEVEL BACK CAVITY FIX

Bevel Back Cavity Fix **Foundation Timber**

3001 2D :



Please check for updates on Niagara's website - www.niagara.nz


Download 2D drawing files in PDF, DWG or DXF format online.

Jointwood Bevel Back technical manual
is available for download at www.niagara.nz/brochures

DATE: 08/04/2025 check for updates and download
2D files in PDF, DWG or DXF format at www.niagara.nz


Bevel Back Cavity Fix **Foundation Concrete**

3002 2D :




Bevel Back Cavity Fix **Door Sill**


3003 2D :



3004 2D :




3005 2D :



FLASHING DIMENSIONS


Bevel Back Cavity Fix **Window Sill**

3006 2D :




Bevel Back Cavity Fix **Window Sill (Support Bar)**

3006 A 2D :




Bevel Back Cavity Fix Window Jamb

3007 2D :



Bevel Back Cavity Fix Window Head


3008 2D :



FLASHING DIMENSIONS


Bevel Back Cavity Fix **Window Head**

3008 A 2D :




Bevel Back Cavity Fix **Soffit**

3009 2D :




Bevel Back Cavity Fix **External Corner**

3010 2D :




Bevel Back Cavity Fix **External Corner Soaker**

3010 A 2D :




Isometric View




Bevel Back Cavity Fix Internal Corner

3011 2D :




Bevel Back Cavity Fix Meter Box Head

3012 2D :




Bevel Back Cavity Fix Meter Box Jamb

3013 2D :



Bevel Back Cavity Fix Meter Box Sill


3014 2D :



DATE: 08/04/2025 check for updates and download
2D files in PDF, DWG or DXF format at www.niagara.nz


Bevel Back Cavity Fix **Pipe Penetration**

3015 2D :




Bevel Back Cavity Fix **Fascia Eaves**

3016 2D :




Bevel Back Cavity Fix **Apron**

3017 2D :




Bevel Back Cavity Fix Parapet Cap

3018 2D :




Bevel Back Cavity Fix Stucco - Below

3019 2D :




Bevel Back Cavity Fix **Stucco - Internal Corner**

3020 2D :




Bevel Back Cavity Fix **Stucco - External Corner**

3021 2D :




Bevel Back Cavity Fix **Profiled Metal - Above**

3022 2D :




Bevel Back Cavity Fix **Profiled Metal - Below**

3023 2D :




Bevel Back Cavity Fix **Profiled Metal - Abutting**

3024 2D :





Bevel Back Cavity Fix **Profiled Metal - Internal Corner**

3025 2D :



Bevel Back Cavity Fix **Profiled Metal - External Corner**


3026 2D :



FLASHING DIMENSIONS


Bevel Back Cavity Fix **Masonry Veneer - Below**

3027 2D :



Bevel Back Cavity Fix **Masonry Veneer - Abutting**


3028 2D :



FLASHING DIMENSIONS


Bevel Back Cavity Fix **Masonry Veneer - External Corner**

3029 2D :




Bevel Back Cavity Fix Masonry Veneer - Internal Corner

3030 2D :




Bevel Back Cavity Fix Above Waterproof Deck

3031 2D :



Bevel Back Cavity Fix Mid-Floor Junction

3032 2D :



DATE: 08/04/2025 check for updates and download
2D files in PDF, DWG or DXF format at www.niagara.nz

JOINTWOOD WEATHERBOARDS WARRANTY

1. Product Warranty

- 1.1 Niagara Sawmilling Company Limited (**Niagara**) warrants for a period of **15 years** from the date of purchase that its Jointwood Weatherboards (**Products**) will be free from production defects and will be resistant to cracking, rotting and damage from borer attacks, to the extent set out in Niagara's product literature current at the time of installation, subject always to the conditions and limits on liability below (**Warranty**).
- 1.2 The Jointwood Weatherboards Technical Manual set out the approved and recommended methods for cladding installation. To request a copy of the Jointwood Weatherboard Technical Manual, please phone toll free: 0800 36 78 46 (Monday to Friday 8am – 5pm), or email: sales@niagara.nz, or download online at www.niagara.nz

2. Conditions of Warranty

- 2.1 The Warranty is strictly subject to the following conditions:
 - 2.1.1 The Products must be installed by a competent and qualified builder, strictly in accordance with:
 - (a) the Jointwood Weatherboards Technical Manual current at the time of installation, utilising products specified in the Jointwood Weatherboard Technical Manual; and
 - (b) all relevant laws and regulations.

Where the Jointwood Weatherboards Technical Manual do not provide suitable detail for installation of the Products then installation must be in accordance with best trade practice determined in consultation with the relevant local or regional council or such other appropriate organisation or authority and the designer of the building works.

- 2.1.2 The Products must be maintained strictly in accordance with the Jointwood Weatherboards Technical Manuals. Further, all other products including coating and jointing systems applied to, or used in conjunction with, the Products must be applied, installed and maintained strictly in accordance with the relevant manufacturer's instructions and best trade practice.
- 2.1.3 The building works in which the Products have been incorporated must be designed and constructed in strict compliance with all relevant provisions of the current New Zealand Building Code, regulations and standards, and the building consent relating to the building works.
- 2.1.4 If any remedial work undertaken in relation to the Warranty involves re-coating of the Products, the customer acknowledges and agrees that there may be slight colour differences between the original and replacement Products due to the

effects of weathering and variations in materials over time.

3. Limits on Liability

- 3.1 Niagara will not be liable to the customer for any breach of Warranty unless the customer gives Niagara written notice of any claim for breach of Warranty within 30 days of the defect becoming reasonably apparent.
- 3.2 In any event, the customer's sole remedy under the Warranty is (at Niagara's discretion) that Niagara will either supply replacement Products, rectify the affected Products where such Products are capable of rectification, or pay for the reasonable cost of the replacement or rectification of the affected Products.
- 3.3 Aside from the remedy described in clause 3.2, Niagara will not be liable for any other losses or damages (whether direct or indirect) including property damage, personal injury, consequential loss, economic loss or loss of profits, whether arising under statute, contract, tort including negligence, or howsoever arising. Without limiting the foregoing, Niagara will not be liable for any claims, damages or defects arising from, or in any way attributable to:
 - 3.3.1 poor workmanship;
 - 3.3.2 poor design or detailing;
 - 3.3.3 incorrect design of the structure;
 - 3.3.4 settlement or structural movement and/or movement of materials to which the Products are attached;
 - 3.3.5 acts of God including, but not limited to, earthquakes, cyclones, floods or other severe weather conditions or unusual climatic conditions;
 - 3.3.6 efflorescence or performance of paint/coatings applied to the Products;
 - 3.3.7 normal wear and tear; or
 - 3.3.8 growth of mould, mildew, fungi, bacteria, or any organism on the surface of any Products (whether on the exposed or unexposed surfaces).
- 3.4 All warranties, conditions, liabilities and obligations other than those specified in this Warranty are excluded to the fullest extent permitted by law. The Warranty does not exclude or modify any legal rights a customer may have under the Consumer Guarantees Act 1993. Unless otherwise specified in writing at the time of sale, Niagara assumes no liability for the Products being fit for any particular purpose under the Building Act 2004, other legislation or at common law.



JOINTWOOD

WEATHERBOARDS



www.niagara.nz

SOUTH ISLAND SALES & DISTRIBUTION

 **0800 36 78 46**
 sisales@niagara.nz

 74 Kennington Road,
Invercargill 9871 - New Zealand

NORTH ISLAND SALES & DISTRIBUTION

 **0800 36 78 46**
 nisales@niagara.nz

 55D Parakiwai Road,
Cambridge 3493 - New Zealand