



Date: 08/02/2024

Product #: **AUA0075**

Coating: GREY ENAMEL

Customer:

Intended Use: Wood Kitchen Cabinet Component Parts

Shelf Life: 28 MONTHS

Specifications

Weight per Gallon: 9.845 Lbs		Flashpoint: 52 °F
Solids by Volume: 39.743 %		
Solids by Weight: 58.348 % (Theoretical)		
Viscosity:	Type: #2 EZ ZAHN @ 77F	24-30
Gloss: 14 TO 18		pH:
VOC (Theoretical): 4.10 Lb/Gallon		Color: GRAY
VOC (minus water and exempt solvents): 4.10 Lb/Gallon		491 g/liter
VHAP (Theoretical): 0.16 Lb/Lb Solid		491 g/liter
		2.17 Lb/Gal Solid

Other Information**Application Recommendations:**

Agitation:	Agitate well before and during use.
Catalyze:	Catalyze 6% BY VOLUME CXC4005 DO NOT EXCEED RECOMMENDED CATALYST LEVEL.
Reduction:	Reduce product to sprayable viscosity with MEK or as directed.
Dry Film Thickness:	The dry film thickness of the total finishing system is not to exceed 5.0 dry mils.
Cure:	Product must be adequately dried and cured to insure promoted properties and performance.
Clean up:	Lacquer Thinner
Application Method:	Spray
Theoretical Coverage:	701.85 sq ft per gallon at 1 mil - Dry

NOTES:

1. AGITATE WELL BEFORE AND DURING USE.
2. USE ONLY RECOMMENDED CATALYST AT RECOMMENDED LEVEL. DO NOT ADD ADD
3. CATALYZE NO MORE THAN THE AMOUNT NEEDED FOR ONE WORKING DAY. FOLLOW DEC.
4. USE ONLY RECOMMENDED RETARDERS, REDUCERS, AND/OR THINNERS.
5. STORE IN A COOL, DRY PLACE THAT IS OUT OF DIRECT SUNLIGHT.
6. AVOID CONTACT WITH METAL, OTHER THAN STAINLESS STEEL.
7. FOR ADDITIONAL INFORMATION ON THIS PRODUCT, REFER TO THE PRODUCT'S SDS

The data on this sheet represent typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. Axalta assumes no obligation or liability for use of this information. **UNLESS AXALTA AGREES OTHERWISE IN WRITING, AXALTA MAKES NO WARRANTIES, EXPRESS OR IMPLIED, AND DISCLAIMS ALL IMPLIED WARRANTIES INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE OR FREEDOM FROM PATENT INFRINGEMENT. AXALTA WILL NOT BE LIABLE FOR ANY SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES.** Your only remedy for any defect in this product is the replacement of the defective product, or a refund of its purchase price, at our option. The information in this sheet, as well as the products referenced herein, shall be considered "Confidential Information". Wet samples and uncured samples of these products shall be maintained as confidential and shall not be disclosed to any third party without the prior written permission of Axalta.