Technical Data Sheet | Fire



Reference No: FR -003 Issue Date: May 2018

AS ISO 9705-2003 and AS 5637.1:2005

The National Construction Code of Australia (NCC) and AS 5637.1:2015 stipulates the classification of materials by Group Number, which indicates the amount of time taken for the material being tested to reach flashover under AS ISO 9705 — 2003 test conditions. The NCC and AS 5637.1:2015 define flashover to be a Heat Release Rate of 1 MW, so materials are classified, in accordance with NCC 2016 spec Cl.10 and AS 5637.1 2015, by the time taken for the Heat Release Rate, as measured during the AS ISO 9705 test, to reach 1 MW per the scheme below;

- Group 1 Materials classified as Group 1 do not reach flashover after ten minutes exposure to a heat source delivering 100 kW immediately followed by a further ten minutes exposure to 300 kW.
- Group 2 Materials classified as Group 2 reach flashover after ten minutes of exposure to a 100 kW heat source.
- Group 3 Materials classified as Group 3 reach flashover after 2 minutes, but before 10 minutes of exposure to a 100 kW heat source.
- Group 4 Materials are classified as Group 4 is they reach flashover before 2 minutes of exposure to a 100 kW heat source.

The NCC and AS 5637.1:2015 also define the smoke growth rate index, or $SMOGRA_{RC}$ as a quantity which may be obtained from the smoke obscuration measurements obtained in the AS ISO 9705 test

SAS International Ceiling System classification

SAS International have carried out a series of Fire Tests in accordance with the above standard for our metal ceiling systems and associated products including:

- Perforated (Up to 22% free area) polyester powder coated metal panels
- Up to 30mm thickness mineral wool acoustic inlays (80 kg/m³ density) and/or Acoustic Fleece backing

The material subjected to this AS ISO 9705 test did not reach a Heat Release Rate of 1 MW during the 1200 second exposure period. Therefore the system has achieved a classification and smoke growth rate:

Classification: Group 1. SMOGRA_{RC} 4.4m²s⁻² x 1000

Further information with regards to SAS fire testing is available via our Technical Department.

SAS International | Fire Technical Data Sheet | Disclaimer

It should be noted that information contained within this document only provides guidance of SAS International products performance in relation to the detailed test conditions. SAS International would strongly recommend that any fire performance is reviewed by qualified and experienced professional and applied in-line with NATIONAL CONSTRUCTION REGULATIONS/CODES and demonstrates a suitable fire engineered solution to suit the requirement of the buildings design and end operational use.

SAS International® reserves the right to review, alter, amend or remove published data without notice as our policy is one of constant improvement. The information contained in this data sheet is believed to be correct at the date of publication. Whilst SAS International will endeavour to keep its publications up to date, readers will appreciate that between publications there may be pertinent changes in the law, or other developments affecting the accuracy of the information contained in this data sheet.