


BRECO *flex* CO., L.L.C.

High Precision Drive Components

The World Leader In Polyurethane Timing Belts

TIMING BELT BACKINGS

Materials and Characteristics



SUPERIOR TIMING BELT BACKINGS

Strength *and* Flexibility



BRECOflex CO., L.L.C., the pioneer and world leader in the polyurethane timing belt industry, offers high precision timing belts with a wide variety of backings for use in conveying, positioning, material handling, and related applications. We manufacture all backings to provide excellent wear resistance and resilience.

Some backings are multi-functional while others are highly specialized. The appropriate selection of the backing material depends on the individual application. Our engineers are available to specify timing belts with the backing that most effectively meets your requirements.

BRECOflex belts with backings, available in various thicknesses, offer different ranges of hardness, density, abrasion resistance, and coefficients of friction to suit your application. We utilize a heated chemical bonding process to adhere the backing to the belt. Superior know-how and state-of-the-art processes ensure a strong bond.

To meet the needs of your specific application, BRECOflex can mechanically rework the tooth side and/or the transport side of the belt. See pages 18-19 for more details.

There are many characteristics to consider when choosing a backing for your application. Some special considerations are shown below. For additional information, refer to the chart next to each backing material on the following pages.

Friction

The backing you choose depends on the transport item properties and the required grip. Choose high friction for a good carrying effect, low friction for accumulating conveyors. Note that when belt load increases so does friction and therefore heat. Choose a slider bed plate material that will have a minimum friction value against the belt. Friction value increases as temperatures rise and reduces at temperatures below freezing.

Drives With Back-Bending

Timing belts with backings are generally suitable for drives with back-bending. Very soft backings such as Sylomer should be set up with reduced pretensioning. Backings made of natural rubber such as Linatex, can be used for back-bending (back pulleys) but only to a limited extent. Please consult our engineering department for more detailed information.

Pulley Diameter


At low ambient temperatures, the flexibility of the backing reduces. You should therefore select larger pulley diameters than you would at normal temperatures. The flexibility of the timing belt also reduces at low temperatures.

The minimum diameters referenced for the backings in this catalog serve as a guideline. They apply at an ambient temperature of 20°C (68°F) and speed of 1 m/s, and assuming a low load burden. If the exact usage details are known, it is possible to reduce the diameters. Likewise the minimum specified pulley diameters apply for homogeneously applied backings of even thickness. Machined backings such as those with cuts or grooves cause notch effects and require much higher minimum diameters. In these cases, our applications engineers will be happy to assist you.

SUPERIOR TIMING BELT BACKINGS

Belt Construction

Timing Belt Properties



Temperature Effect

When transporting hot goods above approx. 80°C (176°F) the duration of contact should be as short as possible to avoid heating the belt's substructure to over 80°C (176°F). Limit exposure to heat to short distances and times then provide sufficient cooling for the remaining revolution period. At temperatures approximately 60°C (140°) and up, the tooth shear strength reduces slightly. If the teeth are subjected to major stress you should increase your safety factor.

Resistance


Material resistance needs to be evaluated for every application. The material resistance depends, among other factors, on the pH value, the concentration, the temperature and the influencing time of the medium. Simple oils generally have no damaging effect on the belt. Additives in the oil and temperatures over approx. 40°C (104°F) can reduce the longevity.

Larger Belts and Thick Backings

Please consult engineering support for backings over 75 mm wide and 2 mm thick because of the different processing properties that vary by material.

As a single source supplier, BRECOflex CO., L.L.C. can provide all of the drive components and accessories for our timing belts to insure the highest accuracy, perfect meshing and longest service life.


PULLEY DIAMETERS FOR LOW TEMPERATURES



TIMING BELT BACKINGS

For General Conveying

Linatex



Properties

Standard Thickness(mm)	2	3	4	5	6	8	10
Min. pulley diameter(mm)	60	70	80	90	100	110	120
Material / Hardness	95% natural rubber/ approx. 38 Shore A						
Tolerances	tolerance for total thickness (timing belt + coating) -1/+1.8mm (ground ± 0.2 mm possible)						
Temperature resistance	-40°C to +70°C (-40°F to 158°F)						
Chemical resistance	oil-proof to a limited extent, resistant to wet abrasion, water resistant, avoid exposure to direct sunlight						
Machinability	contours can be ground and milled to some extent						
Note	from 3mm coating thickness please ask for advice						


Linatrilite



Properties

Standard Thickness(mm)	3	5	6
Min. pulley diameter(mm)	50	60	80
Material / Hardness	Nitrile-based vulcanized material, approx. 55 Shore A		
Tolerances	tolerance for total thickness (timing belt + coating ± 0.4 mm) (ground ± 0.1 mm possible)		
Temperature resistance	-20°C to +110°C (-4°F to 230°F)		
Chemical resistance	resistant to oils, greases and other chemicals; water resistant		
Machinability	contours can be ground and milled and surface ground		

Supergrip



Properties


Standard Thickness(mm)	4
Min. pulley diameter(mm)	60
Material / Hardness	PVC, approx. 40 Shore A
Tolerances	tolerance for total thickness (timing belt + coating) ± 0.5 mm
Temperature resistance	<div style="display: flex; flex-direction: column; align-items: flex-start;"> <div style="display: flex; align-items: center; margin-bottom: 5px;"> <div style="width: 15px; height: 15px; background-color: #4CAF50; margin-right: 5px;"></div> -25°C to +70°C (-13°F to 158°F) </div> <div style="display: flex; align-items: center; margin-bottom: 5px;"> <div style="width: 15px; height: 15px; background-color: #004D40; margin-right: 5px;"></div> -25°C to +70°C (-13°F to 158°F) </div> <div style="display: flex; align-items: center;"> <div style="width: 15px; height: 15px; border: 1px solid black; margin-right: 5px;"></div> -10°C to +110°C (14°F to 230°F) </div> </div>
Chemical resistance	limited resistance to solvents, oils and greases; resistant to acids and alkalis

Available Colors:

TIMING BELT BACKINGS

For General Conveying


PU 385



Properties

Standard Thickness(mm)	2	3	4	5	6
Min. pulley diameter(mm)	60	80	120	150	180
Material / Hardness	polyurethane/approx. 85 Shore A				
Tolerances	tolerance for total thickness (timing belt + coating) ± 0.4 mm (ground ± 0.1 mm possible)				
Temperature resistance	-20°C to +80°C (-4°F to 176°F)				
Chemical resistance	resistant to simple oils and grease, petrol, ozone				
Machinability	contours can be ground and milled and surface ground				
Note	some pitches available with an extruded-on version called <i>T-cover</i> , please refer to pg. 130 in the B212 Polyurethane Timing Belts Catalog.				

Minigrip




Available Colors: ■ ■

Properties

Standard Thickness(mm)	1.5	
Min. pulley diameter(mm)	30	
Material / Hardness	PVC, approx. 50 Shore A	
Tolerances	tolerance for total thickness (timing belt + coating) ± 0.5 mm	
Temperature resistance	■ -15°C to +90°C (5°F to 194°F) ■ -10°C to +110°C (14°F to 230°F)	
Chemical resistance	resistance to solvents, oils and greases; resistant to acids and alkalis	

PVC Blue




Properties

Standard Thickness(mm)	1	(2 / 3 / 4 / 5 / 6 mm upon request)
Min. pulley diameter(mm)	30	
Material / Hardness	PVC, approx. 65 Shore A	
Tolerances	tolerance for total thickness (timing belt + coating) ± 0.5 mm	
Temperature resistance	-15°C to +90°C (5°F to 194°F)	
Chemical resistance	limited resistance to solvents, oils and greases; resistant to acids and alkalis	
Other areas of use	pharmaceutical industry	

TIMING BELT BACKINGS


For General Conveying

PU Yellow



Properties					
Standard Thickness(mm)	2	3	4	5	6
Min. pulley diameter(mm)	70		90	110	
Material / Hardness	polyurethane/approx. 55 Shore A				
Tolerances	tolerance for total thickness (timing belt + coating ± 0.4 mm) (ground ± 0.1 mm possible)				
Temperature resistance	-30°C to +70°C (-22°F to 158°F)				
Chemical resistance	resistant to simple oils and grease, petrol, ozone				
Machinability	contours can be ground and milled and surface ground				
Other areas of use	paper, cardboard, glass conveying.				


D15 Polyurethane



Available Colors:

Properties					
Standard Thickness(mm)	2	3	4	5	6
Min. pulley diameter(mm)	60	80		100	
Material / Hardness	polyurethane/approx. 70 Shore A				
Tolerances	tolerance for total thickness (timing belt + coating) ± 0.6 mm (ground ± 0.1 mm possible)				
Temperature resistance	-20°C to +80°C (-4°F to 176°F)				
Chemical resistance	resistant to simple oils and greases, good resistance to ozone, UV radiation				
Machinability	contours can be ground and milled and surface ground				

NBR 65




Properties		
Standard Thickness(mm)	1.5	3
Min. pulley diameter(mm)	60	80
Material / Hardness	nitrile rubber, approx. 60-70 Shore A	
Tolerances	tolerance for total thickness (timing belt +coating) ± 0.6 mm (ground ± 0.2 mm possible)	
Temperature resistance	-35°C to +70°C (-31°F to 158°F)	
Chemical resistance	resistant to oils and to some extent acids and alkalis	
Machinability	contours can be ground and milled to some extent and surface ground	

TIMING BELT BACKINGS

For General Conveying


TR2



Properties

Standard Thickness(mm)	2.5 / Groove depth: 1.4
Min. pulley diameter(mm)	80
Material / Hardness	polyurethane, approx. 85 Shore A
Tolerances	tolerance for total thickness (timing belt + coating) ± 0.5 mm
Temperature resistance	-20°C to +80°C (-4°F to 176°F)
Chemical resistance	resistant to simple oils, grease, petrol, and ozone


WM 385



Properties

Standard Thickness(mm)	4
Min. pulley diameter(mm)	120
Material / Hardness	polyurethane, approx. 85 Shore A
Tolerances	tolerance for total thickness (timing belt + coating) ± 0.5 mm
Temperature resistance	-20°C to +80°C (-4°F to 176°F)
Chemical resistance	resistant to simple oils, grease, petrol, and ozone

NP 385




Properties

Standard Thickness(mm)	4
Min. pulley diameter(mm)	120
Material / Hardness	polyurethane, approx. 85 Shore A
Tolerances	tolerance for total thickness (timing belt + coating) ± 0.4 mm
Temperature resistance	-20°C to +80°C (-4°F to 176°F)
Chemical resistance	resistant to simple oils, grease, petrol, and ozone

TIMING BELT BACKINGS

For General Conveying


RP 430



Properties


Standard Thickness(mm)	2	3	4	5	6
Min. pulley diameter(mm)	40		50	70	
Material / Hardness	natural rubber, approx. 39 Shore A				
Tolerances	tolerance for total thickness (timing belt + coating ± 0.4 mm) (ground ± 0.1 mm possible)				
Temperature resistance	-35°C to +80°C (-31°F to 176°F)				
Chemical resistance	resistant to simple oils and grease				
Machinability	contours can be ground and milled and surface ground				

Celloflex



Properties


Standard Thickness(mm)	2	3	4	5	6	8	10
Min. pulley diameter(mm)	40	60		80		100	120
Material / Hardness	microcellular elastomer polyurethane/ approx. 350 kg/m ³						
Tolerances	tolerance for total thickness (timing belt + coating) ± 0.7 mm						
Temperature resistance	-30°C to +80°C (-22°F to 176°F)						
Chemical resistance	resistant to simple oils and grease, ozone						
Machinability	contours can be ground and milled and surface ground						



TIMING BELT BACKINGS

For General Conveying


Porol




Properties

Standard Thickness(mm)	3	5	10
Min. pulley diameter(mm)	40	60	80
Material / Hardness	closed-cell cellular rubber, 160-200 kg/m ³		
Tolerances	tolerance for total thickness (timing belt + coating) ±0.7 mm		
Temperature resistance	-40°C to +75°C (-40°F to 167°F)		
Chemical resistance	resistant to water, seawater, methanol, acetone, detergent, acids and alkalis		

Sylomer




Properties

Standard Thickness(mm)	6	12	(Other thickness upon request)
Min. pulley diameter(mm)	60	80	
Material / Hardness	mixed cell polyurethane, 220 kg/m		
Tolerances	tolerance for total thickness (timing belt + coating) ±0.7mm (ground ±0.3 mm possible)		
Temperature resistance	 -30°C to +70°C (-22°F to 158°F)		
Chemical resistance	resistant to simple oils and grease		
Machinability	contours can be ground and milled to some extent and surface ground		
Note	Sylomer colors offer different characteristics, contact applications engineering for more details		

Available Colors: 

Correx Beige




Properties

Standard Thickness(mm)	6	10
Min. pulley diameter(mm)	80	120
Material / Hardness	para rubber, approx. 36 Shore A	
Tolerances	tolerance for total thickness (timing belt + coating) ±0.7 mm (ground ±0.2 mm possible)	
Temperature resistance	up to approx. +70°C (158°F)	
Chemical resistance	resistant to simple oils and grease, ozone	
Machinability	contours can be ground and milled to some extent and surface ground	

TIMING BELT BACKINGS

For General Conveying


PU 60



Properties


Standard Thickness(mm)	2	3	4	5	6
Min. pulley diameter(mm)	80	80	120	150	180
Material / Hardness	polyurethane, approx. 60 Shore A				
Tolerances	tolerance for total thickness (timing belt + coating) ± 0.4 mm (ground) ± 0.1 mm possible				
Temperature resistance	-20°C to +80°C (4°F to 176°F)				
Chemical resistance	simple oils and fats, petrol, ozone				
Areas of use	general transport (glass, wood, metal, paper, textiles cardboard, wet areas)				
Machinability	contour grinding and milling as well as surface grinding possible				

Linaplus



Properties


Standard Thickness(mm)	3	5	6
Min. pulley diameter(mm)	70	90	100
Material / Hardness	vulcanized natural rubber, approx. 38 Shore A		
Tolerances	tolerance for total thickness (timing belt + coating) -1/+1.8mm (ground ± 0.2 mm possible)		
Temperature resistance	-40°C to +70°C (-40°F to 158°F)		
Chemical resistance	resistant to chemicals; material does not leave pressure marks		
Machinability	contours can be ground and milled and surface ground		
Note	Formerly FDA approved, no longer approved as of July 2025		



TIMING BELT BACKINGS

For Food Processing

40 TPE FDA Black




Available Colors:

Properties

Standard Thickness(mm)	2	4	6	8
Min. pulley diameter(mm)	60	80	100	100
Material / Hardness	thermoplastic elastomer, approx. 41 Shore A			
Tolerances	tolerance for total thickness (timing belt +coating) ± 0.4 mm (ground) ± 0.1 mm			
Temperature resistance	-40°C to +80°C (-40°F to 176°F)			
Chemical resistance	very good resistance in water and water based solvents. Not recommended for fats, oils or petrol.			
Areas of use	general transport (glass, wood, metal, paper, textiles, cardboard, wet areas) Food and FDA compliant.			
Machinability	grinding and milling possible to a limited extent.			
Note	FDA approval according to EU 10 / 2011. / Not available in combination with BRECObasic.			

PVC White FDA




Available Colors:

Properties

Standard Thickness(mm)	White 1/ Blue 1 or 2	(2 / 3 / 4 / 5 / 6 mm upon request)
Min. pulley diameter(mm)	60	
Material / Hardness	PVC, approx. 48 Shore A / Blue 65 Shore A	
Tolerances	tolerance for total thickness (timing belt + coating) ± 0.5 mm	
Temperature resistance	-10°C to +110°C (14°F to 230°F)	
Chemical resistance	resistant to oils, greases, acids and alkalis	
Note	FDA approval according to Regulations EU 10-2011	

PVC White Herringbone FDA




Properties

Standard Thickness(mm)	3
Min. pulley diameter(mm)	60
Material / Hardness	PVC, approx. 65 Shore A
Tolerances	tolerance for total thickness (timing belt + coating) ± 0.5 mm
Temperature resistance	-10°C to + 110°C (14°F to 230°F)
Chemical resistance	resistant to oils, greases, acids and alkalis
Note	FDA approval according to Regulations EU 10-2011
Note	The alignment of the herringbone pattern on the belt may differ from what is shown in the photo, as it cannot be guaranteed to be perfectly centered. Also, it will have multiple V-pattern for wider widths.

TIMING BELT BACKINGS

For Food Processing

Supergrip White FDA




Properties	
Standard Thickness(mm)	3
Min. pulley diameter(mm)	60
Material / Hardness	PVC, approx. 38 Shore A
Tolerances	tolerance for total thickness (timing belt + coating) ± 0.5 mm
Temperature resistance	-10°C to +110°C (-14°F to 230°F)
Chemical resistance	resistant to oils, greases, acids and alkalis
Note	FDA approval according to Regulations EU 10-2011

White Nub FDA



Properties	
Standard Thickness(mm)	1.6
Min. pulley diameter(mm)	60
Material / Hardness	PVC, approx. 55 Shore A
Tolerances	tolerance for total thickness (timing belt+coating) ± 0.5 mm
Temperature resistance	-20°C to + 80°C (-4°F to 176°F)
Chemical resistance	resistant to simple oils and fats
Note	FDA approval according to Regulations EU 10-2011

Silicone Endless FDA




Available Colors:

Properties							
Standard Thickness(mm)	2	3	4	5	6	8	10
Min. pulley diameter(mm)	60	70	80	90	100	110	120
Material / Hardness	Silicone, approx. 35 Shore A						
Tolerances	tolerance for total thickness (timing belt +coating) ± 0.1 mm						
Temperature resistance	-20°C to +100°C (4°F to 212°F)						
Chemical resistance	Good resistance to ink, dirt and adhesives						
Areas of use	Printing, high temperature resistance, high friction, ground or sealed surface, FDA compliant						
Note	FDA approval according to Regulations EU 10-2011						

TIMING BELT BACKINGS

For High Temperature


TT 60



Properties

Standard Thickness(mm)	2
Min. pulley diameter(mm)	120
Material / Hardness	polyester fleece
Tolerances	tolerance for total thickness (timing belt + coating) ± 0.4 mm (ground ± 0.1 mm possible)
Temperature resistance	-20°C to +110°C (14°F to 230°F)
Chemical resistance	resistant to oils and greases; electrostatic properties
Areas of use	glass industry, as a conveyor belt in a warm area


EPDM Endless



Properties

Standard Thickness(mm)	2	4	6
Min. pulley diameter(mm)	60	80	120
Material / Hardness	Rubber, approx. 65 Shore A		
Tolerances	tolerance for total thickness (timing belt + coating) ± 0.1 mm		
Temperature resistance	-40°C to +120°C (-40°F to 248°F)		
Chemical resistance	Very good resistance to acids and alkalis, weathering resistant		

Chromeleder




Properties

Standard Thickness(mm)	2	3
Min. pulley diameter(mm)	100	120
Material / Hardness	leather tanned with chromium salts	
Tolerances	tolerance for total thickness (timing belt + coating) ± 0.7 mm	
Temperature resistance	-10°C to +120°C (14°F to 248°F)	
Chemical resistance	resistant to oils and greases; weather resistant	
Potential applications	transportation of oil and grease soaked parts, transportation of sheet metal and pipes	

TIMING BELT BACKINGS

For High Temperature

PTFE FDA




Available Colors:

Properties

Standard Thickness(mm)	0.25
Min. pulley diameter(mm)	40
Material / Hardness	Polytetrafluoroethylene, approx. 54 Shore D
Tolerances	tolerance for total thickness (timing belt+coating) ± 0.2 mm
Temperature resistance	-200°C to +260°C (-328°F to 500°F)
Chemical resistance	good resistance to many acids, bases and solvents

Viton



Properties


Standard Thickness(mm)	2	4
Min. pulley diameter(mm)	80	100
Material / Hardness	synthetic fluoroelastomer, approx. 70-80 Shore A	
Tolerances	tolerance for total thickness (timing belt + coating) ± 0.6 mm (ground ± 0.2 mm possible)	
Temperature resistance	-10°C /190°C (14°F /374°F) (up to 275°C for short periods)	
Chemical resistance	very good resistance to oils, greases, hydrocarbons, acids; impermeable to gas and water vapor	
Machinability	contours can be ground and milled and surface ground	
Potential Applications	transportation of sensitive parts, cardboard packaging, transportation of glass and metal parts	



TIMING BELT BACKINGS

For Reduced Friction


PAR



Properties

Standard Thickness(mm)	0.5	0.8
Min. pulley diameter(mm)	15	25
Material / Hardness	polyamid	
Tolerances	± 0.2 mm	
Temperature resistance	-20°C to +50°C (4°F to 122°F)	
Chemical resistance	resistant to simple oils and grease	


PAZ



Properties

Standard Thickness(mm)	0.5	0.8
Min. pulley diameter(mm)	15	25
Material / Hardness	polyamid	
Tolerances	± 0.2 mm	
Temperature resistance	-20°C to +50°C (4°F to 122°F)	
Chemical resistance	resistant to simple oils and grease	
Note	Material can only be applied during extrusion process	


PAZ-PAR



Properties

Standard Thickness(mm)	0.5	0.8
Min. pulley diameter(mm)	15	25
Material / Hardness	polyamid	
Tolerances	± 0.2 mm	
Temperature resistance	-20°C to +50°C (4°F to 122°F)	
Chemical resistance	resistant to simple oils and grease	

PAZ-PAR, Anti-Static



Properties



Standard Thickness(mm)	0.6
Min. pulley diameter(mm)	20
Material / Hardness	approx. 0.5mm PU 385, top layer 0.1mm anti-static fabric
Tolerances	tolerance for total thickness (timing belt + coating) ±0.4mm
Conductance	10 ⁵ ohm when new
Potential applications	accumulation conveyors for electrical components

TIMING BELT BACKINGS

Machined Backings


Custom Machined Backings

Certain backings allow for special machining and processing to provide for synchronous conveying and positioning of goods. Pockets, contours, slots, holes, etc. can be precisely machined for each requirement. Please contact Applications Engineering for assistance.



Reduced Stress Concentration

Covered timing belts have reduced bending ability. Therefore, larger diameter pulleys and idlers must be used in order to reduce stress concentration. The bending flexibility can be increased by up to 30% by properly placing stress reliefs in the backing material.



Linatex (Cross milled)


Notes to the Designer:

- Additives in oils and temperatures above 40°C (140°F) will reduce belt life
- The coefficient of friction changes with temperature
- Low ambient temperatures reduce flexibility of the backing material. Pulley and idler diameters must be increased accordingly.
- Covered belt applications may require increased pulley and idler diameters in standard and back bending operations.



TIMING BELT BACKINGS

Backing Chart




NOTE: Coefficient of friction will vary depending on the objects being conveyed.

TIMING BELT BACKINGS


Machined Timing Belts

Custom Machined Timing Belts


BRECOflex CO., L.L.C. can mechanically process timing belts for special functional characteristics. Timing belts with thick backs offer a broad range of possibilities for design engineers especially for mechanical processing. Please note that timing belts with thicker backs are less flexible and require toothed pulleys with larger diameters. Better flexibility is achieved through transverse grooves or slits.



- Improved belt width tolerance
- Less lateral movement
- Used to more accurately position mechanical modifications (i.e. profiles, perforations, etc.)




- Improved belt thickness tolerance
- Consistent belt back surface finish and friction
- Roughened belt back for spliced and welded "V" belts
- Standard for truly endless "BFX" belts > 720 mm
- Available for spliced and welded "V" belts > 450mm



- Typically used with extra thick belt back "DR" or "T-Cover"
- Used for small parts conveying
- Used for incline conveying
- Standard and custom configurations available
- Increased flexibility


TIMING BELT BACKINGS

Machined Timing Belts



Longitudinal Machining

- Typically used with extra thick belt back "DR" or "T-Cover" for more design possibilities
- Used for longitudinal product conveying
- Combined with perforations for vacuum applications
- Used to align product during handling



Perforating

- Used for vacuum applications
- Intricate hole patterns possible
- Used with tension free zones resulting in clean holes with no tension member interference
- Complex perforation shapes possible



TIMING BELT BACKINGS

Chemical Resistance Charts

Compatibility Legend



This chart does not refer to chemical blends or combination of chemical exposures which may react differently. Sample sections of belt or back cover materials are available for testing purposes. We recommend testing any chemical combination to confirm specific compatibility. Typically, an immersion test may be performed and the belt periodically examined for softening or hardening. Please contact Applications Engineering for questions regarding chemicals not listed on this chart or to discuss your design.

	Polyurethanes	PVC Back Covers		Rubber Back Covers		Other Covers	
	Belting and Back Covers (PU385, PU Yellow, D15)	Standard (White Nub, Herringbone, Supergrip Blue)	Oil Resistant (Supergrip Green, Minigrip)	Nitrile (Linatrilite, NBR65)	Natural (Linatex, RP430)	Silicone	PTFE (Teflon)
Acetaldehyde	★	★	★	★	☆☆	☆☆	☆☆☆☆
Acetic Acid (Glacial)	☆☆	★	★	☆☆	☆☆	☆☆☆☆	☆☆☆☆
Acetic Acid - 30%	☆☆	☆☆	☆☆	☆☆	☆☆☆☆	☆☆☆☆	☆☆☆☆
Acetic Anhydride	☆☆☆	☆☆	☆☆	☆☆	☆☆	☆☆	☆☆☆☆
Acetone	★	★	★	★	★	☆☆	☆☆☆☆
Alcohols	★	☆☆	☆☆	☆☆☆☆	☆☆☆☆	☆☆☆☆	☆☆☆☆
Aluminum Carbonate	☆☆☆☆	☆☆☆☆	☆☆☆☆	☆☆☆☆	☆☆☆☆	☆☆☆☆	☆☆☆☆
Aluminum Chloride	☆☆☆☆	☆☆☆☆	☆☆☆☆	☆☆☆☆	☆☆☆☆	☆☆☆☆	☆☆☆☆
Aluminum Nitrate	☆☆☆☆	☆☆☆☆	☆☆☆☆	☆☆☆☆	☆☆☆☆	☆☆☆☆	☆☆☆☆
Ammonium Hydroxide	☆☆☆	☆☆☆☆	☆☆☆☆	★	★	☆☆☆☆	☆☆☆☆
Ammonium Nitrate	☆☆☆☆	☆☆☆☆	☆☆☆☆	☆☆☆☆	★	☆☆☆☆	☆☆☆☆
Ammonium Phosphate	☆☆☆☆	☆☆☆☆	☆☆☆☆	☆☆☆☆	☆☆☆☆	☆☆☆☆	☆☆☆☆
Ammonium Sulfate	☆☆☆☆	☆☆☆☆	☆☆☆☆	☆☆☆☆	☆☆☆☆	☆☆☆☆	☆☆☆☆
Animal Fats	☆☆	★	☆☆	☆☆	★	☆☆	☆☆☆☆
Asphalt	☆☆☆	★	☆☆	☆☆	★	☆☆	☆☆☆☆
Barium Chloride	☆☆☆☆	☆☆☆☆	☆☆☆☆	☆☆☆☆	☆☆☆☆	☆☆☆☆	☆☆☆☆
Borax	☆☆☆☆	☆☆☆☆	☆☆☆☆	☆☆	☆☆	☆☆☆☆	☆☆☆☆
Boric Acid	☆☆☆☆	☆☆☆☆	☆☆☆☆	☆☆☆☆	☆☆☆☆	☆☆☆☆	☆☆☆☆
Butter	☆☆☆	★	☆☆	☆☆☆☆	★	☆☆	☆☆☆☆
Calcium Chloride	☆☆☆☆	☆☆☆☆	☆☆☆☆	☆☆☆☆	☆☆☆☆	☆☆☆☆	☆☆☆☆
Calcium Hydroxide	☆☆☆	☆☆☆☆	☆☆☆☆	☆☆☆☆	☆☆☆☆	☆☆☆☆	☆☆☆☆
Calcium Nitrate	☆☆☆☆	☆☆☆☆	☆☆☆☆	☆☆☆☆	☆☆☆☆	☆☆☆☆	☆☆☆☆

TIMING BELT BACKINGS

Chemical Resistance Charts

	Polyurethanes	PVC Back Covers		Rubber Back Covers		Other Covers	
	Belting and Back Covers (PU385, PU Yellow, D15)	Standard (White Nub, Herringbone, Supergrip Blue)	Oil Resistant (Supergrip Green, Minigrip)	Nitrile (Linatrilite, NBR65)	Natural (Linatex, RP430)	Silicone	PTFE (Teflon)
Carbolic Acid	★	★	★	★	★	★	★★★★
Castor Oil	★★★★	★	★★★★	★★★★	★	★★★★	★★★★
Chlorinated Solvents	★	★	★	★	★	★★	★★★★
Chlorine Solutions	★★	★★	★★	★★	★★★★	★★	★★★★
Citric Acid	★★★★	★★★★	★★★★	★★★★	★★★★	★★★	★★★★
Coal	★★★★	★★	★★★★	★★★★	★	★★★★	★★★★
Coconut Oil	★★★★	★	★★★	★★★★	★	★★	★★★★
Copper Sulfate	★★★★	★★★★	★★★★	★★★★	★★★	★★★★	★★★★
Corn Oil	★★★	★	★★★	★★★★	★	★★★	★★★★
Cotton Seed Oil	★★★	★	★★★	★★★★	★	★★★	★★★★
Denatured Alcohol	★	★★	★★	★★★★	★★★★	★★★	★★★★
Diesel Fuel	★★★★	★	★★★	★★★★	★	★★	★★★★
Ethyl Alcohol	★	★★	★★	★★★★	★★★★	★★★	★★★★
Ethyl Cellulose	★	★★	★★	★★★★	★★★★	★★★★	★★★★
Ethylene Glycol	★★★	★★	★★	★★★★	★★★	★★★	★★★★
Fatty Acids	★★★	★	★★	★★★	★	★★★	★★★★
Ferric Chloride	★★★★	★★★★	★★★★	★★★★	★★★★	★★★★	★★★★
Ferric Sulfate	★★★★	★★★★	★★★★	★★★★	★★★★	★★★★	★★★★
Formaldehyde	★★★★	★★★★	★★★★	★★★★	★★★	★	★★★★
Fuel Oils	★★	★	★★	★★★★	★	★★	★★★★
Furfural	★	★	★	★★★★	★	★★★★	★★★★
Gasoline	★★★	★	★	★★★★	★	★★	★★★★
Glucose	★★★★	★★★★	★★★★	★★★★	★★★★	★★★★	★★★★
Glycerine	★★★★	★★★★	★★★★	★★★★	★★★★	★★★★	★★★★
Hydraulic Oil	★	★	★★	★★	★	★★	★★★★
Hydrochloric Acid	★	★★	★★	★	★★	★★	★★★★
Kerosene	★	★	★	★★	★	★★	★★★★
Lacquers	★	★	★	★	★	★	★
Lard	★★	★	★★	★★	★	★★★★	★★★★
Limestone	★★★★	★★★★	★★★★	★★★★	★★★★	★★★★	★★★★
Linseed Oil	★	★	★★	★★★★	★	★★	★★★★
Lubricating Oil	★★	★	★★	★★★★	★	★★	★★★★
Magnesium Chloride	★★★★	★★★★	★★★★	★★★★	★★★★	★★★★	★★★★
Magnesium Hydroxide	★★★★	★★★★	★★★★	★★	★★	★★★★	★★★★
Magnesium Sulfate	★★★★	★★★★	★★★★	★★★★	★★	★★★★	★★★★
Methyl Alcohol	★	★★	★★	★★★★	★★★★	★★	★★★★

POLYURETHANE MATERIAL

Polyurethane	Color	Hardness	FDA 21CFR	Hydrolysis Resistant	Features	Polyurethane	Color	Hardness	FDA 21CFR	Hydrolysis Resistant	Features
TPU-ST1	White	92 shore A	No	Med	Standard Polyurethane	TPU AU2	Clear	95 Shore A	Yes	High	Food grade, wash down
TPU-FDA1	Clear	92 Shore A	Yes	Low	Food grade, non-wash down	TPU AU3	Gray	88 Shore A	No	Low	Resistant to oils, and fats
TPU-FDA2	Clear	85 Shore A	Yes	Low	Food grade, non-wash down	BRECOprotect®	Blue	92 Shore A	Yes	High	Sealed cords FDA wash down
TPU-AU1	Clear	92 Shore A	Yes	High	Food grade, wash down						

TIMING BELT BACKINGS

Chemical Resistance Charts

	Polyurethanes	PVC Back Covers		Rubber Back Covers		Other Covers	
	Belting and Back Covers (PU385, PU Yellow, D15)	Standard (White Nub, Herringbone, Supergrip Blue)	Oil Resistant (Supergrip Green, Minigrip)	Nitrile (Linatrilite, NBR65)	Natural (Linatex, RP430)	Silicone	PTFE (Teflon)
Methyl Ethyl Ketone	★	★	★	★	★	★★	★★★★
Mineral Oil	★★★★	★★	★★★★	★★★★	★	★★	★★★★
Mineral Spirits	★	★	★	★★	★	★★	★★★★
Molasses	★★★★	★★★★	★★★★	★★★★	★★★★	★★★★	★★★★
Naptha	★	★	★	★★	★	★★	★★★★
Nitric Acid	★	★★	★★	★	★	★★	★★★★
Oil Sands	★★★★	★	★★★★	★★★★	★	★★	★★★★
Oil Shale	★★★★	★	★★★★	★★★★	★	★★	★★★★
Ozone	★★★★	★★	★★	★	★	★★	★★★★
Paraffin	★★	★★	★★★★	★★★★	★	★★★★	★★★★
Peanut Oil	★★	★	★★	★★	★	★★	★★★★
Petroleum Oils	★★	★	★★	★★★★	★	★★	★★★★
Phosphate Ore	★★★★	★★	★★	★★★★	★★★★	★★★★	★★★★
Phosphoric Acid	★★	★★★★	★★★★	★★	★★	★★	★★★★
Pine Oil	★★	★★	★★★★	★★★★	★	★★	★★★★
Potassium Chloride	★★★★	★★★★	★★★★	★★★★	★★★★	★★★★	★★★★
Potassium Hydroxide	★★	★★★★	★★★★	★★	★★	★★	★★★★
Potassium Nitrate	★★★★	★★★★	★★★★	★★★★	★★★★	★★★★	★★★★
Potassium Sulfate	★★★★	★★★★	★★★★	★★★★	★★	★★★★	★★★★
Silicone Oil	★★★★	★★	★★★★	★★★★	★★	★★★★	★★★★
Soda Ash	★★★★	★★★★	★★★★	★★★★	★★★★	★★★★	★★★★
Sodium Bicarbonate	★★★★	★★★★	★★★★	★★★★	★★★★	★★★★	★★★★
Sodium Bisulfate	★★★★	★★★★	★★★★	★★★★	★★	★★★★	★★★★
Sodium Chloride	★★★★	★★★★	★★★★	★★★★	★★★★	★★★★	★★★★
Sodium Hydroxide	★★	★★★★	★★★★	★★	★★★★	★★	★★★★
Sodium Hypochlorite	★★	★★	★★	★★	★★	★★	★★★★
Sodium Nitrate	★★★★	★★★★	★★★★	★★	★★	★★★★	★★★★
Sodium Peroxide	★★★★	★★★★	★★★★	★★	★★	★★★★	★★★★
Sodium Phosphates	★★★★	★★★★	★★★★	★★★★	★★★★	★★★★	★★★★
Sodium Silicate	★★★★	★★★★	★★★★	★★★★	★★★★	★★★★	★★★★
Sodium Sulfate	★★★★	★★★★	★★★★	★★★★	★★	★★★★	★★★★
Sodium Sulfide	★★★★	★★★★	★★★★	★	★★	★★★★	★★★★
Soybean Oil	★★	★★	★★	★★★★	★	★★	★★★★
Sugar Beets	★★★★	★★★★	★★★★	★★★★	★★★★	★★★★	★★★★
Sugar Cane	★★★★	★★★★	★★★★	★★★★	★★★★	★★★★	★★★★
Sufur	★★★★	★★★★	★★★★	★	★	★★★★	★★★★

Reference: National Industrial Belting Association (1992). Chemical Resistance Chart.

TENSION MEMBER MATERIAL

Material	Corrosion Resistance	Features
Steel	Low	Standard cord, best stiffness and strength
Stainless Steel	High	80% of standard strength and equal stiffness
BRECOprotect®	High	Sealed steel cords in AU1 polyurethane
Kevlar (Aramid)	High	60% more elongation, absorbs water

TIMING BELT BACKINGS

Chemical Resistance Charts

	Polyurethanes	PVC Back Covers		Rubber Back Covers		Other Covers	
	Belting and Back Covers (PU385, PU Yellow, D15)	Standard (White Nub, Herringbone, Supergrip Blue)	Oil Resistant (Supergrip Green, Minigrip)	Nitrile (Linatrilite, NBR65)	Natural (Linatex, RP430)	Silicone	PTFE (Teflon)
Sulfuric Acid	★★	★★★★	★★★★	★	★★	★★	★★★★★
Tar (Bituminous)	★★★★★	★★	★★★★★	★★★★★	★	★★★★★	★★★★★
Tartaric Acid	★★★★★	★★★★★	★★★★★	★★★★★	★★★★	★★★★★	★★★★★
Tetrachloroethylene	★	★	★	★	★	★	★
Toluene	★	★	★★	★★	★	★	★★★★★
Trichloroethylene	★	★	★	★	★	★	★
Trichloroethane	★	★	★	★	★	★	★★★★★
Turpentine	★	★	★★	★★★★★	★	★★	★★★★★
Ultra-Violet	★★★★	★★★★★	★★★★★	★★	★★★★	★★★★★	★★★★★
Urea	★★★★★	★★★★★	★★★★★	★★★★★	★★★★★	★★★★★	★★★★★
Urine	★★★★	★★★★★	★★★★★	★★★★	★★★★	★★★★★	★★★★★
Vegetable Oils	★★★★	★	★★★★	★★★★★	★	★★★★	★★★★★
Vinegar	★★★★★	★★★★★	★★★★★	★★★★	★★★★	★★★★	★★★★★
Water	★★★★★	★★★★★	★★★★★	★★★★★	★★★★★	★★★★★	★★★★★
Wood Oils	★★★★★	★★	★★★★★	★★★★★	★	★★★★★	★★★★★
Xylene	★	★	★	★	★	★	★★★★★
Zinc Chloride	★★★★★	★★★★★	★★★★★	★★★★★	★★★★★	★★★★★	★★★★★
Zinc Sulfate	★★★★★	★★★★★	★★★★★	★★★★★	★★★★	★★★★★	★★★★★

Tension Member Selection: Tension member, or cord selection is important for corrosive environments. Standard steel tension members have a zinc coating but are not suitable for long life in wash down environments. Stainless steel or BRECOprotect® with its sealed encapsulated cords are recommended for continuous or intermittent wash down.

Water or Oil-based Compounds: When the base for the chemical compound can be prevented from absorbing into the belt polyurethane the resistance is higher to other parts of the compound that would otherwise be more harmful. Many compounds are water based so polyurethane with high resistance to water absorption (hydrolysis) may be advisable. BRECOflex CO., L.L.C. offers specifically formulated alternative polyurethanes and tension member materials that can help combat these attacks.

Intermittent Contact: Many timing belts are utilized in the food or medical industry where periodically the belts need to be cleaned. It may be possible to use chemicals rated as conditional or unacceptable such as chlorine compounds when a follow-up rinsing process is performed. Please contact us for material samples to confirm acceptability for your use.



ISO 9001 CERTIFIED COMPANY

BRECOflex CO., L.L.C.

High Precision Drive Components

Contact Us

222 Industrial Way West, Eatontown, NJ 07724

Tel: 732-460-9500 • Fax: 732-542-6725

www.brecoflex.com • email: info@brecoflex.com

Copyright 2026 BRECOflex CO., L.L.C. • BRECO®, BRECOFLEX® & ATN® are registered trademarks of BRECO Antriebstechnik GmbH • ARC-POWER® is a registered trademark of BRECOflex CO., L.L.C. • Kevlar® is a registered trademark of DuPont Patents Pending. Specifications are subject to change without prior notice.

All recommendations for the use of the products described herein and all other data or information set forth in this publications, whether concerning such products or otherwise, are furnished without any guarantee, warranty representations or inducement of any kind whether expressed or implied, including but not limited to warranties of merchantability and fitness for a particular purpose. BRECOflex CO., L.L.C. expressly disclaims liability under any theory, including without limitation, contract negligence, misrepresentation or breach of any obligation relating to the recommendation, data or information set forth herein. Readers and customers are encouraged to conduct their own test before using any product. Read its label and all related instructions. BRECOflex CO., L.L.C. reserves the right to make changes in the technical and dimensional specifications of its products without prior notice. Responsibility for expenses incurred as a result of product changes or discontinuance or a product lies solely with the purchaser.

05/2026