

# MasterEmaco<sup>®</sup> P 5000AP

Single component, cement based, multi-use, bonding and active protective primer

## DESCRIPTION

**MasterEmaco P 5000AP** active primer, not only reinstates a high pH environment it also contains active corrosion inhibiting additives for the protection of reinforcement steel. It can also be used as an adhesive bonding slurry for subsequent repair mortars. When mixed with water, it forms a slurry that can be applied by brush to the clean exposed reinforcement, or directly on the dampened, prepared concrete substrate when used as a bonding coat.

## RECOMMENDED USES

**MasterEmaco P 5000AP** is used for the protection of reinforcement steel:

- When steel is visible and the available depth of cover is less than 10 mm.
- When concrete is contaminated with chlorides
- In critical environments when extra protection is specified.
- When the timing at the jobsite does not allow for the repair mortars to be applied immediately after cleaning the steel.

**MasterEmaco P 5000AP** can also be used to aid bond and application properties of hand applied repair mortars in extreme thicknesses and conditions.

## FEATURES AND BENEFITS

- **Meets all major international norms** - for steel priming in concrete repair systems.
- **Excellent rust inhibiting properties** - as it reinstates a high pH environment.
- **Contains active corrosion inhibitors** - to further protect the steel.
- **Polymer modified** - for additional adhesive bond to the steel.
- **Long life repairs** - does not reduce adhesion of repair mortars to steel
- **Wide compatibility** - with steel reinforcing bars and concrete or repair mortars.
- **Fast curing** - to save time and money.
- **Simply mixing** – just add water.
- **Multi-use** - can also be used as a bonding slurry to improve bond and application thicknesses of MasterEmaco repair mortars on prepared concrete surfaces.
- **Orange** - for easy site control of reinforcement coverage

- **Only use what is needed** - supplied in re-usable air-tight containers
- **Low hazard** - low chromate (Cr[VI] < 2 ppm )

## PROPERTIES

PROPERTY	VALUES
Appearance	Orange powder
Layer thickness	2mm in layers
Density	Approx. 1.8 g/cm <sup>3</sup>
Mixing water	Approx. 0.22 – 0.26 l/kg
Working time	Approx. 60 minutes
Temperature for application (support and material)	Between +5 and +35°C
Pull out strength of coated rebar	≥ 80% Comparison vs uncoated
ZTV-Sib90 compliance testing TL PE-PCC	
- total halogen content	≤ 0.05 Weight μA/cm <sup>2</sup>
- corrosion stimulation	≤ 10 μA/cm <sup>2</sup>
- corrosion resistance	≤ 1 mm (migration of rust underneath the coating starting from uncoated edge)
- accelerated weathering 10 cycles DIN 50017 10 cycles DIN 50018 120 hours DIN 50021	No corrosion / no delamination / max. crack width ≤ 0.1mm
VOC Content : 9g/L Test method: ASTM D3960	

## APPLICATION

### Surface preparation

All corrosion and its by-products must be removed from. The preparation should meet the requirements of ISO 8501-1 / ISO 12944-4 class SA 2 for the full 360° circumference of the steel reinforcement to be coated. When used as a bond coat on concrete, the surface must be completely clean and structurally sound. Remove deteriorated or contaminated concrete or mortar, e.g. by grit or high pressure water blasting. Saturate the concrete surface with water but remove excess before application. Surface profile as required by the repair mortar usually CSP 5 or greater.



We create chemistry

# MasterEmaco® P 5000AP

## Mixing

In a suitable container, mix **MasterEmaco P 5000AP** with a paddle mounted on a slow-speed drill, or by hand, until a smooth, thick consistency is achieved. Use only clean, uncontaminated water. Mixing water needed: 0.22 to 0.26 litres per kg of powder, depending upon consistency required. Leave to stand for approx. 5 minutes and re-mix briefly before use, adjusting the consistency when required, without exceeding the maximum water demand.

## Application of slurry

Substrate and ambient temperatures must be a minimum of +5°C and a maximum of +35°C. The minimum temperatures must be maintained during application and for at least 24 hours thereafter for optimum curing of the product.

As a reinforcement primer: Apply the mixed material in an even layer at least 1mm thick (approx 1.5kg/m<sup>2</sup>) to the full circumference of the prepared reinforcement using a soft paint brush. When the first coat has hardened sufficiently, (approx. 30-90minutes) apply a second coat also 1mm thick. It is important that this second layer has sufficiently hardened before the repair mortar is applied. When applying the repair mortar by hand this can be done after approximately 2 hours. However, when spraying a repair mortar the priming coat must be left to dry completely (min. 8 hours @ 20°C).

As a bonding slurry: Work the mixed material well into the prepared and pre-soaked, damp surface by using a suitable brush. Typical application rates are 2-3kg per m<sup>2</sup>. Apply the repair mortar wet in wet. Never allow the slurry bond coat to dry out.

## ESTIMATING DATA

Approx. 1.5 kg of dry powder per m<sup>2</sup> and mm layer thickness. This consumption is theoretical and depends on the roughness of the substrate. It should be verified on each particular job by means of "in situ" tests.

MasterEmaco P 5000AP				
L	Thickness in mm /m <sup>2</sup>	m <sup>3</sup>	pails /m <sup>3</sup>	m <sup>2</sup> /mm thickness
4	4mm	(0.004)	250	4 m <sup>2</sup>

## PACKAGING

**MasterEmaco P 5000AP** is available in 5kg plastic re-sealable pails.

## SHELF LIFE

**MasterEmaco P 5000AP** has a shelf life of 12 months. Store out of direct sunlight, clear of the ground on pallets protected from rainfall.

## PRECAUTIONS

For the full health and safety hazard information and how to safely handle and use this product, please make sure that you obtain a copy of the BASF Safety Data Sheet (SDS) from our office or our website.

MasterEmaco-P5000AP-ANZ V4-0417

## STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this BASF publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

## NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by BASF either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not BASF, are responsible for carrying out procedures appropriate to a specific application.

**BASF Australia Ltd**  
ABN 62008437867  
Level 12  
28 Freshwater Place  
Southbank VIC 3006  
**Freecall: 1300 227 300**  
www.master-builders-solutions.basf.com.au

**BASF New Zealand Ltd**  
Level 4, 4 Leonard Isitt Drive  
Auckland Airport 2022  
Auckland, New Zealand  
**Freecall: 0800 334 877**  
www.master-builders-solutions.basf.co.nz

**BASF Emergency Advice**  
1800 803 440 within Australia (24hr)  
0800 944 955 within New Zealand

Supplied by



*Making your job easier!*

09 42 68 101

sales@everitts.co.nz

www.everitts.co.nz