

Evaporation Retarder

ER-921

TECHNICAL DATA

1.0 DESCRIPTION

ER-921 is a surface-active agent used to reduce the water evaporation rate from the surface of newly laid concrete. It is designed to form a thin film to reduce rapid moisture loss from the concrete surface. ER-921 is spray applied in diluted form to fresh concrete flatwork to reduce the tendency for surface plastic cracking to occur. ER-921 aids and improves the workability and finishing characteristics of the concrete surface. ER-921 also helps extend the surface workability time for a given set of weather conditions.

2.0 PROPERTIES

2.1. Colour	Clear
2.2. S.G.	1
2.3. Viscosity	Low
2.4. Toxicity	Non toxic
2.5. Dilution Ratio	1 part ER-921 to 9 parts clean water. All references to & instructions for ER-921 are for diluted product.
2.6. Coverage	Up to 10m ² per litre (fully diluted).

3.0 USES

Use ER-921 as an evaporation retarder for concrete flatwork surfaces when the evaporation rate exceeds the bleeding rate. Recommended for use on all concrete surfaces except dry shake hardeners and toppings.

4.0 APPLICATION

- 4.1. Dilute ER-921 as supplied at the ratio of 1 part ER-921 with 9 parts water.
- 4.2. Apply ER-921 with a commercial sprayer. Use a Chapin 8005 spray tip (or equivalent) that produces a fine mist.
- 4.3. Apply a fine mist to completely cover the concrete surface. ER-921 is most effective the sooner it is applied, for example, immediately after screeding and or between finishing operations.
- 4.4. When working in hot, dry conditions, ER-921 should be reapplied after each operation (floating, trowelling, etc).
- 4.5. Do not allow ER-921 to puddle. If puddling occurs, wipe up immediately and rinse with water.
- 4.6. Clean all equipment immediately after use with clean water.
- 4.7. Cure concrete with FRACURE or FRACURE EMULSION after bleed water or excess surface water has dissipated. ER-921 is NOT a curing compound. The protective film usually lasts as long as the concrete is plastic. For proper curing, use a curing compound or water cure.



Fraser Brown & Stratmore Ltd

Address: 185 Rata Street, PO Box 35136 Naenae, Lower Hutt, New Zealand

Telephone: 04 567 8436 Freephone: 0800 835 699 Facsimile: 04 567 7232 Freefax: 0800 FIBRES (342 737)

Website: www.fbsltd.co.nz

Email: info@fbsltd.co.nz

The information contained in this data sheet, is to the best of our current knowledge, true and accurate, but any recommendations or suggestions which may be made are without liability on our part, since the conditions of use are beyond our control. Buyers and users are urged to make their own assessment of our products under their own conditions and for their own requirements. Fraser Brown & Stratmore Ltd reserves the right to alter formulations without notice. Properties as stated were determined under controlled laboratory conditions.



ER-921

TECHNICAL DATA Continued

5.0 PRECAUTIONS

- 5.1. DO NOT USE ER-921 as a finishing aid for cementitious materials such as dry shake hardeners or toppings.
- 5.2. ER-921 should not be worked into the concrete surface nor should it be used to re-temper concrete.
- 5.3. ER-921 is not suitable for application onto vertical surfaces or where excessive ER-921 runoff may occur.
- 5.4. Keep away from direct sunlight, frost and localised heat sources. Keep all containers tightly closed when not in use.
- 5.5. Fraser Brown & Stratmore Limited is not responsible for compatibility with other manufacturer's products.

6.0 PACKAGING

ER-921 is supplied as 1, 4 & 20-litre concentrates.



Fraser Brown & Stratmore Ltd

Address: 185 Rata Street, PO Box 35136 Naenae, Lower Hutt, New Zealand

Telephone: 04 567 8436 Freephone: 0800 835 699 Facsimile: 04 567 7232 Freefax: 0800 FIBRES (342 737)

Website: www.fbsltd.co.nz

Email: info@fbsltd.co.nz

The information contained in this data sheet, is to the best of our current knowledge, true and accurate, but any recommendations or suggestions which may be made are without liability on our part, since the conditions of use are beyond our control. Buyers and users are urged to make their own assessment of our products under their own conditions and for their own requirements. Fraser Brown & Stratmore Ltd reserves the right to alter formulations without notice. Properties as stated were determined under controlled laboratory conditions.

