

MasterFlow[®] 810 (formerly known as Masterflow 830)

Non-shrink, precision cementitious grout for use in general civil engineering works

DESCRIPTION

MasterFlow 810 is a ready to use, non-shrink, natural aggregate cementitious precision grout for use in general civil engineering works.

MasterFlow 810 provides extended working life and high early and ultimate strengths.

RECOMMENDED USES

All precision, non-shrink grouting applications with clearances of 10mm or more including:

- Critical equipment baseplates, soleplates and columns.
- Precast wall panels, beams, columns, structural building members and curtain walls.
- Patching poured in place concrete structures e.g. honeycombing, using preplaced aggregate techniques.
- Underpinning.
- Anchoring dowels, bolts and other fixings.
- Applications requiring high early compressive strengths and high ultimate compressive strengths.

FEATURES AND BENEFITS

- **High strength** – Provides good early and ultimate strengths which ensure quick return to service and long term durability
- **Non shrink** – Hardens free of bleeding, settlement and drying shrinkage when placed at flowable consistency
- **Flowable consistency** – Ensures complete filling of even intricate voids often without the need for pumping and strapping
- **Ample working time** – Remains placeable up to 1 hour, even at high ambient temperatures
- **Dense, impermeable grout** – Provides a good watertight seal
- **Economical** – Greater volumes of grout can be mixed and handled with less labour.
- **Easy to use** – Requires no special mixing equipment, it can be mixed in a standard concrete mixer or in a pail using a grout stirrer.
- **No added chloride** – Does not add to chloride load on structure
- **Strict quality control** – Ensures reliable and consistent product performance.
- **Provides complete non shrink performance** – when tested in accordance with simulated Bedplate Technique.
- **Compliance with codes** – Meets the non-shrink requirements of ASTM C1090 and CRD-C 621, Corps of Engineers Specification for

Non Shrink Grout; tested to the requirements of AS1478.2 "Methods of sampling and testing admixtures for concrete, mortar and grout".

PROPERTIES

	Flowable	
Compressive strength	1 day	25 N/mm ²
	3 days	42 N/mm ²
	7 days	55 N/mm ²
	28 days	65 N/mm ²
Estimate setting time	Initial	5:30 hours
	Final	6:30 hours

Note: Tested using cubes of size: 50mm x 50mm x 50mm, restrained for 24 hrs, cured by immersion in water.

Flow Retention

Flow retention when placed at 'flowable' consistency at 23°C.

Age at Test	Flow	Retention
Initial	47cm	100%
After 30 minutes	35cm	90%
After 1 hour	24cm	75%

Test Method: AS1478.2 Appendix D

Bleeding, Plastic Density and Setting Time

Plastic properties when placed at 'flowable' consistency at 23°C

Bleeding (AS1012.6)	none	
Plastic Density (AS 1012.5)	2145	
Setting times (AS 1012.18)	Initial	4.6 hours
	Final	6.0 hours

Volume Change

Volume change when placed at 'flowable' consistency at 23°C.

Age at Test	Volume Change
1 day	Positive
3 days	Positive
7 days	Positive
28 days	Positive

Test Method: ASTM C1090 (CRD-C621)

VOC content: 3g/L

Test method: SCAQMD 304-91



The Chemical Company

MasterFlow[®] 810 (formerly known as Masterflow 830)

NOTE: The data shown is based on controlled laboratory tests. Reasonable variations from the results shown can be expected. Field and laboratory tests should be conducted on the basis of the desired placing consistency rather than strictly on indicated water demand. If the project requires that strength tests be made on site do not use cylinder moulds. Compressive strength should be determined in 50mm cube moulds fitted with compression cover plates in accordance with AS 1478.2 Appendix A.

APPLICATION

For application directions on preparation, forming, mixing, placing and curing **Masterflow 810**, as well as the precautions to take in hot and cold weather, refer to "Application Guide for **Masterflow** Cementitious Precision Grouts" available from your local BASF Construction Chemicals representative. For situations requiring 'dry pack' (damp pack) application, refer to **Masterflow 700**.

MasterFlow 810 can be mixed to a flowable consistency. The quantity of water required for a 20 kg bag is approximately 3.6 litres.

Water addition may be affected by temperature conditions on site. Trials are recommended to determine the correct water requirement.

MasterFlow 810 should be used within 30 minutes of mixing.

CLEANING

Clean tools and equipment with water before **MasterFlow 810** has hardened, otherwise mechanical cleaning will be required.

ESTIMATING DATA

A 20 kg bag of **MasterFlow 810** when mixed to a flowable consistency will yield the following volume:

Flowable: 3.6 litres water Yield: 11 litres grout

PACKAGING

MasterFlow 810 is packaged in 20kg multi-ply paper sacks.

SHELF LIFE

MasterFlow 810 has a shelf life of approximately 12 months when stored in a cool dry place in unopened sacks.

PRECAUTIONS

For detailed Health, Safety and Environmental Recommendations, please consult and follow all instructions on the product Material Safety Data Sheet (MSDS) from our office or our website.

ID# MasterFlow 810 ANZ v1.1 0113

STATEMENT OF RESPONSIBILITY The technical information and application advice given in this BASF publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE Field service where provided does not constitute supervisory responsibility. Suggestions made by BASF either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not BASF, are responsible for carrying out procedures appropriate to a specific application.

BASF Australia Ltd
ABN 62008437867
Construction Chemicals Division
11 Stanton Road Seven Hills, NSW 2147

Sales Offices:
Sydney, Brisbane, Melbourne,
Adelaide, Perth
Freecall: 1300 227 300

BASF Emergency Advice:
1800 803 440 within Australia (24hr)
0800 944 955 within New Zealand

BASF New Zealand Ltd
BASF WEB SITES

45 William Pickering Drive, Albany, Auckland, Phone: 0800 334 877
www.basf-cc.com.au www.basf-cc.co.nz

Supplied by



RIGHT PRODUCT
RIGHT PRICE
RIGHT TO YOUR SITE



09 42 68 101 sales@everitts.co.nz www.everitts.co.nz