

# EPOXY PASTE EPAR 802

## TECHNICAL DATA

### 1.0 DESCRIPTION

EPAR 802 is a soft, smooth epoxy paste which is solventless and non shrink. EPAR 802 can be applied up to 5mm thick on vertical surfaces without slumping and can easily be feathered out or sanded.

EPAR 802 bonds strongly to concrete, timber, metals and stone.

Also available with a cold cure hardener for use from 0°C – 10° C.

### 2.0 PHYSICAL PROPERTIES:

2.1	Viscosity	Thixotropic paste.
2.2	Mix Ratio	1 : 1 by volume.
2.3	Pot Life	1 – 1.5 hours at 20°C. Std hardener.
2.4	Minimum Application Temp.	10°C. Std hardener.
2.5	Shelf Life	1 year in original unopened containers.
2.6	Cured Properties	(Standard hardener at 20°C)
2.6.1	Colour	Grey.
2.6.2	Specific Gravity	1.5
2.6.3	Compressive Strength	33 MPa 2 days, 50 MPa 7 days.
2.6.4	Compressive Modulus	3 GPa.
2.6.5	Tensile Strength	19 MPa.
2.6.6	Thermal Expansion	5x 10 <sup>-5</sup> mm/mm/°C.

### 3.0 USES

The excellent gap filling adhesive properties of EPAR 802 make it suitable for a wide variety of applications including the following:

- 3.1 Laminating and jointing of fibrous cement sheet.
- 3.2 General concrete repair and levelling.
- 3.3 Production of exposed aggregate finish by bonding pebbles to a variety of surfaces.
- 3.4 Tile adhesive.
- 3.5 Smoothing and patching timber, concrete or metal surfaces prior to painting. Can be trowelled to a smooth finish.
- 3.6 Filling & smoothing screw holes in fibre cement sheets.

### 4.0 APPLICATION INSTRUCTIONS

- 4.1 SURFACE PREPARATION. Thoroughly clean the jointing surfaces of all extraneous matter, especially oil and grease. Laitance should be removed from concrete surfaces mechanically or by acid etching. For best results steel surfaces should be prepared by sand blasting or grinding.



## Fraser Brown & Stratmore Ltd

Address: 185 Rata Street, PO Box 35136 Naenae, Lower Hutt, New Zealand

Telephone: 04 567 8436 Freephone: 0800 835 699 Facsimile: 04 567 7232 Freefax: 0800 FIBRES (342 737)

Website: [www.fbsltd.co.nz](http://www.fbsltd.co.nz)

Email: [info@fbsltd.co.nz](mailto:info@fbsltd.co.nz)

The information contained in this data sheet, is to the best of our current knowledge, true and accurate, but any recommendations or suggestions which may be made are without liability on our part, since the conditions of use are beyond our control. Buyers and users are urged to make their own assessment of our products under their own conditions and for their own requirements. Fraser Brown & Stratmore Ltd reserves the right to alter formulations without notice. Properties as stated were determined under controlled laboratory conditions.



# EPAR 802

---

## TECHNICAL DATA Continued

---

- 4.2 **MIXING.** Accurately proportion required volume of resin and hardener ensuring this amount can be used within its pot life. Mix the two parts thoroughly by using a spatula or preferably a mixing paddle on a low speed electric drill. Mix until a uniform grey colour is obtained.
- 4.3 **APPLICATION.** When being used as an adhesive apply an even layer of EPAR 802 to jointing surfaces preferably by notched trowel. Do not disturb joint for 8 hours or until EPAR 802 has hardened sufficiently to withstand use.
- 4.4 **CLEAN UP.** Hands and equipment should be washed in soap and water before curing is advanced.

## 5.0 PACKAGING

- 2lt pack (1 litre resin, 1 litre hardener)
- 4lt pack (2 litres resin, 2 litres hardener)
- 8lt pack (4 litres resin, 4 litres hardener)



## Fraser Brown & Stratmore Ltd

Address: 185 Rata Street, PO Box 35136 Naenae, Lower Hutt, New Zealand

Telephone: 04 567 8436 Freephone: 0800 835 699 Facsimile: 04 567 7232 Freefax: 0800 FIBRES (342 737)

Website: [www.fbsltd.co.nz](http://www.fbsltd.co.nz)

Email: [info@fbsltd.co.nz](mailto:info@fbsltd.co.nz)

The information contained in this data sheet, is to the best of our current knowledge, true and accurate, but any recommendations or suggestions which may be made are without liability on our part, since the conditions of use are beyond our control. Buyers and users are urged to make their own assessment of our products under their own conditions and for their own requirements. Fraser Brown & Stratmore Ltd reserves the right to alter formulations without notice. Properties as stated were determined under controlled laboratory conditions.

