

**ARMORLON®****TRANSGUARD® 2000**

Supplied by

**TECHNICAL DATA SHEET****DESCRIPTION**

Transguard® 2000 consists of a natural colored polypropylene nonwoven fabric with a white polyethylene coating applied to one side. The non perforated coating contains ultraviolet light stabilizers providing protection against UV degradation.

**PHYSICAL PROPERTIES AND TYPICAL VALUES**

PROPERTY	ASTM TEST METHOD	U.S. VALUE	METRIC VALUE
Weight	D-2103	34 Lbs/1000 FT <sup>2</sup>	16.6 KG/100 M <sup>2</sup>
Thickness	D-5199	22 MIL	0.56 mm
Grab Tensile	D-4632	64 Lbf	284.7 N
Grab Elongation	D-4632	65 %	65 %
Trapezoidal Tear	D-4533	28 Lbf	124.5 N
Hydraulic Burst	D-3786	130 PSI	0.9 Mpa
Water Loss (per 24 hrs.)	C-156	0.0062 Lbs/Ft <sup>2</sup>	0.0600 gm/m <sup>2</sup>
Reflectance	E-1347	79 %	79 %

**FEATURES AND BENEFITS**

Transguard® 2000 Single Use Wet Cure Covers meet or exceed ASTM C-171, "Standard Specification for Sheet Materials for Curing Concrete" for moisture retention and reflection.

Roll Size: 2.4m x 60m (144m<sup>2</sup>)

Roll Weight: 25kg

The information provided herein is based upon data believed to be reliable. All testing is performed in accordance with ASTM standards and procedures. All values are typical and nominal and do not represent either minimum or maximum performance of the product. Although the information is accurate to the best of our knowledge and belief, no representation of warranty or guarantee is made as to the suitability or completeness of such information. Likewise, no representation of warranty or guarantee, expressed or implied, or merchantability, fitness or otherwise, is made as to product application for a particular use.

Supplied by

*Making your job easier!***09 42 68 101**[sales@everitts.co.nz](mailto:sales@everitts.co.nz)[www.everitts.co.nz](http://www.everitts.co.nz)