



CONTINUUM™ DGDA-2420 NT

Bimodal Polyethylene Resin

Overview

CONTINUUM™ DGDA-2420 NT Bimodal Polyethylene Resin is produced using UNIPOL™ II process technology. This product is formulated with a UV stabilizer for outdoor storage. This product may be utilized for pipe applications where long-term hydrostatic strength combined with outstanding resistance to slow crack growth and rapid crack propagation is desired. Suitable applications include natural gas distribution pipes, irrigation and drip tube.

Industrial Standards Compliance:

- ASTM D 3350: cell classification PE277370D
- ISO PE 80 pipe grade
- ASTM PE 2708 pipe grade - 1250 psi HDB @ 73F, 800 psi HDS at 73F, and 1000 psi HDB at 140F

Consult the regulations for complete details.

Additive

- Antiblock: No
- Slip: No
- Processing Aid: Yes

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density (Natural Compound)	0.941 g/cm ³	0.941 g/cm ³	ASTM D792
Base Density ¹	0.940 g/cm ³	0.940 g/cm ³	Dow Method
Melt Index			ASTM D1238
190°C/2.16 kg ²	0.16 g/10 min	0.16 g/10 min	
190°C/21.6 kg ³	9.5 g/10 min	9.5 g/10 min	
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength ⁴ (Yield)	> 2600 psi	> 17.9 MPa	ASTM D638
Tensile Elongation ⁴ (Break)	> 600 %	> 600 %	ASTM D638
Flexural Modulus - 2% Secant ^{5, 4}	> 90000 psi	> 621 MPa	ASTM D790B
Resistance to Rapid Crack Propagation, P _c			
Full Scale : 32°F (0°C) ⁶	> 560 psi	> 38.6 bar	ISO 13478
S-4 : 32°F (0°C) ⁷	> 145 psi	> 10.0 bar	ISO 13477
Resistance to Rapid Crack Propagation, T _c - S-4 @ 5 bar ⁷	< 28 °F	< -2 °C	ISO 13477
Slow Crack Growth Resistance ⁴			
Notched Pipe Test	> 3000 hr	> 3000 hr	ISO 13479
PENT	15000 hr	15000 hr	ASTM F1473
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Brittleness Temperature ⁴	< -103 °F	< -75.0 °C	ASTM D746A
Thermal Stability	> 428 °F	> 220 °C	ASTM D3350

Notes

These are typical properties only and are not to be construed as specifications. Users should confirm results by their own tests.

¹ Base density is estimated using the assumption that every 1000 ppm of antiblock in the finished product raises the density of the polymer by 0.0006 g/cm³. Base density is the estimated density of the polymer if it did not contain any antiblock.

² Melt Index

³ Flow Index

⁴ Compression molded parts prepared according to ASTM D 4703 Procedure C unless otherwise noted in the test method. Properties will vary with changes in molding conditions and aging time.

⁵ Method I (3 point load)

⁶ Calculated value, determined by the equation in ISO 4437 based on S-4 test data. Pipe diameter of 12 inch IPS (30.5 cm) and Standard Dimension Ratio (SDR) 11.5.

Pipe diameter of 12 inch IPS (30.5 cm) and Standard Dimension Ratio (SDR) 11.5.

⁷ Pipe diameter of 12 inch IPS (30.5 cm) and Standard Dimension Ratio (SDR) 11.5.

Product Stewardship

Dow has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis for our product stewardship philosophy by which we assess the safety, health, and environmental information on our products and then take appropriate steps to protect employee and public health and our environment. The success of our product stewardship program rests with each and every individual involved with Dow products - from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

Customer Notice

Dow strongly encourages its customers to review both their manufacturing processes and their applications of Dow products from the standpoint of human health and environmental quality to ensure that Dow products are not used in ways for which they are not intended or tested. Dow personnel are available to answer your questions and to provide reasonable technical support. Dow product literature, including safety data sheets, should be consulted prior to use of Dow products. Current safety data sheets are available from Dow.

Medical Applications Policy

Any and all medical application use of Dow materials, whether a device, a component, or any type of primary or secondary packaging of a medically related object or substance, needs to be reviewed and approved by Dow before any Dow material can be tested in such application.

Dow requests that customers considering use of Dow products in medical applications notify Dow so that appropriate assessments may be conducted. Dow does not endorse or claim suitability of its products for specific medical applications. It is the responsibility of the medical device or pharmaceutical manufacturer to determine that the Dow product is safe, lawful, and technically suitable for the intended use. **DOW MAKES NO WARRANTIES, EXPRESS OR IMPLIED, CONCERNING THE SUITABILITY OF ANY DOW PRODUCT FOR USE IN MEDICAL APPLICATIONS.**

For further information contact your Dow sales or technical representative to request a Medical Application Review Request Form.

Additional details of Dow's Medical Applications Policy are available at: <https://www.dow.com/en-us/support/product-safety.html>

Tobacco and Marijuana Policy

Dow does not support or intend for its products to be used, directly or indirectly, in the production of tobacco, the manufacture of tobacco products, the manufacture and use of electronic cigarettes (including vaping devices), the production of marijuana, or the manufacture of marijuana products intended for human consumption, where the Dow product (or its residues) may be present in the finished product or be alleged to facilitate the delivery of nicotine, other tobacco components, marijuana, or marijuana components.

Harmful Applications Policy

Dow does not intend for its products to be used in applications specifically intended to harm humans.

Disclaimer

NOTICE: No freedom from infringement of any patent owned by Dow or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, the Customer is responsible for determining whether products and the information in this document are appropriate for the Customer's use and for ensuring that the Customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. Dow assumes no obligation or liability for the information in this document. **NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.**

NOTICE: If products are described as "experimental" or "developmental": (1) product specifications may not be fully determined; (2) analysis of hazards and caution in handling and use are required; (3) there is greater potential for Dow to change specifications and/or discontinue production; and (4) although Dow may from time to time provide samples of such products, Dow is not obligated to supply or otherwise commercialize such products for any use or application whatsoever.

NOTICE: This data is based on information Dow believes to be reliable, as demonstrated in controlled laboratory testing. They are offered in good faith, but without guarantee, as conditions and method of use of Dow products are beyond Dow's control. Dow recommends that the prospective user determine the suitability of these materials and suggestions before adopting them on a commercial scale.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication, however we do not assume any liability for the accuracy and completeness of such information.

For additional information, not covered by the content of this document, contact us via our web site http://www.dow.com/products_services/.

Additional Information

North America	Europe/Middle East	+800-3694-6367
U.S. & Canada:	1-800-441-4369	+31-11567-2626
	1-989-832-1426	+800-783-825
Mexico:	+1-800-441-4369	
Latin America	South Africa	+800-99-5078
Argentina:	+54-11-4319-0100	
Brazil:	+55-11-5188-9000	
Colombia:	+57-1-219-6000	Asia Pacific
Mexico:	+52-55-5201-4700	+800-7776-7776
		+603-7965-5392

www.dow.com

This document is intended for use within Asia Pacific, Latin America, North America

Published: 2006-04-25

© 2023 The Dow Chemical Company

