

GlasSil™

One Part Neutral Cure Silicone Sealant

Product Description

GlasSil is a one component silicone sealant which cures to a high modulus silicone rubber on exposure to atmospheric moisture at room temperature. This product is a ketoxime cure sealant which does not emit the odors associated with acetoxy cure sealant, and is virtually non-corrosive to metal. In addition to the unique features of silicone rubber such as superior high and low temperature resistance, water resistance, and outstanding weatherability, GlasSil also provides excellent adhesion to glass, metal, concrete and numerous construction materials.

Key Features and Typical Benefits

- One component, ready-to-use sealant
- Room temperature cure
- Neutral cure (ketoxime cure)
- No acetoxy odor during cure
- Easy gunnability over a wide temperature range
- Maintains good flexibility
- Excellent adhesion to many materials

Potential Applications

- Sealant for glass-to-glass and glass-to-metal sashing.
- Sealant for pre-fabricated housing, freight containers, cold storage rooms interior sealing in building and housing.

Packaging

- 300g cartridge (available in cases of 14 cartridges)

Colors

Available in 5 colors:

- Clear
- White
- Black
- Dark Brown
- Aluminum Gray

Typical Physical Properties

Typical property values of GlasSil sealant as supplied and cured are set forth in the tables below.

Typical Properties - Supplied

Property	Value ⁽¹⁾	Test Method
Consistency	Paste	JIS A 1439
Specific Gravity (23°C)	1.02	JIS A 1439
Extrudability (5°C)	5 seconds	JIS A 1439
Tack Free Time (23°C)	10 minutes	JIS A 1439
Sag/Slump	0 mm	JIS A 1439

Typical Properties - Cured

Property	Value ⁽¹⁾	Test Method
50% Modulus	0.46 Mpa (4.7 kgfcm ²)	JIS A 1439
Ultimate Tensile Strength	0.83 MPA (8.5 kgfcm ²)	JIS A 1439
Ultimate Elongation	170%	JIS A 1439

TEST CONDITIONS

- Substrate : H-shaped, anodized aluminum
 Primer : TOSPRIME D
 Cure time : 14 days at 23°C/50% relative humidity
 : 14 days at 30°C/50% relative humidity

Application Instructions

Surface Preparation

- Substrate surface should be thoroughly cleaned with a suitable solvent such as alcohol, xylene, or methyl ethyl ketone (MEK). Do not use soap, detergent or water. Wipe the surface dry. Sealant will not properly adhere to a wet substrate.

Masking

- To obtain a neat sealant line, use masking tape to cover areas adjacent to any joints before priming.

Primer

- A preliminary adhesion test of sealant on the substrate is recommended to ascertain proper adhesion. For difficult-to-bond substrates, use of a primer (TOSPRIME C, D or E) is suggested. Please refer to the chart on page 3 for proper primer selection. Allow primer to dry thoroughly before proceeding.

Back-Up Material

- Do not apply sealant in direct contact with organic rubber such as chloroprene or EPT etc. Rubber closed to back-up materials may stain the silicone sealant.

Applying and Tooling Sealant

- Cut nozzle to desired bead size, break the membrane film completely and extrude sealant in the joint. Tool immediately, within 5 minutes of application, with a spatula to spread the sealant against the back-up material and joint surfaces. Remove masking tape immediately after tooling. Sealant will begin to skin on the exposed surface in about 10 minutes and cure will progress inward.

Handling and Safety

- Wear eye protection when handling uncured sealant as it can irritate eyes. In case of eye contact, immediately flush eyes well with water and contact a physician.
- This product releases methyl ethyl ketoxime vapors as a by-product of cure. Maintain adequate ventilation in the work place at all times.
- Extended contact with the skin may cause irritation and should be avoided.
- Not for food contact use.

Storage

- Store in a cool, dry, dark place.
- Keep out of reach of children.

Primer Selection

TOSSEAL primers; TOSPRIME C, D and E have been specially prepared to ensure the durability and bonding strength of GlasSil to various substrates. The chart below shows which primer is most compatible with the substrate.

Primer	Substrate
TOSPRIME C	Mortar, Masonry
TOSPRIME D	Glass, Metal, Ceramic
TOSPRIME E	Painted metal, Painted surfaces

CAUTION: Primers contain solvents which are highly flammable and toxic. Observe all cautions. Storage, mixing and use must be done in a well ventilated area away from any source of ignition such as heat, sparks, and flame.

Do not use on marble without primer because of migration. TOSPRIME C is recommended.

Limitations

Customers must evaluate MPM products and make their own determination as to fitness of use in their particular applications.

Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

For Industrial Use Only

It is the responsibility of the user to determine the suitability of any Momentive Performance Materials Japan product for any intended application. NEVER USE ANY MOMENTIVE PERFORMANCE MATERIALS JAPAN PRODUCT FOR IMPLANTATION OR INJECTION INTO THE HUMAN BODY. Specifications are available by contacting Momentive Performance Materials Japan. Typical property data values should not be used as specifications. In as much as Momentive Performance Materials Japan LLC has no control over the use to which others may put the material, it does not guarantee that the same results as those described herein will be obtained. Each user of the material should make his own tests to determine the suitability of the material for his own particular use. Statements concerning possible or suggested uses of the materials described herein are not to be construed as constituting a license under any Momentive Performance Materials Japan patent covering use or as recommendations for use of such materials in the infringement of any patent. Material Safety Data Sheets are available upon request from Momentive Performance Materials Japan. The contents of this catalog are subject to change without notice. No part of this data may be reproduced without the prior approval of Momentive Performance Materials Japan.

Customer Service Centers

Americas	+1 800 295 2392 Toll free Email: commercial.services@momentive.com
Latin Americas	Brazil +55 11 4534 9650 Direct Number Email: contato@momentive.com Mexico +52 55 2169 7670 Direct Number Email: commercial.services@momentive.com
EMEIA - Europe, Middle East, Africa, and India	Europe +39 05 1092 4300 Direct Number Middle East, Africa and India + 91 44 7121 2207 Direct Number* *All Middle Eastern countries, Africa, India, Pakistan, Bangladesh, Sri Lanka Email: 4information.eu@momentive.com
APAC - Asia Pacific	China 800 820 0202 Toll free +86 21 3860 4892 Direct Number Japan Sales: JP.Silicones@momentive.com Korea +82 2 6201 4600 Direct Number South East Asia, Australia & New Zealand +60 3 9206 1543 Direct Number* *South East Asia countries (Malaysia, Singapore, Thailand, Indonesia, Vietnam, Philippines, Cambodia, Myanmar / other countries located in Pacific region).
MyMomentive™ Order Management Site	shop.mymomentive.com

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY "SUPPLIER"), ARE SOLD SUBJECT TO SUPPLIER'S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER'S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBE HEREIN. Each user bears full responsibility for making its own determination as to the suitability of Supplier's materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier's products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

Before purchasing or using any Momentive products, please visit www.siliconeforbuilding.com/legaldisclaimer to view our full product and sales disclaimer.

The use of the "TM" symbol designates registered or unregistered trademarks of Momentive Performance Materials Inc., or its affiliated companies.

Copyright 2026 Momentive Performance Materials Inc. All rights reserved.



Licensed Partner

siliconesforbuilding.com