

Veridian R (Specification Data)

FLOORING PROPERTIES & PACKAGING

Construction Extruded Core with Pre-Attached Underlayment:	Rigid Core 4.5mm Thick + 1mm IXPE Pad
Collection:	Veridian R
Use:	Commercial & Residential
Size:	9.13" Width X 60" Length (232mm X 1524mm)
Installation Method:	i4F Drop & Lock
Certification:	FloorScore certified by SCS Global Services
Wear Layer:	20mil (0.5mm)
Edge Detail:	Painted Micro-Bevel
Emboss:	Natural Wood Texture
Gauge:	4.5mm Rigid Core + 1mm IXPE Attached Pad = 5.5mm Total Thickness
Planks/Case:	8
Coverage/Each Plank:	3.81 Sq. Ft. (0.354 Sq. Meters)
Coverage/Case:	30.45 Sq. Ft. (2.8289 Sq. Meters)
Coverage/Pallet:	48 Cases/Pallet (1461.6 Sq. Ft. / 135.79 Sq. Meters)
Limited Warranty:	Limited Lifetime Residential / 20-Year Limited Commercial

STANDARDS – SAFETY & PERFORMANCE

Standard	Description	Requirements	Results
ASTM E648	Critical Radiant Flux (Radiant Panel)	Class I: ≥ 0.45 W/cm ²	Surpasses Requirements ¹
ASTM E662	Smoke Density	Flaming & Non-Flaming ≤ 450	Surpasses Requirements ²

CDPH/EHLB, Standard Method v1.2	VOCs/TVOCs, Formaldehyde	Refer to Standard	Surpasses Requirements
ASTM F963	Heavy Metals	Refer to Standard	Surpasses
ASTM D7823 / CPSC-CH-C1001-09.3	Phthalates	Refer to CPSIA3	Requirements
ASTM D2047	Coefficient of Friction / Slip Resistance	N/A (No Official Requirements)	Surpasses ≥0.6 (Dry) Requirements

STANDARDS – SOUND

Standard	Description	Requirements		Results
ASTM E90 & ASTM E413	Airborne Sound Transmission Loss of Building Partitions and Elements (STC / Sound Transmission Class)	6" Concrete Slab	STC ≥ 50	STC 56 (Surpasses Requirements)
		6" Concrete Slab + Drop-Ceiling	STC ≥ 50	STC 59 (Surpasses Requirements)
ASTM E492 & ASTM E989	Impact Sound Transmission Through Floor-Ceiling Assemblies (IIC / Impact Insulation Class)	6" Concrete Slab	IIC ≥ 50	IIC 57 (Surpasses Requirements)

STANDARDS – MANUFACTURING & USAGE (ASTM F3261)


Standard	Description	Requirements	Results
ISO 24337	Size	Tolerance - Width of 9.13" (232mm) ±0.008" (±0.20mm) Tolerance - Length of 60" (1524mm) ±0.020" (±0.5mm) ≤0.010" (0.25mm)	Surpasses Requirements
ASTM F2421	Squareness		Surpasses
ASTM F387	Thickness	With Foam Back Layer Tolerance: ±0.008" (0.2mm) vs. Specified Minimum: 0.080" (2.0mm)	Requirements Surpasses
ISO 24337	Flatness	Max. Values - Width of 9.13" (180mm) Fw ±0.008" (0.2mm) Fl concave ≤ 0.15%; Fl convex ≤ 0.20%	Requirements Surpasses Requirements

ISO 24337	Openings	Average (OAvg) $\leq 0.004"$ (0.1mm) Maximum (OM) $\leq 0.008"$ (0.2mm)	Surpasses Requirements
ISO 24337	Ledging	Average (HAvg) $\leq 0.004"$ (0.1mm) Maximum (HM) $\leq 0.006"$ (0.15mm) Average: $\leq 0.007"$ (0.18mm)	Surpasses Requirements
ASTM F1914	Residual Indentation		Surpasses Requirements
ASTM F1914	Surface Integrity	No puncture through wear layer / décor into rigid core	Surpasses Requirements
ISO 23999	Dimensional Stability	$\leq 0.25\%$ / lineal ft. (305 mm)	Surpasses Requirements
ISO 23999	Curling	$\leq 0.080"$ (2.0mm)	Surpasses
ASTM F925	Chemical Resistance	No more than "Slight Change"	Requirements Surpasses
ASTM F1514	Resistance to Heat	Average $\Delta E < 8.0$	Surpasses Requirements Requirements
ASTM F1515	Resistance to Light Static Load	Average $\Delta E < 8.0$	Surpasses Requirements
ASTM F970		No Official Requirements (Wear Layer $< 20\text{mil}$)	$\leq 0.005"$ (0.13mm), 250psi


Footnotes

- ASTM E648 - Critical Radiant Flux (Radiant Panel): Passes Requirements for Class I per International Building Code (IBC) 2018 & NFPA 101 Life Safety Code.
- ASTM E662 - Smoke Density: 450 is the limit established by many state, county, and/or local building and/or fire codes, but is not set as a limit for (resilient) flooring products nationwide. Thus, Smoke Density requirements for flooring products may vary from jurisdiction to jurisdiction. Consult your building inspector / fire marshal to learn more.
- CPSIA = Consumer Product Safety Improvement Act.

Recommend Installation Options:



Ashlar



Stagger