


BOULEVARD

TECHNICAL DATA

<i>Format:</i>	All formats available	<i>Type:</i>	Glazed Porcelain	
<i>Color:</i>	All colors available	<i>Thickness:</i>	8.5 mm	
<i>Graphic:</i>	12	<i>Recycled Content:</i>	28% *Pre-Consumer	
	ASTM Test	ISO Test	Value Required ANSI	Declared ASTM
WATER ABSORPTION	<i>C373</i>	<i>ISO.10545/3</i>	<i>≤0.5%</i>	<i>≤0.5%</i>
BREAKING STRENGHT	<i>C648</i>	<i>ISO.10545/4</i>	<i>≥ 350</i>	<i>≥350</i>
SCRATCH HARDNESS	<i>MOH’s Scale</i>	<i>EN-101</i>	<i>-</i>	<i>5</i>
CHEMICAL RESISTANCE	<i>C650</i>	<i>ISO-10545/13</i>	<i>Unaffected</i>	<i>Unaffected</i>
FROST RESISTANCE	<i>C1026</i>	<i>ISO-10545/12</i>	<i>Resistant</i>	<i>Resistant</i>
GROUP	<i>SEE FAQs</i>	<i>SEE FAQs</i>	<i>-</i>	<i>4</i>
PEI - GLAZED TILES	<i>C1027</i>	<i>ISO-10545/7</i>	<i>-</i>	<i>IV</i>
MINIMUM BOND STRENGHT (PSI)	<i>C482</i>	<i>-</i>	<i>≥ 50 psi</i>	<i>165</i>
DYNAMIC COEFFICIENT OF FRICTION (DCOF)	<i>A137.1</i>	<i>-</i>	<i>≥0.42</i>	<i>≥0.42</i>
SHADE AND TEXTURE RATING	<i>CTDA “V”</i>	<i>-</i>	<i>-</i>	<i>V3</i>
FACIAL DIMENSIONS	<i>C499</i>	<i>ISO-10545/2</i>	<i>1.5% Max</i>	<i>Pass</i>
RANGE OF THICKNESS	<i>C499</i>	<i>ISO-10545/2</i>	<i>0.040 Max</i>	<i>Pass</i>
WARPAGE	<i>C485</i>	<i>ISO-10545/2</i>	<i>0.75%</i>	<i>Pass</i>
WEDGING	<i>C502</i>	<i>ISO-10545/2</i>	<i>1.0% Max</i>	<i>Pass</i>

*Contains a percentage of pre-consumer recycled content superior to 25% which has been certified by Bureau Veritas.



MODERN
SURFACES