

Model/ Series:

Size:

Colors:

Type:

Thickness:

Recycled Content:

SHORES

4"X24" & 5"X6" Hexagon

All Colors Available

GLAZED PORCELAIN

9.5 mm

	25%	Pre-Consumer		
Technical Data	ASTM Test	ISO Test	Value Required ANSI	Declared ASTM
Water Absorption	C373	ISO-10545/3	<=0.5%	<=0.5%
Break Strength	C648	ISO-10545/4	>= 250	Min. 290
Scratch Hardness	MOH's Scale	EN-101	-	5
Chemical Resistance	C650	ISO-10545/13	Unaffected	Unaffected
Frost Resistance	C1026	ISO-10545/12	Resistant	Resistant
Group	SEE FAQS	SEE FAQS	-	3
Deep Abrasion - Unglazed Tiles	C1243	ISO-10545/6	<175 mm3	-
PEI - Glazed Tiles***	C1027	ISO-10545/7	-	1-5*
Minimum Bond Strength (PSI)	C482		>=50 psi	165
Dynamic Coefficient of Friction (DCOF)	A137.1	-	>=0.42	>=0.42
Shade and Texture Rating	CTDA "V"	-	-	V1
Facial Dimensions	C499	ISO-10545/2	1.5% Max	Pass
Range of Thickness	C499	ISO-10545/2	0.040 Max	Pass
Warpage	C485	ISO-10545/2	0.75%	Pass
Wedging	C502	ISO-10545/2	1.0% Max	Pass

*PEI is 1 for Azul, Verde and Negro, 3 for Acero, 4 for Gris and 5 for Blanco

Model/ Series:

Size:

Colors:

Type:

Thickness:

Recycled Content:

SHORES

2"X10"

All Colors Available

Ceramic Wall Tile

8.7 mm

- Pre-Consumer

Technical Data	ASTM Test	ISO Test	Value Required ANSI	Declared ASTM
Water Absorption	C373	ISO-10545/3	7.0% < wa <=20%	>10%
Break Strength	C648	ISO-10545/4	>= 250	Meets or Exceeds
Scratch Hardness	MOH's Scale	EN-101	-	-
Chemical Resistance	C650	ISO-10545/13	Unaffected	Unaffected
Shade and Texture Rating	CTDA "V"	-	-	V1
Warpage	C485	ISO-10545/2	0.0075	Pass
Wedging	C502	ISO-10545/2	1.0% Max	Pass