NitriDerm[®] Ultra Black

Nitrile Exam Gloves Series 187

This popular black color masks a variety of stains and is a true medical grade exam glove. Engineered with a medium modulus and high tensile strength, this glove is first choice for a wide range of end users including law enforcement and corrections. Textured for excellent grip. Tested to provide maximum protection from fentanyl exposure.

Characteristics: Non-Sterile, Powder-Free, Black Color

SIZE	ITEM NO.
XS	187050
S	187100
M	187200
L	187300
XL	187350
XXL	187400



XS-XL: 100 Gloves/Box, 10 Boxes/Case XXL: 90 Gloves/Box, 10 Boxes/Case



Tested for use with Chemotherapy Drugs, Fentanyl Citrate & Xylazine HCI

Features:

- Non-Latex = No Risk of Latex Allergens
- Textured Finish = Improved Wet/Dry Grip
- Low Modulus = a Softer, More Comfortable Fit

Manufactured in compliance with multiple international standards, including ASTM D6319, ASTM D5151, ASTM F1671, and ASTM D6978

	of Medica	erapy Drugs as per ASTM D6978 I Gloves to Permeation by Chemotherapy Drugs	
Carmustine (3.3 mg/ml)	14.4	Methotrexate (25.0 mg/ml) >	>240
Cisplatin (1.0 mg/ml)	>240	Mitomycin C (0.5 mg/ml)	>240
Cyclophosphamide (20.0 mg/ml)	>240	Mitoxantrone (2.0 mg/ml) >	>240
Cytarabine (100.0 mg/ml)	>240	Paclitaxel (6.0 mg/ml)	>240
Dacarbazine (10.0 mg/ml)	>240	Thiotepa (10.0 mg/ml)	29.2
Doxorubicin Hydrochloride (2.0 mg/ml)	>240	Vincristine Sulfate (1.0 mg/ml) >	>240
Etoposide (20.0 mg/ml)	>240	Also Tested: Fentanyl Citrate (100 mcg/2ml)	>240
Fluorouracil (50.0 mg/ml)	>240	Xylazine HCI (100 mg/ml)	>240
Ifosfamide (50.0 mg/ml)	>240	Simulated Gastric Acid	>240

Please note that Carmustine and Thiotepa have low permeation times. WARNING: Do not use with Carmustine and Thiotepa. Caution: In compliance with ASTM D6978, the testing conditions used are intended to approximate the worst-case conditions for clinical use. Testing was conducted on single layer glove material. It is the users' responsibility to determine the applicability of these gloves for their intended use with chemotherapy drugs.

Tensile Strength & Elongation	Before Aging	After Accelerated Aging
Tensile Strength (Mpa)	33	31
ASTM Requirement Min. (Mpa)	14	14
Elongation (%)	560	520
ASTM Requirement Min. (%)	500	400

Average Length	9.5 in ◆ 240 mm
Average Palm Thickness	4.0 mil ◆ 0.10 mm
Average Finger Thickness	5.0 mil ◆ 0.12 mm





View this product on our website:

