



Characteristics

Made from non-latex, polychloroprene synthetic polymer, these new Blackwork® Chloroprene exam gloves offer all of the benefits of natural rubber latex, with none of the allergen problems associated with latex. These exam gloves are the most comfortable gloves you'll ever wear! They're incredibly soft, unbelievably elastic, and yet they're still amazingly strong. Textured finish provides excellent wet or dry gripping ability. Black color.



***Blackwork*®
Chloroprene
Black Gloves**

**Exam Glove
Non-Sterile**



PRODUCT DETAILS

SIZE	ITEM NO.	PACKAGING	DESCRIPTION
XS	1010	100 Gloves/box, 10 boxes/case	Gloves, Exam, Chloroprene, Non-Sterile, Powder-Free, Textured, Black
S	1020	100 Gloves/box, 10 boxes/case	
M	1030	100 Gloves/box, 10 boxes/case	
L	1040	100 Gloves/box, 10 boxes/case	
XL	1050	100 Gloves/box, 10 boxes/case	

Product Attributes

- Low Modulus
- Non-Latex
- Textured Finish

Benefits

- Softer, More Comfortable Fit
- No Risk of Latex Allergens
- Improved Wet/Dry Grip

Product Solutions You Trust

Specification Sheet

BLACKWORK



NON-LATEX POWDER-FREE
NON-LATEX POWDER-FREE
NON-LATEX POWDER-FREE
NON-LATEX POWDER-FREE
NON-LATEX POWDER-FREE
NON-LATEX POWDER-FREE
NON-LATEX POWDER-FREE
NON-LATEX POWDER-FREE
NON-LATEX POWDER-FREE
NON-LATEX POWDER-FREE
NON-LATEX POWDER-FREE
NON-LATEX POWDER-FREE
NON-LATEX POWDER-FREE
NON-LATEX POWDER-FREE
NON-LATEX POWDER-FREE

Blackwork Chloroprene is manufactured in compliance with multiple international standards, including the following:

Designation	Standard
ASTM D6977	Standard Specification for Polychloroprene Examination Gloves for Medical Application
ASTM D5151	Standard Test Method for Detection of Holes in Medical Gloves
ASTM F1671	Standard Test Method for Resistance of Materials Used in Protective Clothing to Penetration by Blood-Borne Pathogens

Average Length	Average Palm Thickness	Average Finger Thickness
9.5 in ♦ 240 mm	2.8 mil ♦ 0.07 mm	3.5 mil ♦ 0.09 mm

Tensile Strength & Elongation	Before Aging	After Accelerated Aging
Tensile Strength (Mpa)	15.9	20.9
ASTM Requirement Min. (Mpa)	14	14
Elongation (%)	817	732
ASTM Requirement Min. (%)	500	400



intertek

Innovative Healthcare Corporation is certified to ISO 13485:2003 QMS for medical devices.