

Pulse® PURE™

Nitrile Exam Gloves Series 178

Made without the use of sulfur based chemical accelerators, our new Pulse® PURE™ eliminates the risk of both Type I (latex) and Type IV (chemical) allergic reactions. And unlike typical accelerator free nitrile gloves, new Pulse® PURE™ is as soft and comfortable as our regular Pulse® nitrile. So, while it's the obvious choice for those with skin sensitivities, it's also a great choice for all glove wearers.

Characteristics: Powder-Free, Non-Sterile, Blue color



SIZE	ITEM NO.
XS	178052
S	178102
M	178202
L	178302
XL	178352

All Sizes:

200 Gloves/Box, 10 Boxes/Case

✓ **Tested for use with
Chemotherapy Drugs
AND Fentanyl Citrate**

Features:

- Textured Finish = an Improved Wet/Dry Grip
- Low Modulus = a Softer, More Comfortable Fit
- Non-Latex = No Risk of Latex Allergens



Manufactured in compliance with multiple international standards, including ASTM D6319, ASTM D5151, ASTM F1671, and ASTM D6978

Tested for use with Chemotherapy Drugs as per ASTM D6978 Standard Practice for Assessment of Medical Gloves to Permeation by Chemotherapy Drugs Minimum Breakthrough Detection Time in Minutes:			
Azacytidine (25.0 mg/ml)	>240	Ifosfamide (50.0 mg/ml)	>240
Carboplatin (10.0 mg/ml)	>240	Irinotecan (20.0 mg/ml)	>240
Carmustine (3.3 mg/ml)	11.5	Methotrexate (25.0 mg/ml)	>240
Cisplatin (1.0 mg/ml)	>240	Mitomycin C (0.5 mg/ml)	>240
Cyclophosphamide (20.0 mg/ml)	>240	Mitoxantrone (2.0 mg/ml)	>240
Dacarbazine (10.0 mg/ml)	>240	Oncovin (1.0 mg/ml)	>240
Docetaxel (10.0 mg/ml)	>240	Oxaliplatin (5.0 mg/ml)	>240
Doxorubicin Hydrochloride (2.0 mg/ml)	>240	Paclitaxel (6.0 mg/ml)	>240
Epirubicin (2.0 mg/ml)	>240	Thiotepa (10.0 mg/ml)	24.3
Etoposide (20.0 mg/ml)	>240	Vincristine Sulfate (1.0 mg/ml)	>240
Fluorouracil (50.0 mg/ml)	>240	Vinorelbine (10.0 mg/ml)	>240
Gemcitabine (38.0 mg/ml)	>240	Also Tested: Fentanyl Citrate (100 mcg/2ml)	>240

Tensile Strength & Elongation	Before Aging	After Accelerated Aging
Tensile Strength (Mpa)	31.6	29.7
ASTM Requirement Min. (Mpa)	14	14
Elongation (%)	662	598
ASTM Requirement Min. (%)	500	400

Average Length	9.5 in ♦ 240 mm
Average Palm Thickness	3.0 mil ♦ 0.08 mm
Average Finger Thickness	3.7 mil ♦ 0.09 mm

Please note that Carmustine and Thiotepa have extremely low permeation times of 11.5 minutes and 24.3 minutes respectively.

Caution: In compliance with ASTM D6978, the testing conditions used are intended to approximate the worst-case conditions for clinical use. Testing was conducted on single layer glove material. It is the users' responsibility to determine the applicability of these gloves for their intended use with chemotherapy drugs.



Innovative Healthcare Corporation is certified to ISO 13485:2016 QMS for medical devices.



Product Solutions You Trust

View this product on our website:

