


FIBERGLASS RODS

FIBERGLASS RODS FOR THE POLYWOOD-EPOXY-SYSTEM

Wood, concrete and natural stone restoration



ADVANTAGES OF FIBERGLASS RODS

- ✓ Completely inert
- ✓ Non-corrosive
- ✓ Non-conductive
- ✓ Only one quarter of the weight of a steel rod
- ✓ Sand-coated to improve adhesion

Description

Fibreglass rods are used in both new construction and restoration works. They are fully inert, non-corrosive, non-conductive, and weigh only one quarter of the weight of a comparable steel rod. In terms of elasticity modulus, expansion and shrinkage, fibreglass rods are more compatible with wood than steel. The rods feature a spiral wrap and are sand-coated to enhance adhesion with epoxy, wood or concrete.

Application area

Used to create load-bearing connections and to reinforce timber (and concrete) elements or anchor natural stone. Typical applications include inserting reinforcements or connectors in beams, purlins, rafters, trusses, span elements, sills, thresholds, columns, window frames and other timber structures.

They are particularly suitable for beam-end restoration and the creation of timber prostheses (and can likewise be anchored in concrete). Natural stone can be reinforced by inserting the rods into drilled holes.

Fibreglass reinforcement rods are bonded using epoxy adhesives (such as RC 850) or cementitious grouts.

Application instructions

Cut the fibreglass rods to the required length using a cutting disc (according to the structural engineer's calculations). Keep the rods dry, clean and free from oils. Drill the number of holes and diameters as specified by the structural engineer. Avoid drilling holes within 4 cm of any surface cracks. Discuss the exact position of the holes with the structural engineer. Blow all dust from the drilled holes and bond using RC 850 or RC POLYHOUT-EPOXY resin (components A and B).

Technical properties

Service life	100 years	
Voluminous mass	$2 \pm 0,10 \text{ g/cm}^3$	
Glass fibre content	80% ($\pm 5\%$)	
Average glass transition temperature (TG)	$\geq 100 \text{ }^\circ\text{C}$	EN ISO 11357-2
Water absorption (24h)	$<0,25\% \text{ @ } 50^\circ\text{C}$	ASTM D570, subsection 7.4
Curing ratio	$\geq -10 \text{ }^\circ\text{C}$	
Alkali resistance	$\geq 80\%$	
Fire classification	E	UNI EN 13501-1:2019
Elasticity modulus (E)	$\geq 46 \text{ GPa}$	ISO 1046-1 subsection 6

Physical properties

Nominal rod diameter	mm	6	10	12	16	20
Measured diameter	mm	± 7.25	± 11.50	± 13.30	± 16.80	± 21.50
Nominal area	mm ²	28	78	113	201	314
Tensile strength (F_R)	Mpa	≥ 1000	≥ 1000	≥ 850	≥ 850	≥ 850
Ultimate strain (ϵ_R)	%	≥ 2.1	≥ 2.1	≥ 1.8	≥ 1.8	≥ 1.8
Ultimate tensile load	kN	28	≥ 78	≥ 96	≥ 170	≥ 266
Ultimate tensile strength of bent rods (f_{ub})	MPa	≥ 176	≥ 176	≥ 176	≥ 176	≥ 238
Ultimate tensile load of bent rods	kN	4.9	≥ 13.7	≥ 19.8	≥ 35.3	≥ 74.7
Ultimate transverse shear strength (τ_s)	MPa	-	≥ 140	≥ 140	≥ 140	≥ 140
Ultimate transverse shear load	kN	-	≥ 10.9	≥ 15.8	≥ 28.1	≥ 43.9
Bond strength in concrete C20/25	MPa	≥ 10	≥ 5	≥ 5	≥ 5	≥ 5
Minimum bending radius (r_i)	Mm	50	50	75	75	110

* Andere diktes en formaten op aanvraag.

Dimensions

Fiberglass rods are available in standard lengths of 3 metres.

We stock 6 mm, 10 mm, 12 mm and 20 mm diameters. Other diameters can be manufactured on request, subject to longer lead times.

Photos



Legal Notes

The information and recommendations contained in this document have been prepared in good faith based on the current knowledge and experience of Reynchemie, concerning products that are correctly stored, handled and applied under normal conditions and in accordance with our guidelines. Since practical conditions, materials and substrates may vary from one application to another, Reynchemie cannot guarantee the merchantability or suitability of the product for a particular purpose. The user remains responsible for carrying out preliminary tests to verify the compatibility of the product with the intended application. All stated values and properties are average results determined at 20 °C; reasonable deviations are acceptable. Products used in combination with this product within the same application system (such as preparation or finishing products) must always be applied according to the instructions provided in their respective technical data sheets. Reynchemie reserves the right to modify the composition or properties of its products without prior notice. Except where mandatory legal provisions apply, Reynchemie accepts no liability for damage resulting from improper application of its products or from failure to comply with the provided instructions. Third-party property rights must always be respected. All orders are accepted under the applicable sales and delivery conditions. Users must always consult the latest version of the local Technical Data Sheet (TDS) and Safety Data Sheet (SDS) for the respective product; copies will be provided upon request if not available on our website www.reynchemie.com. This document supersedes all previous versions.