

TECHNICAL DATA SHEET OF PP WOVEN GROUND COVER

TECHNICAL DATA SHEET					TEGC-90	TEGC-100
Sr. No	Test Name	Orientation	Test method	UOM	Required Value	Required Value
1	Roll Width		-	FT	As Required	As Required
2	Roll Length		-	FT	As Required	As Required
3	GSM		-	g/m ²	90	100
4	Mesh	MDXCD	-	EPI X PPI	10X10	10X10
5	Grab Breaking Load	MD	ASTM D 4632	LBS	145	160
		CD	ASTM D 4632	LBS	135	150
6	Elongation at Breaking	MD	ASTM D 4632	%	18	18
		CD	ASTM D 4632	%	18	18
7	Trapezoid Tearing Strength	MD	ASTM D 4533	LBS	55	60
	Trapezoid Tearing Strength	CD	ASTM D 4533	LBS	55	60
8	CBR Puncture	-	ASTM D 6241	LBS	350	450

Address: P2, Prime Industrial and Logistics Hub, Vadala Road,
 Near Bharat Gas Plant, N.H.8, Village: Hariyala,
 District: Kheda, Gujarat – 387570, India.
CIN: L29100GJ1989PLC012576
Email: export@geotexelin.com | sales@geotexelin.com
Website: www.geotexelin.com



Scan to View &
 Download all TDS