SunBloc 9000

BLACKOUT FABRIC (0%)

AVAILABLE COLOURS

White SB9010	
Cream SB9015	
Ivory SB9020	
Oyster SB9070	
Palomino SB9025	
Champagne SB9060	
Tan SB9030	
Grey SB9040	
Dark Grey SB9080	
Black SB9050	

FABRIC SPECIFICATIONS

Stock Widths:	36" / 45" / 54" / 72"
Openness:	0%
Composition:	27% Fiberglass 73% PCE Coating
Thickness:	.015"
Weight:	12.0 oz / yd^2
Fire Rating:	NFPA-701 CAN/ULC-S109
Bacterial/Fungal Resistance:	ASTM G21 ASTM 1428
Cleaning Info:	Contact Manufacturer
Spline:	Yes
Railroading:	Yes

10 YEAR INTERIOR WARRANTY

FIRE RATED

GREENGUARD

GREENGUARD GOLD

Constructed of tough, closely woven fiberglass and coated on both sides with durable, sun-resistant, flexible PCE film.

Flame, fade, and mildew resistant, washable and tear proof. Designed for tough service without that "institutional look"

If you require fabric samples please go to: www.frasershading.com/contact

Actual fabric colours may vary from pictures | Fabric stock levels may vary

Openness factors are approximate | Mockups are recommended

Specification subject to change without notice | ©Fraser Shading Systems 2026

FRASER SHADING SYSTEMS | Unit 101 – 5219 192nd Street | Surrey, BC, Canada V3S 4P6
Off: 604-881-4881 | Fax: 604-881-4882 | www.frasershading.com | www.instagram.com/fraser_shading_systems

CERTIFICATE OF COMPLIANCE

SunBloc 9000

Indiana Coated Fabrics

- Openness: 0 %

17135-420

Certificate Number

02 Jun 2011- 02 Jun 2026

Certificate Period

Certified

Status

UL 2818 - 2022 Gold Standard for Chemical Emissions for Building Materials, Finishes and Furnishings

Window treatments are determined compliant in accordance with California Department of Public Health (CDPH) Standard Method V1.2-2017 using an Office and Classroom Environment. Product tested in accordance with UL 2821 test method to show compliance to emission limits on UL 2818. Section 7.1 and 7.2.

GREENGUARD Gold Certification Criteria for Building Products and Interior Finishes

Criteria	CAS Number	Maximum Allowable Predicted Concentration	Units
TVOC (A)	-	0.22	mg/m³
Formaldehyde	50-00-0	9 (7.3 ppb)	µg/m³
Total Aldehydes (B)	-	0.043	ppm
4-Phenylcyclohexene	4994-16-5	6.5	µg/m³
Particle Matter less than 10 µm (C)	-	20	µg/m³
1-Methyl-2-pyrrolidinone (D)	872-50-4	160	µg/m³
Individual VOCs (E)	-	1/2 CREL or 1/100th TLV	-

(A) Defined to be the total response of measured VOCs falling within the C6 – C16 range, with responses calibrated to a toluene surrogate. Maximum allowable predicted TVOC concentrations for GREENGUARD Gold (0.22 mg/m³) fall in the range of 0.5 mg/m³ or less, as specified in CDPH Standard Method v1.2.

(B) The sum of all measured normal aldehydes from formaldehyde through nonanal, plus benzaldehyde, individually calibrated to a compound specific standard. Heptanal through nonanal are measured via TD/GC/MS analysis and the remaining aldehydes are measured using HPLC/UV analysis.

(C) Particle emission requirement only applicable to HVAC Duct Products with exposed surface area in air streams (a forced air test with specific test method) and for wood finishing (sanding) systems.

(D) Based on the CA Prop 65 Maximum Allowable Dose Level for inhalation of 3,200 µg/day and an inhalation rate of 20 m³/day

(E) Allowable levels for chemicals not listed are derived from the lower of 1/2 the California Office of Environmental Health Hazard Assessment (OEHHA) Chronic Reference Exposure Level (CREL) as required per the CDPH/EHLB/Standard Method v1.2 and BIFMA level credit 7.6.2 and 1/100th of the Threshold Limit Value (TLV) industrial work place standard (Reference: American Conference of Government Industrial Hygienists, 6500 Glenway, Building D-7, and Cincinnati, OH 45211-4438).

FRASER SHADING SYSTEMS | Unit 101 – 5219 192nd Street | Surrey, BC, Canada V3S 4P6
Off: 604-881-4881 | Fax: 604-881-4882 | www.frasershading.com | www.instagram.com/fraser_shading_systems