



SunBloc 9100

BLACKOUT FABRIC (0%)

AVAILABLE COLOURS

	FRONT	BACK (White)
Cream SB9115		
Ivory SB9102		
Putty SB9150		
Linge SB9185		
Mineral Dust SB9145		
Grey SB9110		
Dark Grey SB9140		
Chocolate SB9120		
Denim SB9135		
Navy SB9190		
Forest Green SB9160		
Black SB9170		

FABRIC SPECIFICATIONS

Stock Widths:	36" / 45" / 54" / 72"
Openness:	0%
Composition:	27% Fiberglass 73% PCE Coating
Thickness:	.013"
Weight:	12.0 oz / yd ²
Fire Rating:	NFPA-701 CAN/ULC-S109
Bacterial/Fungal Resistance:	ASTM G21 ASTM 1428
Cleaning Info:	Contact Manufacturer
Spline:	Yes
Railroading:	Yes



Constructed of tough, closely woven fiberglass and coated on both sides with durable, sun-resistant, flexible PCE film and white backing. Flame, fade, and mildew resistant, washable and tear proof. Designed for tough service without that "institutional look"

If you require fabric samples please go to: www.fraser shading.com/contact

Actual fabric colours may vary from pictures | Fabric stock levels may vary

Openness factors are approximate | Mockups are recommended

Specification subject to change without notice | ©Fraser Shading Systems 2026



CERTIFICATE OF COMPLIANCE



SunBloc 9100

Indiana Coated Fabrics

- Openness: 0 %

17135-420

Certificate Number

02 Jun 2011- 02 Jun 2026

Certificate Period

Certified

Status

UL 2818 - 2022 Gold Standard for Chemical Emissions for Building Materials, Finishes and Furnishings

Window treatments are determined compliant in accordance with California Department of Public Health (CDPH) Standard Method V1.2-2017 using an Office and Classroom Environment. Product tested in accordance with UL 2821 test method to show compliance to emission limits on UL 2818. Section 7.1 and 7.2.

GREENGUARD Gold Certification Criteria for Building Products and Interior Finishes

Criteria	CAS Number	Maximum Allowable Predicted Concentration	Units
TVOC (A)	-	0.22	mg/m ³
Formaldehyde	50-00-0	9 (7.3 ppb)	µg/m ³
Total Aldehydes (B)	-	0.043	ppm
4-Phenylcyclohexene	4994-16-5	6.5	µg/m ³
Particle Matter less than 10 µm (C)	-	20	µg/m ³
1-Methyl-2-pyrrolidinone (D)	872-50-4	160	µg/m ³
Individual VOCs (E)	-	1/2 CREL or 1/100th TLV	-

- (A) Defined to be the total response of measured VOCs falling within the C6 – C16 range, with responses calibrated to a toluene surrogate. Maximum allowable predicted TVOC concentrations for GREENGUARD Gold (0.22 mg/m³) fall in the range of 0.5 mg/m³ or less, as specified in CDPH Standard Method v1.2.
- (B) The sum of all measured normal aldehydes from formaldehyde through nonanal, plus benzaldehyde, individually calibrated to a compound specific standard. Heptanal through nonanal are measured via TD/GC/MS analysis and the remaining aldehydes are measured using HPLC/UV analysis.
- (C) Particle emission requirement only applicable to HVAC Duct Products with exposed surface area in air streams (a forced air test with specific test method) and for wood finishing (sanding) systems.
- (D) Based on the CA Prop 65 Maximum Allowable Dose Level for inhalation of 3,200 µg/day and an inhalation rate of 20 m³/day
- (E) Allowable levels for chemicals not listed are derived from the lower of 1/2 the California Office of Environmental Health Hazard Assessment (OEHHA) Chronic Reference Exposure Level (CREL) as required per the CDPH/EHLB/Standard Method v1.2 and BIFMA level credit 7.6.2 and 1/100th of the Threshold Limit Value (TLV) industrial work place standard (Reference: American Conference of Government Industrial Hygienists, 6500 Glenway, Building D-7, and Cincinnati, OH 45211-4438).

