

Characteristics

70-275 is a high-quality acrylic clearcoat for fast and economic car refinishing (express technology), especially in case of oven drying. After the drying of 15 minutes at 60 °C or alternatively 25 minutes at 40°C plus cooling time it is possible to start already the polishing process. 70-275 2K Fast Clearcoat is also suitable for partial car coatings. Ready for use after the addition of hardener 70-260HN/70-260HF. This product provides excellent resistance against environmental and weathering conditions as well as yellowing and offers durable gloss retention.

Physical Characteristics



12 month




2004/42/IIB(d)(420)<420



2:1
70-260HN / 70-260HF

Application



17 - 19 s
4 mm DIN



1,2 - 1,3 mm
2,0 - 2,2 bar

Consumption: 9 - 10 m²/l



1,5 - 2



Between the coatings
Before the oven drying

3 - 5 min
10 - 15 min



50 - 60 µm

Drying



dust free: 15 - 20 min
set to touch: 1 - 2 h
ready for assembly 6 h

set to touch: 15 min (HN)
set to touch: 5 min (HF)
ready for assembly after cooling

shortwave 8 minutes
mediumwave 10 - 15 minutes

20°
1 - 1,5 h

Storage



Store the product in a ventilated place. Keep away from direct exposure to sunlight. Keep between +5°C and 20°C.

Safety



For more informations check the safety data sheet.



This data sheet is for information purpose only. To our knowledge the data provided complies with the latest standard and is based on years of experience in the manufacturing of our products. Copyright: Q-Company Int. GmbH, all rights reserved.