

BATTERIES POL-R


TECHNICAL DATA SHEET

PGC2AGMDT



SPECIFICATIONS

Part Number	PGC2AGMDT	
BCI	GC2	
Volt	6 Volts	
Type	AGM	
Terminal	Dual, auto post + stud 5/16"	
Terminal Torque	176-203 in-lb (20-23 Nm)	
Container Material	ABS	
Reserve Capacity	25A	460 min
	56 A	175 min
	75 A	120 min
Capacity	20 Hr	210 Ah
	5 Hr	175 Ah
	Discharge	-20~55°C (-4~131°F)
Operating Temp. Range	Charge	0~40°C (32~104°F)
	Storage	-15~40°C (5~104°F)



carbon



GENERAL FEATURES

Stable initial capacity

- PAM/NAM amount optimization
- 4BS crystal paste mixing & curing technology
- Double layer separator technology
- Improved design electrolyte S.G.

Less water loss

- PAM/NAM amount optimization
- New PAM/NAM recipe introduced
- Rare earth alloy

Solve NAM sulphation

- Carbon boost technology
- Pre-sulfate technology

Improved PSoC cycling

- Carbon boost technology
- Mix carbon boost technology
- Targeting for higher level through carbon technology

Delay PAM softening and shedding

- Plate assembly pressure re-engineering
- 4BS crystal paste mixing & curing technology
- Higher paste density

Optimize electrolyte stratification

- Introduce new AGM technology


Excellent deep cycle performance

- Plate assembly pressure re-engineering
- New PAM/NAM recipe introduced
- AGM electrolyte technology
- Rare earth alloy
- Double layer separator technology
- Lower acid filling temperature

DIMENSIONS


Length	260 mm (10 1/4")
Width	180 mm (7 1/16")
Case Height	252 mm (9 15/16")
Overall Height	274 mm (10 13/16")
Weight	30.4 kg (67.0 lbs)

DRAWING




CHARGE / DISCHARGE PERFORMANCE CURVES


Charging Profiles




Relationship of OCV and State Of Charge



Cycle Life in Relation to Depth Of Discharges



Self-discharge Characteristics



POL-R, all rights reserved. POL-R is not liable for damages that may occur from any information provided in or omitted from this publication, under any circumstances. POL-R reserves the right to make changes or adjustments to this publication at any time without notices or obligations.

POL-R