



■ Transparente

Especificaciones: 48MM / 72 mm / 144 mm x 914 m / 1828 m

Temp. Máx de trabajo en funcionamiento: 80°C

Temp. De trabajo: 10 °C - 40°C



Producto	Grosor total	Adhesión al pelado		Resistencia a la tracción		% de elongación a la rotura
	(µm)	(N/in)	ASTM D-3330 (oz/in)	(N/in)	ASTM D-3759 (lb/in)	ASTM D-3759
BHC038-b	38µm	4.1	14.75	80↑	17.9↑	100%
BHC040-b	40µm	4.2	15.11	80↑	17.9↑	100%
BHC043-zy8	43µm	4.4	15.8	80↑	17.9↑	100%
BHC045-zy8	45µm	4.5	16.12	82↑	18.43↑	100%
BHC047-b	47µm	4.8	17.19	82↑	18.43↑	100%
BHC050-zy8	50µm	5.2	18.71	85↑	19.01↑	100%
BHC055-b	55µm	5.5	19.8	85↑	19.01↑	100%
BHC060-b	60µm	5.5	19.8	100↑	22.5↑	100%



□ Blanco

Especificaciones: 48MM / 72 mm / 144 mm x 914 m / 1828 m

Temp. Máx de trabajo en funcionamiento: 80°C

Temp. De trabajo: 10 °C - 40°C



Producto	Grosor total	Adhesión al pelado		Resistencia a la tracción		% de elongación a la rotura
	(µm)	(N/in)	ASTM D-3330 (oz/in)	(N/in)	ASTM D-3759 (lb/in)	ASTM D-3759
BHC038-b	38µm	4.1	14.75	80↑	17.9↑	100%
BHC040-b	40µm	4.2	15.11	80↑	17.9↑	100%
BHC043-zy8	43µm	4.4	15.8	80↑	17.9↑	100%
BHC045-zy8	45µm	4.5	16.12	82↑	18.43↑	100%
BHC047-b	47µm	4.8	17.19	82↑	18.43↑	100%
BHC050-zy8	50µm	5.2	18.71	85↑	19.01↑	100%
BHC055-b	55µm	5.5	19.8	85↑	19.01↑	100%
BHC060-b	60µm	5.5	19.8	100↑	22.5↑	100%



■ Canela

Especificaciones: 48MM / 72 mm / 144 mm x 914 m / 1828 m

Temp. Máx de trabajo en funcionamiento: 80°C

Temp. De trabajo: 10 °C - 40°C



Producto	Grosor total	Adhesión al pelado		Resistencia a la tracción		% de elongación a la rotura
	(µm)	(N/in)	ASTM D-3330 (oz/in)	(N/in)	ASTM D-3759 (lb/in)	ASTM D-3759
BHC038-b	38µm	4.1	14.75	80↑	17.9↑	100%
BHC040-b	40µm	4.2	15.11	80↑	17.9↑	100%
BHC043-zy8	43µm	4.4	15.8	80↑	17.9↑	100%
BHC045-zy8	45µm	4.5	16.12	82↑	18.43↑	100%
BHC047-b	47µm	4.8	17.19	82↑	18.43↑	100%
BHC050-zy8	50µm	5.2	18.71	85↑	19.01↑	100%
BHC055-b	55µm	5.5	19.8	85↑	19.01↑	100%
BHC060-b	60µm	5.5	19.8	100↑	22.5↑	100%



■ Transparente

Especificaciones: 72MM X 200M / 914M /1828M

144MM X 200M / 914M/1828M

Temp. Máx de trabajo en funcionamiento: 80°C

Temp. De trabajo: 10 °C - 40°C



Producto	Grosor total	Adhesión al pelado		Resistencia a la tracción		% de elongación a la rotura
	(µm)	(N/in)	ASTM D-3330 (oz/in)	(N/in)	ASTM D-3759 (lb/in)	ASTM D-3759
BHB038	38µm	7.8	28	80↑	17.9↑	100%
BHB040	40µm	8.2	29.5	80↑	17.9↑	100%
BHB045-2	45µm	8.4	30.2	85↑	19.1↑	100%
BHB047	47µm	8.5	30.5	85↑	19.1↑	100%
BHB050-2	50µm	8.8	31.6	90↑	20.23↑	100%



□ Blanco

Especificaciones: 72MM X 200M / 914M /1828M

144MM X 200M / 914M/1828M

Temp. Máx de trabajo en funcionamiento: 80°C

Temp. De trabajo: 10 °C - 40°C



Producto	Grosor total	Adhesión al pelado		Resistencia a la tracción		% de elongación a la rotura
	(µm)	(N/in)	ASTM D-3330 (oz/in)	(N/in)	ASTM D-3759 (lb/in)	ASTM D-3759
BHB038	38µm	7.8	28	80↑	17.9↑	100%
BHB040	40µm	8.2	29.5	80↑	17.9↑	100%
BHB045-2	45µm	8.4	30.2	85↑	19.1↑	100%
BHB047	47µm	8.5	30.5	85↑	19.1↑	100%
BHB050-2	50µm	8.8	31.6	90↑	20.23↑	100%



■ Canela

Especificaciones: 72MM X 200M / 914M /1828M

144MM X 200M / 914M/1828M

Temp. Máx de trabajo en funcionamiento: 80°C

Temp. De trabajo: 10 °C - 40°C



Producto	Grosor total	Adhesión al pelado		Resistencia a la tracción		% de elongación a la rotura
	(µm)	(N/in)	ASTM D-3330 (oz/in)	(N/in)	ASTM D-3759 (lb/in)	ASTM D-3759
BHB038	38µm	7.8	28	80↑	17.9↑	100%
BHB040	40µm	8.2	29.5	80↑	17.9↑	100%
BHB045-2	45µm	8.4	30.2	85↑	19.1↑	100%
BHB047	47µm	8.5	30.5	85↑	19.1↑	100%
BHB050-2	50µm	8.8	31.6	90↑	20.23↑	100%