



TECHNICAL DATA SHEET

P214

V2-22/03/2024

QC EPOXY BINDER

DESCRIPTION

A solvent free epoxy binding and casting resin with excellent non-yellowing properties.

PROPERTIES

Excellent Adhesion

Tensile Strength: 20Mpa Flexural Strength: 20Mpa

Hardness (Shore A): 95

RECOMMENDED AREAS FOR USE

Designed as a binder for Quartz and Silica aggregates. May also be used as a primer and topcoat for epoxy floors.

COLOUR	: Clear
N°. OF COMPONENTS	: 3
MIXING RATIO (VOL)	: 2:1
CONSISTENCY	: Liquid
VOLUME SOLIDS	: 100%
MIXED DENSITY	: 1.09
POT LIFE @ 25°C	: 30 min
TOUCH DRY @ 25°C	: 6 hrs
HARD DRY @ 25°C	: 24 hrs
FULL CURE	: 7 days
CLEANER	: P701 WSBC
SHELF LIFE	: 12 months
PACK SIZE	: 15 Litres

MIXING RATIO WITH QUARTZ

AGGREGATE

: Base: 1.2lt (1.36kg) : Activator: 0.6lt (0.64kg)

: Aggregate: 25kg

CHEMICAL RESISTANCE

Resists most common aggressive chemicals, petroleum products, dilute acids, alkalis, aliphatic solvents and sea water.

SURFACE PREPARATION

All surfaces must be clean, structurally sound, and free of dust, oil and dirt. Concrete surfaces should be abrasive blasted or acidetched to remove laitance. Moisture content should be below 10%.

MIXING INSTRUCTIONS

Mix the base and activator in the proportions given using a slow mechanical mixer, then add the aggregate and mix again. Make sureonly enough is mixed that can be used within 20 minutes at 25°C.

Although P214 is safe, inert and harmless when fully cured, care should be taken to avoid skin contact or inhalation of the uncuredcomponents during mixing and application. Refer to the relevant 16-point Safety Data Sheet.

