

NIAGARA GAVARNIE

“Timeless and exceptional durability”

TANNING TARGET

Grain resistance to abrasion, balance between firmness and softness, easy cutting, thickness over time

Vegetable tanning, wax/tallow nourishment, quebracho mimosa, oak, chestnut tanning agents.

FINISHING TARGET

Natural – Grip

Aniline finish, semi aniline finish, wax or extra grip finish, grain and flesh side hardener.

HORSE EQUIPMENT

Hard Leather





ENRICH YOUR LEATHER

COLORS

- Dyed through or on surface, contrast levels
- Shiny / matt
- Master sample

FEEL

- Natural touch
- Extragrip touch
- Firmness / flexible

GRAIN

- Natural grain
- Grainprints available
- Extra protective finish possible

THICKNESS

- 3,0-3,5mm
- 3,5-4,0mm
- 4,0-4,5mm
- On demand

HIDES

- Shoulder
- Half back/dosset
- Half butt

SELECTION & CUTTING SERVICE

A natural leather requires selection. We base our selection on your saddle pattern on hides.

We provide a cutting service to offer 100% usable leather avoiding any waste for the customer. No waste means more savings.

LABELS, ORIGIN & TRACEABILITY

- Responsibly farmed bull leather
- 100% European origin
- Belgium Artisan Certified
- Sustainable water consumption
- Renewable chemicals REACH compliance



TEST TABLE

	METHOD			SAMPLE		RESULT NIAGARA	RESULT GAVARNIE
Veslic rub fastness dry	1kg/100 c	ISO 11640			ISO 2419	5	4/5
Veslic rub fastness wet	1kg/25 c	ISO 11640			ISO 2419	2/3	3
Tear load			TVS 10KN100			335kg	367kg
Tear resistance			TVS 10KN100			2,85kg/mm ²	3,26 kg / mm ²
Elongation at rupture			TVS 10KN100			59,4 mm	40mm
Tensile endurance elongation	30-0,5kg/ 1000 c	ISO 3376	TVS 10KN100	ISO 2419	12x200 mm	6,3%	2,6%

