europlac®

FIREPLAC® SE

FIREPLAC® SE consists of flame-retardant chipboard veneered with 0.6 mm oak and then UV varnished.













Especially suitable for ceilings; walls; furniture



FIREPLAC® SE

CORE BOARD	Recommended configuration	Individualisation	
Core board:	Chipboard flame retardant		
Core board thickness:	19 mm	see core board table	
FORMATS			
Formats:	2800 x 2070 mm	fixed dimensions possible	
VENEER GLUING			
Veneer gluing:			
VISIBLE SIDE			
Veneer:	exclusively European oak (certificate)		
Quality:	A-First Quality	A-Pattern matching 5*, A, B, C:	
Grading:	Half-crown cut	2 further grading types: see www.europlac.com/customisation	
Bonding method:	Veneer book matched	6 further bonding methods see www.europlac.com/customisation	
Veneer thickness:	approx. 0,6 mm (certificate)		
Surface processing:	Rough-ground (grain 120)	further surface processings: see www.europlac.com/customisation	
Surface finishing:	UV-lacquered matt	5 further surface finishes: see www.europlac.com/customisation	
REVERSE SIDE			
Veneer:	exclusively European oak (certificate)		
Quality:	В	A-First Quality, A, C, paper, factory selection:	
Bonding method:	Veneer book matched	6 further bonding methods see www.europlac.com/customisation	
Veneer thickness:	approx. 0,6 mm (certificate)		
Surface processing:	Rough-ground (grain 120)	further surface processings: see www.europlac.com/customisation	
Surface finishing:	UV-lacquered matt	5 further surface finishes: see www.europlac.com/customisation	

CERTIFICATES

FSC® / PEFC / E1 / E0.5: Certificate depending on the product version.

ADDITIONAL INFORMATION

Flame retardant in composite tested according to EN 13501-1:2019, test incl. veneer edge 0.5 mm. Classification: C-s2, d0.





FIREPLAC® SE

VARIATIONS

Thickness	Standard format	Classification	Classification report
17mm	2800x2070mm	C-s2, d0	FIRES-CR-161-24-AUPS
19mm	2800x2070mm	C-s1, d0	FIRES-CR-161-24-AUPS
29mm	2655x2100mm	B-s1, d0	PK-18-090

Note: Please note that wood is a natural product. Irregularities in color and structure are a natural characteristic and are generally desirable. Please understand that samples and illustrations regarding color and structure can only be an indication.

