

FIREPLAC® VE-A2

veneered with noblewood

Core board – consisting mainly of perlite – veneered with fine oak wood



low weight



incombustible




recyclable



formaldehyde-free



long tool life



Especially suitable for
ceilings; walls; furniture; shop fitting and exhibition stands;

FIREPLAC® VE-A2

veneered with noblewood

	Recommended configuration	Individualisation
CORE BOARD		
Core board:	carrier mainly made of perlite, A2-sI, d0 according to EN 13501-1	
Core board thickness:	20 mm	see core board table
FORMATS		
Formats:	2420 x 1210 (Thickness 15-40 mm)	2440 x 1080 (Thickness 50-100 mm)
VENEER GLUING		
Veneer gluing:	D3 NAF according to EN 204	D4 according to EN 204
VISIBLE SIDE		
Veneer:	European oak	140 wood species see www.europlac.com/customisation
Quality:	A-First Quality	A-Pattern matching 5*, A, B, C: see www.europlac.com/customisation
Grading:	Half-crown cut	2 further grading types: see www.europlac.com/customisation
Bonding method:	Veneer book matched	6 further bonding methods see www.europlac.com/customisation
Veneer thickness:	approx. 0,6 mm	
Surface processing:	Rough-ground (grain 120)	further surface processings: see www.europlac.com/customisation
Surface finishing:		5 further surface finishes: see www.europlac.com/customisation
REVERSE SIDE		
Veneer:	Eiche euro	140 wood species see www.europlac.com/customisation
Quality:	B	A-First Quality, A, C, paper, factory selection: see www.europlac.com/customisation
Bonding method:	Veneer book matched	6 further bonding methods see www.europlac.com/customisation
Veneer thickness:	approx. 0,6 mm	
Surface processing:	Rough-ground (grain 120)	further surface processings: see www.europlac.com/customisation
Surface finishing:		5 further surface finishes: see www.europlac.com/customisation

CERTIFICATES

FSC® / PEFC / E1 / E0.5: Certificate depending on the product version

ADDITIONAL INFORMATION

Core board: Weight: 550 kg/m³, flexural strength VIAM048 approx. 5 N/mm², compressive strength TIAM031 approx. 9N/mm²
The material wood is a natural product. Characteristic are color and structure differences.

ences. These natural features qualify the precious wood material as real and give it a unique beauty. Samples and illustrations can only serve as a guide.

Note: Please note that wood is a natural product. Irregularities in color and structure are a natural characteristic and are generally desirable. Please understand that samples and illustrations regarding color and structure can only be an indication.

CONTACT OUR EXPERT TEAM

Röhr GmbH | Narzissenstr. 5
88069 Tettnang | Deutschland

Tel. +49 7542 93660
info@europlac.com