



APPLICATION ANWENDUNG / APPLICATION / TOEPASSING	LANDSCAPING
PRODUCTION METHOD HERSTELLUNGSVERFAHREN / MODE DE FABRICATION / PRODUCTIEPROCES	TUFTED
FIBRE FASER / FIBRE / VEZEL / FIBRA / FIBRA	PE + PP DTEX 12000
PILE HEIGHT POLHÖHE / HAUTEUR DU VELOURS / POOLHOOGTE	±50 MM
TOTAL HEIGHT GESAMTHÖHE / HAUTEUR TOTALE / TOTALE HOOGTE	±52 MM
PILE WEIGHT POLEINSATZGEWICHT / POIDS DU VELOURS / POOLGEWICHT	± 1603 GR/M²
TOTAL WEIGHT GESAMTGEWICHT / POIDS TOTAL / TOTAALGEWICHT	± 2785 GR/M²
GAUGE TUFTTEILUNG / JAUGE / TUFTDELING	3/8"
STITCHES (10 CM') STICHZAHL / NOMBRE DE POINTS / STEKENAANTAL	± 25 /10CM'
STITCHES (M²) STICHZAHL / NOMBRE DE POINTS / STEKENAANTAL	± 26250 /M²
PRIMARY BACKING TRÄGER / DOSSIER PRIMAIRE / TUFTDOEK	UV RESISTANCE PP CLOTH ± GR/M²
SECONDARY BACKING RÜCKEN / DOSSIER SECONDAIRE / SECUNDAIRE BACKING	LATEX ± GR/M²
WATER PERMEABILITY WASSERDURCHLASSIGKEIT / PERMÉABILITÉ / WATERDOORLATENDHEID	1800 L/H/M2
UV-STABILITY	ISO 4892-3:2012
COLORFASTNESS	GREY SCALE 4-5
CHLORINE RESISTANCE	GRADE 4 (ISO 105-E03-2010)
FIRE SAFETY CERTIFICATE + NORM	EFL EN 13501-1:2007 + A1:2009
ROLL WIDTH ROLLBREITE / LARGEUR DES ROULEAUX / ROLBREEDTE	2 M / 4 M
ROLL LENGTH ROLLÄNGE / LONGUEUR DES ROULEAUX / ROLLENGTE	±25 M
UV-WARRANTY NORTH EUROPE ABOVE PARIS, SOUTH EUROPE BELOW PARIS UV-GARANTIE / GARANTIE UV / UV GARANTIE	NORTHERN EUROPE: 7 YEARS / SOUTHERN EUROPE: 5 YEARS
PRODUCT WARRANTY PRODUKTGARANTIE / GARANTIE DU PRODUIT / PRODUCTGARANTIE	8 YEARS

