

**BE37C01****White polyester basecoat styrene-free**

<b>Color</b>	White	
<b>Area of use</b>	Furniture	
<b>Application</b>	Spray	
<b>Mixing</b>	<b>Product</b> BE37C01 JE001 JE002 Thinner	<b>Weight</b> 100 2 2 15-20

**TECHNICAL CHARACTERISTICS:**

<b>Specific gravity (kg/l)</b>	1.430 ± 0.010
<b>Solids content (%)</b>	78 ± 1
<b>Viscosity (DIN8 at 20°C)</b>	25" ± 5

**GENERAL CHARACTERISTICS:**

<b>Pot-life at 20°C</b>	4-5 h
<b>Recommended application weight (g/m<sup>2</sup>)</b>	150 - 250
<b>Number of layers</b>	2-3
<b>Interval between layers</b>	40-60 min
<b>Drying time (100 g/m<sup>2</sup> at 20°C)</b>	Dust free: 40 min Touch dry: 2-3 h Stackable: 12 h minimum Sandable after 16 h

**GENERAL CHARACTERISTICS:**

<b>Substrate preparation</b>	Sanding with P240 abrasive
<b>Shelf-life (months)</b>	4

**FEATURES:**

- good hiding power
- good sandability
- the product gives a longer pot-life of the mixture

**SUBSTRATE PREPARATION:**

The substrate must be properly prepared and cleaned of all kinds of dirt and dust.

**WARNING:**

Use only hardeners and thinners recommended by the company's technologists.

**TRANSPORTATION AND STORAGE:**

The product should be stored in a tightly closed can, protected from moisture and direct sunlight. After opening the package, the product should be used as quickly as possible. More detailed information on handling the product please find in the safety data sheet.

**HEALTH & SAFETY:**

For full Health and Safety information, please refer to Safety Data Sheet.

Suitable protective equipment (glasses, gloves, mask etc.) must be worn while using these products. Good ventilation must be provided in the working environment.