

GRP1033.00.0001**Polyurethane basecoat white**

Color	White	
Area of use	MDF, solid wood, veneer, plywood. Horizontal and vertical surfaces	
Application	Spray, Airmix, Airless spray	
Mixing	Product GRP1033.00.0001 HHP1033.00.0000 Thinner	Weight 100 30 10-20

TECHNICAL CHARACTERISTICS:

Specific gravity (kg/l)	1.550 ± 0.03
Solids content (%)	76 ± 2
Viscosity (KU at 25°C)	100-105
Viscosity (DIN4 at 20°C)	13-16"

GENERAL CHARACTERISTICS:

Pot-life at 20°C	3
Recommended application weight (g/m²)	Min 100 - Max 180
Number of layers	1-3
Interval between coats: (at 20°C)	Min: 20' Max: 60'
Drying time (100 g/m² at 20°C)	Dust free: 10-15' Touch dry: 25-30' Sanding: 60-80' Stackable: 720
Forced drying* (100 g/m²): 40°C)	Sanding: 30' Stackable: 3 hours

GENERAL CHARACTERISTICS:

Substrate preparation	The longer the drying of the basecoat, the less shrinkage in the end.
Shelf-life (months)	24

*forced drying:

Flash off at 20°C – 5'; drying at 40°C – 15'; cooling до 20°C – 10'.

FEATURES:

- Good leveling, suitable for large surfaces
- High filling power and covering

SUBSTRATE PREPARATION:

The substrate must be properly prepared and cleaned of all kinds of dirt and dust.

WARNING:

Use only hardeners and thinners recommended by the company's technologists.

TRANSPORTATION AND STORAGE:

The product should be stored in a tightly closed can, protected from moisture and direct sunlight. After opening the package, the product should be used as quickly as possible. More detailed information on handling the product please find in the safety data sheet.

HEALTH & SAFETY:

For full Health and Safety information, please refer to Safety Data Sheet.

Suitable protective equipment (glasses, gloves, mask etc.) must be worn while using these products. Good ventilation must be provided in the working environment.