

**TP45GXXC01****Polyurethane converter white matte**

<b>Color</b>	White	
<b>Gloss level</b>	10, 20	
<b>Area of use</b>	Furniture, doors	
<b>Application</b>	Spray	
<b>Mixing</b>	<b>Product</b> TP45GXXC01 JP003 Thinner	<b>Weight</b> 100 50 10-30

**TECHNICAL CHARACTERISTICS:**

<b>Specific gravity (kg/l)</b>	1.280 ± 0.03
<b>Solids content (%)</b>	61 ± 2
<b>Viscosity (DIN6 at 20°C)</b>	70" ± 5

**GENERAL CHARACTERISTICS:**

<b>Pot-life at 20°C</b>	2h
<b>Recommended application weight (g/m<sup>2</sup>)</b>	Min 120 - Max 160
<b>Number of layers</b>	1
<b>Drying time (100 g/m<sup>2</sup> at 20°C)</b>	Dust free: 20-30' Touch dry: 50-60' Stackable: 12 hours

**GENERAL CHARACTERISTICS:**

<b>Substrate preparation</b>	Sanding with P320-P400 abrasive
<b>Shelf-life (months)</b>	12

**FEATURES:**

- good scratch resistance
- smooth to the touch
- good leveling
- good surface hardness

**SUBSTRATE PREPARATION:**

The substrate must be properly prepared and cleaned of all kinds of dirt and dust.

**WARNING:**

Use only hardeners and thinners recommended by the company's technologists.

**TRANSPORTATION AND STORAGE:**

The product should be stored in a tightly closed can, protected from moisture and direct sunlight. After opening the package, the product should be used as quickly as possible. More detailed information on handling the product please find in the safety data sheet.

**HEALTH & SAFETY:**

For full Health and Safety information, please refer to Safety Data Sheet.

Suitable protective equipment (glasses, gloves, mask etc.) must be worn while using these products. Good ventilation must be provided in the working environment.