

BE38C00**Clear polyester basecoat styrene-free**

Color	Clear	
Area of use	Product is suitable for finishing of bathroom's furniture, kitchen cabinets, flat surfaces, items and accessories in general	
Application	Spray	
Mixing	Product BE38C00 JE001 JE002 Thinner	Weight 100 2 2 10-20

TECHNICAL CHARACTERISTICS:

Specific gravity (kg/l)	1.030 ± 0.010
Solids content (%)	79 ± 1
Viscosity (DIN4 at 20°C)	30" ± 3

GENERAL CHARACTERISTICS:

Pot-life at 20°C	20 ± 2 min
Recommended application weight (g/m²)	150 - 250
Number of layers	2-3
Interval between layers	40-60 min
Drying time (100 g/m² at 20°C)	Dust free: 40-60 min Touch dry: 2-3 h Stackable: 12 h minimum Sandable after 24 h

GENERAL CHARACTERISTICS:

Substrate preparation	Sanding with P240 abrasive. While working on exotic hardwoods, it is recommended to apply an insulating basecoat before.
Shelf-life (months)	6

FEATURES:

- great wetting properties
- good sandability
- good built.

SUBSTRATE PREPARATION:

The substrate must be properly prepared and cleaned of all kinds of dirt and dust.

WARNING:

Use only hardeners and thinners recommended by the company's technologists.

TRANSPORTATION AND STORAGE:

The product should be stored in a tightly closed can, protected from moisture and direct sunlight. After opening the package, the product should be used as quickly as possible. More detailed information on handling the product please find in the safety data sheet.

HEALTH & SAFETY:

For full Health and Safety information, please refer to Safety Data Sheet.

Suitable protective equipment (glasses, gloves, mask etc.) must be worn while using these products. Good ventilation must be provided in the working environment.