

KVP5015.XX.0001**Polyurethane converter (base for tinting) white**

| | | |
|--------------------|---|-------------------------------------|
| Color | White | |
| Gloss | 5, 10, 20, 30 | |
| Area of use | Tintable topcoat | |
| Application | Spray | |
| Mixing | Product KVP5015.XX.0001 HHP5015.00.0000 Thinner | Weight 100 50 15-20 |

TECHNICAL CHARACTERISTICS:

| | |
|--------------------------------|--------------|
| Specific gravity (kg/l) | 1.420 ± 0.03 |
| Solids content (%) | 72 ± 2 |
| Viscosity (KU at 25°C) | 100-105 |

GENERAL CHARACTERISTICS:

| | |
|---|---|
| Pot-life at 20°C | 4-5 |
| Recommended application weight (g/m²) | Min 90 - Max 110 |
| Number of layers | 1-2 |
| Interval between coats: (at 20°C) | Min: 45' Max: 60' |
| Drying time (100 g/m² at 20°C) | Dust free: 15-20' Touch dry: 45-60' Stackable: 6-8h |

GENERAL CHARACTERISTICS:**Shelf-life (months)**

12

FEATURES:

- yellowing resistance
- color stability
- high hiding power
- very good levelling
- very good scratch resistance

SUBSTRATE PREPARATION:

The substrate must be properly prepared and cleaned of all kinds of dirt and dust.

WARNING:

Use only hardeners and thinners recommended by the company's technologists.

TRANSPORTATION AND STORAGE:

The product should be stored in a tightly closed can, protected from moisture and direct sunlight. After opening the package, the product should be used as quickly as possible. More detailed information on handling the product please find in the safety data sheet.

HEALTH & SAFETY:

For full Health and Safety information, please refer to Safety Data Sheet.

Suitable protective equipment (glasses, gloves, mask etc.) must be worn while using these products. Good ventilation must be provided in the working environment.