

LKA3066.99.0000**Clear acrylic high gloss topcoat**

Color	Clear	
Gloss	High gloss	
Area of use	Surfaces for polishing	
Application	Spray	
Mixing	Product LKA3066.99.0000 HHA3066.00.0000 Thinner	Weight 100 100 45-55

TECHNICAL CHARACTERISTICS:

Specific gravity (kg/l)	1.000 ± 0.03
Solids content (%)	55 ± 2
Viscosity component A (DIN4 at 20°C)	110-130

GENERAL CHARACTERISTICS:

Pot-life at 20°C	6
Recommended application weight (g/m²)	100 - 110
Number of layers	1-3
Interval between layers (min, at 20°C)	10-15
Drying time (100 g/m² at 20°C)	Dust free: 20-25' Touch dry: 1,5-2h Stackable: 24h

Shelf-life (months)

12

FEATURES:

- Excellent transparency
- Gloss retention
- Excellent levelling
- Easy to polish after 24 hours
- Homogeneous appearance before and after polish
- Yellowing resistance

SUBSTRATE PREPARATION:

The substrate must be properly prepared and cleaned of all kinds of dirt and dust.

WARNING:

Use only hardeners and thinners recommended by the company's technologists.

TRANSPORTATION AND STORAGE:

The product should be stored in a tightly closed can, protected from moisture and direct sunlight. After opening the package, the product should be used as quickly as possible. More detailed information on handling the product please find in the safety data sheet.

HEALTH & SAFETY:

For full Health and Safety information, please refer to Safety Data Sheet.

Suitable protective equipment (glasses, gloves, mask etc.) must be worn while using these products. Good ventilation must be provided in the working environment.