

**BP59C00****Polyurethane basecoat clear**

<b>Color</b>	Clear	
<b>Area of use</b>	General purpose product, suitable also for vertical applications on doors, mouldings and furniture elements	
<b>Application</b>	Spray	
<b>Mixing</b>	<b>Product</b> BP59C00 JP023 Thinner	<b>Weight</b> 100 50 25-30

**TECHNICAL CHARACTERISTICS:**

<b>Specific gravity (kg/l)</b>	1.020 ± 0.010
<b>Solids content (%)</b>	53 ± 2
<b>Viscosity component A (DIN6 at 20°C)</b>	95 ± 5"

**GENERAL CHARACTERISTICS:**

<b>Pot-life at 20°C</b>	2 h
<b>Recommended application weight (g/m<sup>2</sup>)</b>	Min 80 - Max 140
<b>Number of layers</b>	1
<b>Drying time (100 g/m<sup>2</sup> at 20°C)</b>	Dust free: 20' Touch dry: 60' Stackable: 16 h Sandable after 3 h minimum

**GENERAL CHARACTERISTICS:**

<b>Substrate preparation</b>	Sanding with P180-P240 abrasive
<b>Shelf-life (months)</b>	12

**FEATURES:**

- good thixotropy
- good sandability
- good filling power
- product is easy to sand and can be overcoated in short times

**SUBSTRATE PREPARATION:**

The substrate must be properly prepared and cleaned of all kinds of dirt and dust.

**WARNING:**

Use only hardeners and thinners recommended by the company's technologists.

**TRANSPORTATION AND STORAGE:**

The product should be stored in a tightly closed can, protected from moisture and direct sunlight. After opening the package, the product should be used as quickly as possible. More detailed information on handling the product please find in the safety data sheet.

**HEALTH & SAFETY:**

For full Health and Safety information, please refer to Safety Data Sheet.

Suitable protective equipment (glasses, gloves, mask etc.) must be worn while using these products. Good ventilation must be provided in the working environment.