

TECHNICAL DATA SHEET

LKP3050.95.0000

Clear PU high gloss topcoat

Color	Clear	
Gloss level	93 ± 2	
Area of use	Glossy surfaces not suitable for polishing	
Application	Spray	
Mixing	Product LKP3050.95.0000 HHP1033.00.0000 Thinner	Weight 100 100 0-30

TECHNICAL CHARACTERISTICS:

Specific gravity (kg/l)	1.000 ± 0.03
Solids content (%)	56 ± 2
Viscosity component A (DIN4 at 20°C)	55-65

GENERAL CHARACTERISTICS:

Pot-life at 20°C	10
Recommended application weight (g/m²)	90 - 110
Number of layers	1-2
Drying time (100 g/m ² at 20°C)	Dust free: 25' Touch dry: 90' Stackable: 24h

ColorfactoryGmbH



TECHNICAL DATA SHEET

Shelf-life (months)

24

FEATURES:

- High and stable brightness
- Scratch and impact resistance
- High film thickness
- Excellent pin hole resistance

SUBSTRATE PREPARATION:

The substrate must be properly prepared and cleaned of all kinds of dirt and dust.

WARNING:

Use only hardeners and thinners recommended by the company's technologists.

TRANSPORTATION AND STORAGE:

The product should be stored in a tightly closed can, protected from moisture and direct sunlight. After opening the package, the product should be used as quickly as possible. More detailed information on handling the product please find in the safety data sheet.

HEALTH & SAFETY:

For full Health and Safety information, please refer to Safety Data Sheet.

Suitable protective equipment (glasses, gloves, mask etc.) must be worn while using these products. Good ventilation must be provided in the working environment.