

**TP27G99C01****Polyurethane topcoat white high-gloss**

<b>Color</b>	White	
<b>Gloss</b>	100	
<b>Area of use</b>	Furniture	
<b>Application</b>	Spray / Curtain coater	
<b>Mixing</b>	<b>Product</b> TP27G99C01 JP046 Thinner	<b>Weight</b> 100 100 20-50

**TECHNICAL CHARACTERISTICS:**

<b>Specific gravity (kg/l)</b>	1.380 ± 0.010
<b>Solids content (%)</b>	73 ± 1
<b>Viscosity (DIN4 at 20°C)</b>	140" ± 5

**GENERAL CHARACTERISTICS:**

<b>Pot-life at 20°C</b>	4 h
<b>Recommended application weight (g/m<sup>2</sup>)</b>	Min 120 - Max 150
<b>Number of layers</b>	1-2
<b>Drying time (100 g/m<sup>2</sup> at 20°C)</b>	Dust free: 25-30' Touch dry: 60-90' Stackable: 24 h

**GENERAL CHARACTERISTICS:**

<b>Substrate preparation</b>	The longer basecoat drying, the lower shrinkage of high-gloss coating
<b>Shelf-life (months)</b>	12

**FEATURES:**

- great levelling properties
- good hiding point
- good scratch resistance
- good light fastness
- suitable for spray and curtain coater application (especially on sanded polyester basecoat).

**SUBSTRATE PREPARATION:**

The substrate must be properly prepared and cleaned of all kinds of dirt and dust.

**WARNING:**

Use only hardeners and thinners recommended by the company's technologists.

**TRANSPORTATION AND STORAGE:**

The product should be stored in a tightly closed can, protected from moisture and direct sunlight. After opening the package, the product should be used as quickly as possible. More detailed information on handling the product please find in the safety data sheet.

**HEALTH & SAFETY:**

For full Health and Safety information, please refer to Safety Data Sheet.

Suitable protective equipment (glasses, gloves, mask etc.) must be worn while using these products. Good ventilation must be provided in the working environment.