



MULTIBOND 1095

— High-Performance Wood Adhesive —

LAMINATING | VENEERING

FORMULATED FOR PEAK PANEL PERFORMANCE

Multibond 1095 is a single-component crosslinking polyvinyl acetate (PVA) emulsion adhesive designed for a wide range of laminating applications. Optimized for hot pressing operations and extended layup times, this product offers improved resistance to surface checking compared to conventional PVA adhesives on the market. Multibond 1095 has met applicable ASTM formaldehyde emission requirements and passes HPVA Type II wet-use testing when properly applied, cured, and stored.



ADHESIVE PROPERTIES

Chemical Family Description	Crosslinking PVA adhesive
Appearance	White liquid adhesive
Pre-Press Working Time	10-15 minutes
Chalk	46°F / 7.8°C
Shelf Life	3 months
Bonding Operations	Hot press and cold press compatible
Like all adhesives, proper use, storage, and manufacturing conditions are required to achieve stated performance. Actual properties and results may vary depending on application, bonding practices, and environmental conditions.	

INDUSTRIAL APPLICATIONS

Used for a variety of laminating and veneering applications including engineered wood flooring, hardwood plywood, and other wood panel manufacturing operations.

PRODUCT FEATURES

- Water resistant with improved resistance to surface checking
- Meets requirements for ANSI/HPVA HP-1-2024 Type II wet use
- Meets the definition of NAF for CARB and TSCA Title VI
- ASTM D6007-22 testing results show no detectable formaldehyde emissions for wood-based materials (*Capital Testing Lab Test ID No. FSC6155*)



PRODUCTION BENEFITS

Every operation is different. For many flooring, plywood and other wood-based panel manufacturers, switching from a urea-formaldehyde adhesive to a PVA adhesive may create opportunities to reduce operating costs and get more from existing equipment. Learn more about Multibond 1095 by contacting your Franklin A&P sales representative or visiting franklinap.com/multibond-1095. You can also scan the QR code and search for the product on our website.

STORAGE, SHELF LIFE & HANDLING

Shelf life: Best if used within **three months** of date of manufacture. Mix before use. Consult our technical service team, SDS, and PDS to confirm compatibility before use of product. Contact our team by scanning the QR code below or emailing IASTS@franklininternational.com.

YOUR TRUSTED PARTNER IN ADHESION | franklinap.com | **1.800.877.4583**

As with all products, proper use, storage, and handling are required to achieve stated compliance, end use product capabilities, and performance. The information provided in this Product Guide is based on data believed to be reliable; however, it is offered without guarantee, as methods and conditions of use are beyond Franklin's control. Customers are responsible for evaluating product suitability prior to commercial use. Substrate appearance and performance including potential surface marking, discoloration, or coating variation may be influenced by material composition, application conditions, or environmental exposure. Franklin assumes no responsibility for such effects. All purchases are subject to Franklin International, Inc.'s Standard Terms and Conditions of Sale; any additional or differing terms are expressly rejected. Contact us for a copy of these Terms if needed. © 2026 Franklin International. All rights reserved. Franklin International, 2020 Bruck Street, Columbus, OH 43207, USA.

