



13 Oz. Vinyl (100%)

Colors: All Standard Colors

Properties	Test Method	Test Result
Weight (Oz./Yd)	ASTM D-5041	13.2
Thickness (inches)	PCCP	0.017"
Warp Tensile Strength	ASTM D-5100	238 lbs.
Fill Tensile Strength	ASTM D-5100	233 lbs.
Warp Tear Strength	ASTM D-2261	132 lbs.
Fill Tear Strength	ASTM D-2261	126 lbs.
Hydrostatic Resistance	ASTM D-5512	375 lbs./in.

Disclaimer: Information from Collins Company is based on data believed reliable but provided only as reference averages, not specifications. The purchaser is solely responsible for determining suitability for use. Collins Company assumes no liability and disclaims all warranties, express or implied, including merchantability, fitness for purpose, or any arising from trade, and this document is not engineering advice.

California

300 East Eucalyptus Avenue
Ontario, CA 91762

collinscompany.com

Call (800) 222-4348
Fax (909) 548-6908

Georgia

1375 Weber Industrial Drive
Cumming, GA 30041