



Closed Mesh Polypropylene (95%)

Colors: Green, Black

Mechanical Properties	Test Method	Unit	Typical Roll Value	
			MD	CD
Grab Tensile Strength	ASTM D 4632	lbs	420	225
Trapezoid Tear Strength	ASTM D 4533	lbs	125	90
Shade		%	95	
Air Flow	ASTM D 737	cfm	>150	
Physical Properties	Test Method	Unit	Typical Roll Value	
Weight	ASTM D 5261	oz/yd sq.	5.6	
Construction		EPI/PPI	30 x 16	
Fiber Content			100% PP	
Thermal Properties				
Softening & Melting Temperature	Soften at 300-310 degrees Fahrenheit and melt at 325-335 degrees Fahrenheit.			
Shrinkage	Shrinkage at boil, 3-9% Shrinkage at 250 degrees Fahrenheit, 5-12.5%			
Flammability	Difficult to ignite and upon burning it melts to a head. Proper additives can produce flame retardancy.			
Additional Properties				
Effects of Moisture	Polypropylene does not absorb moisture.			
Abrasion Resistance	Polypropylene has excellent abrasion resistance.			
Mildew & Insect Resistance	Insects and mildew do not attach to polypropylene.			
Identification	Because of low specific gravity, polypropylene floats on water. Melting point: 325 to 335 degrees Fahrenheit.			
Tensile Properties	Polypropylene monofilaments have an average tenacity range of 4-7 grams per denier. Polypropylene has an ultimate elongation of 14-30%			

Disclaimer: Information from Collins Company is based on data believed reliable but provided only as reference averages, not specifications. The purchaser is solely responsible for determining suitability for use. Collins Company assumes no liability and disclaims all warranties, express or implied, including merchantability, fitness for purpose, or any arising from trade, and this document is not engineering advice.

California

300 East Eucalyptus Avenue
Ontario, CA 91762

collinscompany.com

Call (800) 222-4348
Fax (909) 548-6908

Georgia

1375 Weber Industrial Drive
Cumming, GA 30041