

DYNO Pure Acrylic for interior

DESCRIPTION

Based on lightfast pigments and pure acrylic latex, Dyno Acrylic Emulsion is a high-quality acrylic emulsion paint for interior finishes where a washable, hard-wearing, low-sheen finish is required. It is characterized by good resistance to discoloration on masonry surfaces.

PRODUCT FEATURES AND RECOMMENDED USES

Ideal for interior decoration on concrete, both new and old masonry surfaces, such as plaster, brick, asbestos, and shingles.

TECHNICAL DATA

Type 100% Pure Acrylic Emulsion **Color** Dyno Acrylic Emulsion Color Card

Texture Matt

Non-Volatile40 - 45 % by volumeCoverage (Theoretical)35 - 45 sq.m./GallonWet Film Thickness90 - 100 micronsDry Film Thickness35 - 45 micronsApplicationBrush, Roller or Spray

Diluent Clean Water

Brush, Roller 10 – 15% by volume

Air spray 20 - 30% by volume
Touch Dry 20 - 30 minutes

Drying Time Touch Dry 20 - 30 minutes (21-27°C and 50% RH) Hard Dry 1 - 2 hours

Re-Coat 1 - 2 hours

SURFACE PREPARATION

For re-painting, make sure the surface to be painted is free from dirt, grease, waxy contaminants, and loose, peeling paint. If mold and fungus appear on the painted surfaces, it is important that all existing mold be killed before applying a new coat of paint. One effective method for killing mold is to wash the mold-infested surfaces with Dyno Super Mold Killer. The treated surfaces should then be rinsed with clean water and allowed to dry before repainting.

For new masonry surfaces, allow the surface to completely dry for a minimum of 30 days. Before painting, make sure the surface is free from dirt, grease, and waxy contaminants.

SUGGESTED COATING SYSTEMS

For New Masonry Surfaces

Dyno Alkali Resisting Primer P-1000 1 Coat

Dyno Pure Acrylic for Interior 2 Coats

For Repainting

Dyno Chalking Sealer P-1100 1 Coat

Dyno Pure Acrylic for Interior 2 Coats

01/2024

Disclaimer: This information is based on our present state of knowledge. It should therefore not be construed as guaranteeing specific properties of the product described or its suitability for a particular use. This information relates only to the specific material designated and may not be valid for such material used in combination with any other materials or in any process. Such information is, to the best of the company's knowledge and belief, accurate and reliable as of the date indicated. However, no warranty, guarantee or representation is made to its accuracy, reliability or completeness. It is the user's responsibility to satisfy himself as to the suitability of such information for his own particular use.