



# PAINTER'S TOUCH® 2X ULTRA COVER CLEAR SPRAYS

## DESCRIPTION AND USES

Rust-Oleum® Painter's Touch® 2X Ultra Cover Clear Sprays are designed to provide long lasting protection and durability. These sprays apply easily, provide excellent coverage and dry fast to a tough attractive finish. Painter's Touch Ultra Cover 2X Clear Sprays feature an advanced spray system that allows you to spray at any angle, even upside down for those hard to reach areas. A comfort spray tip with a wider finger pad to reduce fatigue caused by continuous spraying. Not for use on galvanized metal.

Some plastics made of polyethylene such as Little Tikes® children's product are manufactured in such a way that may hinder maximum paint adhesion. Not for use on galvanized metal.

## PRODUCTS

| SKU (12 ounces) | DESCRIPTION      |
|-----------------|------------------|
| 249087          | Matte Clear      |
| 249117          | Gloss Clear      |
| 249845          | Satin Clear      |
| 249859          | Semi-Gloss Clear |

## PRODUCT APPLICATION

### PAINTING CONDITIONS

Use outdoors or in a well ventilated area such as an open garage. Use when temperature is between 50-90°F (10-32°C) and humidity is below 65% to ensure proper drying. Do not apply to surfaces, when heated, exceed 200°F (93°C). Do not apply to galvanized steel. Avoid spraying in very windy and dusty conditions. Cover surrounding area to protect from spray mist.

### SURFACE PREPARATION

Remove all dirt, grease, oil, salt and chemical contaminants by washing the surface with a commercial detergent or other suitable cleaning method. Rinse thoroughly with fresh water and allow to thoroughly dry. All surfaces must be dry at time of application. Remove loose paint and rust with a wire brush or sandpaper. Lightly sand glossy surfaces to create a surface profile.

**WARNING!** If you scrape, sand or remove old paint from any surface, you may release lead paint dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE; ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead).

\* Little Tikes® is a registered trademark of The Little Tikes Company.

## PRODUCT APPLICATION (cont.)

### APPLICATION

Shake can vigorously for one minute after the mixing ball begins to rattle. If mixing ball fails to rattle DO NOT STRIKE CAN. Contact Rust-Oleum. Shake often during use. Hold can upright 10-16" from surface and spray in a steady back-and-forth motion, slightly overlapping each stroke. Keep the can the same distance from the surface. Keep the can in motion while spraying. **Do not use near open flame.**

### DRY & RECOAT TIMES

Dry and recoat times are based on 70°F and 50% relative humidity. Allow more time at cooler temperatures. Dries to touch in 20 minutes, to handle in 1 hour, and is fully dry in 24 hours. Apply a second coat at anytime. If the coating is a new finish, recoat within 30 minutes or after 48 hours. NOTE: On plastic, maximum paint adhesion and durability is achieved in 5-7 days.

### CLEAN-UP

Wipe off tip before storing. Clean-up wet paint with xylene or mineral spirits. Properly discard empty container. Do not burn or place in home trash compactor.

### CLOGGING

If the valve clogs, twist and pull off spray tip and rinse in a solvent such as mineral spirits. Do not stick pin or other objects into the stem.



## TECHNICAL DATA

### PAINTER'S TOUCH® 2X ULTRA COVER CLEAR SPRAYS

#### PHYSICAL PROPERTIES

|                                                                   |        | 2X ULTRA COVER CLEAR SPRAYS                                                                     |
|-------------------------------------------------------------------|--------|-------------------------------------------------------------------------------------------------|
| Resin Type                                                        |        | Acrylic                                                                                         |
| Pigment Type                                                      |        | Amorphous Silica                                                                                |
| Solvents                                                          |        | Acetone, Dimethyl Carbonate, N-Butyl Acetate, Propylene Glycol Monomethyl Ether Acetate, Xylene |
| MIR                                                               |        | 0.85 Max                                                                                        |
| Fill Weight                                                       |        | 12 ounces                                                                                       |
| Recommended Dry Film Thickness (DFT) per Coat                     |        | 1.0-2.0 mils<br>(25-50µ)                                                                        |
| Practical Coverage at Recommended DFT (assumes 15% material loss) |        | 8-12 sq.ft./can<br>(0.74-1.11 m <sup>2</sup> /can)                                              |
| Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity          | Touch  | 20 minutes                                                                                      |
|                                                                   | Handle | 1 hour                                                                                          |
|                                                                   | Recoat | Anytime – If coating is a new finish, recoat within 30 minutes or after 48 hours                |
| Dry Heat Resistance                                               |        | 200°F (93°C)                                                                                    |
| Shelf Life                                                        |        | 5 years                                                                                         |
| Flash Point                                                       |        | -156°F (-104°C)                                                                                 |
| Safety Information                                                |        | For additional information, see SDS                                                             |

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.