



STOPS RUST® ANTI-SLIP RESISTANT COATING

DESCRIPTION AND USES

Rust-Oleum® Stops Rust® Anti-Slip creates a non-skid surface on concrete, metal and wood. The fast drying formula dries clear and can be applied to ramps, stairs, railings and more.

Stops Rust Anti-Slip features an advanced spray system that allows you to spray at any angle, even upside down for those hard to reach areas. A comfort spray tip with a wider finger pad reduces fatigue caused by continuous spraying.

PRODUCT

SKU	DESCRIPTION (12 oz. Spray)
271455	Anti-Slip Resistant Coating

PRODUCT APPLICATION

PAINTING CONDITIONS

Use outdoors or in a well ventilated area such as an open garage. Use when temperature is between 50-90°F (10- 32°C) and humidity is below 85% to ensure proper drying. Do not apply to surfaces that, when heated, exceed 200°F (93°C). Avoid spraying in very windy and dusty conditions. Cover surrounding area to protect from spray mist.

SURFACE PREPARATION

Wash the surface with a commercial detergent, or other suitable cleaning method to remove dirt. Rinse with fresh water and let dry. Remove loose paint and rust with a wire brush or sandpaper. Clean concrete surfaces with a suitable cleaner and water. Rinse and allow to dry. Lightly sand glossy surfaces.

WARNING: If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

PRIMING

Priming is not necessary but additional coats may be required on porous surfaces such as unfinished wood and concrete.

PRODUCT APPLICATION (cont.)

APPLICATION

Shake can vigorously for one minute after the mixing ball begins to rattle. If mixing ball fails to rattle DO NOT STRIKE CAN. Contact Rust-Oleum. Shake often during use. Hold can 12-16" from surface and spray in a steady back-and-forth motion, slightly overlapping each stroke. Keep the can the same distance from the surface and in motion while spraying. Apply 2 or more light coats a few minutes apart. Do not use near open flame.

DRY & RECOAT

Dry and recoat times are based on 70°F (21°C) and 50% relative humidity. Allow more time at cooler temperatures. Apply a second coat within 1 hour or after 48 hours. Allow surfaces to dry for 24 hours before use.

CLEAN-UP

Wipe off tip when finished. Clean up wet paint with xylene or mineral spirits. Properly discard empty container. Do not burn or place in home trash compactor.

CLOGGING

If the valve clogs, twist and pull off spray tip and rinse in a solvent such as mineral spirits. Do not insert any object into can valve opening.

	TECHNICAL DATA	SRT-30
	STOPS RUST® ANTI-SLIP RESISTANT COATING	

PHYSICAL PROPERTIES

ANTI-SLIP RESISTANT COATING		
Resin Type	Proprietary Non-Hazardous Polymer	
Pigment Type	Polypropylene	
Solvents	Acetone, Ethyl Benzene, N-Butyl Acetate, Xylene	
MIR	2.10 Max	
Fill Weight	12 ounces	
Recommended Dry Film Thickness (DFT) Per Coat	1.5-2.5 mils (37.5-62.5μ)	
Practical Coverage at Recommended DFT	10-12 sq.ft./can (0.90-1.09 m ² /can)	
Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity	Touch	2-4 hours
	Recoat	Apply a second coat within 1 hour or after 48 hours
	Fully Dry	Allow surfaces to dry for 24 hours before use
Dry Heat Resistance	200°F (93°C)	
Shelf Life	5 years	
Flash Point	-156°F (-104°C)	
Safety Information	For additional information, see SDS	

Calculated values are shown and may vary from the actual manufactured material.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.



Rust-Oleum Corporation
11 Hawthorn Parkway
Vernon Hills, Illinois 60061

Phone: 877-385-8155
www.rustoleum.com

Form: GDH-627
Rev.: 051421