

DYNO Acrylic Primer P-2710

DESCRIPTION

Dyno Acrylic Primer P-2710 is a water-based acrylic primer specially developed for use with Dyno Acrylic products. The undertone of this primer enhances the topcoat, providing better coverage and optimal gold luster.

PRODUCT FEATURES AND RECOMMENDED USES

Used as a primer for Dyno Gold Water-Based Paint 2700 on walls, concrete, wood, alloys, and metal surfaces that have been properly primed.

TECHNICAL DATA

Acrylic Emulsion Type

Color Yellow

Texture Low Sheen Matt Non-Volatile 40 - 45 % by volume Coverage (Theoretical) 35 - 45 sq.m./Gallon Wet Film Thickness 90 - 100 microns **Dry Film Thickness** 35 - 45 microns **Application** Brush, Roller or Spray

Diluent Clean Water

> Brush, Roller 10 - 15 % by volume 20 - 30 % by volume Air spray

Drying Time Touch Dry 20 - 30 minutes

> Hard Dry 1 - 2 hours Re-Coat 1 - 2 hours

SURFACE PREPARATION

For re-painting, make sure the surface to be painted is free from dirt, grease, waxy contaminants, and loose or peeling paint. If mold and fungus appear on the painted surfaces, it is important to remove all existing mold before applying a new coat of paint. One effective method for killing mold is to wash the affected surfaces with Dyno Super Mold Killer. The treated surfaces should then be rinsed with clean water and allowed to dry before repainting. For new masonry surfaces, allow the surface to dry completely for a minimum of 30 days. Before painting, ensure the surface is free from dirt, grease, and waxy contaminants.

SUGGESTED COATING SYSTEMS

For New Masonry Surfaces

Dyno Alkali Resisting Primer P-1000 1 Coat Dyno Acrylic Primer P-2710 1 Coat Dyno Acrylic Emulsion Gold 2700 2 Coats

Re-painting

Dyno Chalking Sealer P-1000 1 Coat Dyno Acrylic Primer P-2710 1 Coat Dyno Acrylic Emulsion Gold 2700 2 Coats

Metal Alloy

Dyno Wash Primer, Dyno Metal Conditioner 1 Coat Dyno Acrylic Primer P-2710 1 Coat Dyno Acrylic Emulsion Gold 2700 2 Coats

Disclaimer: This information is based on our present state of knowledge. It should therefore not be construed as guaranteeing specific properties of the product described or its suitability for a particular use. This information relates only to the specific material designated and may not be valid for such material used in combination with any other materials or in any process. Such information is, to the best of the company's knowledge and belief, accurate and reliable as of the date indicated. However, no warranty, guarantee or representation is made to its accuracy, reliability or completeness. It is the user's responsibility to satisfy himself as to the suitability of such information for his own particular use.