

DESCRIPTION

An alkyd-based primer specially formulated for priming alkyd enamel. It is quick-drying, fungus-resistant, has good leveling, and high opacity. It also provides good intercoat adhesion between the primer and topcoat enamel.

PRODUCT FEATURES AND RECOMMENDED USES

Most suitable as an undercoat for wood, primed metal, or masonry surfaces before the final finish with Dyno Gloss Enamel.

TECHNICAL DATA

Type	Synthetic Alkyd
Color	White
Texture	Low Sheen Matt
Non-Volatile	45 - 50% by volume
Coverage (Theoretical)	45 - 60 sq.m./Gallon
Wet Film Thickness	65 - 85 microns
Dry Film Thickness	30 - 40 microns
Application	Brush, Roller or Spray
Diluent	Dyno Thinner No.1
	Brush, Roller 5 – 10% by volume
	Air Spray 10 – 20% by volume
Drying Time	Touch Dry 1.0 - 1.5 hours
	Hard Dry 8 - 10 hours
	Recoat Dry 8 - 10 hours

SURFACE PREPARATION

Make sure the surface to be painted is free from dirt, grease, any waxy contaminants, and loose or peeling paint. Cracks and open grain should be properly sealed and sanded smooth before priming.

SUGGESTED COATING SYSTEMS

For Resinous Wood

Dyno Aluminium Wood Primer	1 Coat
Dyno Universal Undercoat P-3000	1 Coat
Dyno High Gloss Enamel	2 Coats

For Normal Hard Wood

Dyno Universal Undercoat P-3000	1 Coat
Dyno High Gloss Enamel	2 Coats