

DYNO Aluminum Wood Primer

DESCRIPTION

An ideal primer for all types of wood. Due to the overlapping of the aluminum flakes, Dyno Aluminum Wood Primer acts as a barrier shield against moisture ingress while preventing raised grain and providing better adhesion for the topcoat finish.

PRODUCT FEATURES AND RECOMMENDED USES

Suitable for priming new resinous wood to prevent raised grain and the bleeding of resinous exudation into the topcoat.

TECHNICAL DATA

Type Alkyd Resin, Aluminum

Dull Silver Color Low Sheen Matt **Texture** Non-Volatile 40 - 45% by volume Coverage (Theoretical) 45 - 55 sa.m./Gallon Wet Film Thickness 70 - 80 microns **Dry Film Thickness** 30 - 40 microns Application Brush, Roller or Spray Diluent Dyno Thinner No.1

Brush – No Diluent

Roller 5% by volume
Spray 5 - 15% by volume
Touch Dry 1 - 1.5 hours
Hard Dry 5 - 7 hours

5 - 7

hours

SURFACE PREPARATION

Drying Time

Make sure the surface to be painted is free from dirt, grease, any waxy contaminants, and loose or peeling paint. Cracks and open grain should be properly sealed. Sand the surface smooth before applying.

Recoat Dry

SUGGESTED COATING SYSTEMS

For Resinous Wood

Dyno Aluminum Wood Primer 1 Coat
Dyno Universal Undercoat P-3000 1 Coat
Dyno High Gloss Enamel 2 Coats

01/2024