





1. Application Sector

DAMTEC® multi is an underlay for impact sound reduction.

2. Material

Granules of rubber with PU elastomer bonding agent

3. Appearance

colour: multicolour

surface: granule structure

4. Dimensions/Tolerances

width: 1,000 mm ± 1.5 %

length: on request

available thickness: 3, 4.5, 5, 6, 9, 9.5, 10 and 12 mm \pm 0.6 mm

density: approx. 970 kg/m³

5. Physical Characteristics

tensile strength: approx. 0.4 N/mm² (ISO 1798) elongation at break: approx. 50% (ISO 1798)

service temperature range: - 30°C to 80°C

With the publication of this product data sheet all former issues cease to be valid.





 \pm 1.0 mm









Product Data Sheet No. 94310 - RV - 06 Edition: January 2021

impact sound improvement:

(ISO 10140 / ISO 717)

 $\Delta L_W = 16dB$ with 3mm under 8mm tiles ΔL_W = 21dB with 3mm under 60mm screed

 ΔL_W = 24dB with 4.5mm under 60mm screed ΔL_W = 21dB with 8/4 3D under 60 mm screed

(ASTM E2179 / E 989)

 Δ IIC = 20dB with 3mm under 8mm tiles Δ IIC = 24dB with 3mm under 60mm screed AIIC = 27dB with 4.5mm under 60mm screed Δ IIC = 27dB with 5mm under 60mm screed Δ IIC = 24dB with 8/4 3D under 60mm screed

6. Installation:

Installation is to be carried out in accordance with the DAMTEC® multi installation instructions.

7. Other Matters:

Castor chair behaviour and residual indentation after static loading of the flooring can change in accordance with the insulating underlay used. Only use underlay approved by the floor manufacturer. Prior to any installation work, carefully read and observe the usage instructions and processing guidelines of the adhesive cement and floor finish manufacturers. In case of doubt, please contact the manufacturer's applications engineering department for advice.

DISCLAIMER:

The information provided is intended only as a summary and general overview on matters of interest. The information is not intended to be comprehensive nor does it constitute expert advice. KRAIBURG RELASTEC shall not be liable for incidental and/or consequential damages directly or indirectly sustained, nor any loss caused by not complying with relevant industry/product standards and improper use of any Damtec® products. Due to varying construction methods, any other circumstances not stated above should be brought to the attention of KRAIBURG RELASTEC for review. For suitability to the prevailing site conditions, it is advised that certified testing should be conducted. It is recommended to seek further advice on your application with our technical staff prior to use.

The data sheet is not subject to any change service! All information is without guarantee. With the publication of this product data sheet all former issues cease to be valid.





