

# LABFAST® 85 PRO

Best Value, Long Working Time, Quick Curing and Reduced Odor  
Polyaspartic with Advanced Opacity Technology

## Technical Data Sheet



### Description

The LABFAST® 85 PRO is a high-solids, two-component (1A:1B), non-yellowing with reduced odor polyaspartic for concrete floor coating, commonly used with vinyl flakes. The colored LABFAST® 85 PRO serves as the base coat, while the clear version is used as a protective topcoat, LABFAST® 85 PRO provide optimal work time/cure time ratio. LABFAST® 85 PRO formulation includes Advanced Opacity Technology which reduces chip repulsion effect and allowing pigments to remain on top of the substrate therefore improving coverage and aesthetics. The utilization of the LABFAST® 85 PRO allows the installation of a full floor system in one single day, with rapid return to service. The LABFAST® 85 PRO displays excellent curing capability even at very low temperature levels. This product offers superior mechanical and chemical properties and is low maintenance. It also displays a superior aesthetic finish and excellent UV stability which makes it ideal for exterior applications. We recommend the utilization of the LABTEC vinyl chips in combination with the LABFAST® products. Two- or three-coat systems can be considered.

### Uses

The chemical and mechanical properties of LABFAST® 85 PRO provide excellent results for several applications. Note that the smell may not be suitable for all applications depending on tolerance and ventilation.

- + Garages
- + Other residential applications
- + Commercial centers
- + Office buildings
- + Retail stores
- + Manufacturing facilities
- + Public facilities including hospitals and schools
- + Other commercial uses

### Advantages

- + Reduced odor compared to previous generation
- + High solids content, 85%
- + Advanced Opacity Technology
- + Better coverage of the substrate
- + Reduction of the chip repulsion effect
- + Up to 15% less topcoat needed
- + Advanced Opacity Technology
- + Available in clear and pre-tinted versions
- + Non-yellowing
- + Excellent impact and abrasion resistance
- + Easy to use 1A:1B system with common hardener for the base coat and topcoat
- + Possibility to install base coat and topcoat in a single workday

- + Cures quickly - recommended to obtain best curing at very low temperature levels (below -10°C /14°F)
- + Ideal for exterior applications
- + Possible to install two- or three-coat systems
- + Easy to install
- + Very long recoat window and pot life
- + Excellent chemical and mechanical resistance
- + Impermeability / low moisture sensitivity
- + Superior gloss finish
- + High density of the product prevents dirt penetration resulting in low maintenance

### Product Data

<b>Mix Ratio</b>	1A:1B	
<b>Packaging</b>	2 US gallon kits (2 x 3.78L)	
<b>Color</b>	Clear	
<b>Solids Coverage / US GAL</b>	<b>Mils</b>	<b>Sq. Ft.</b>
	6	267
	8	200
	10	160
	12	133
	14	114
<b>Shelf Life</b>	One year, in original unopened factory pails under normal storage conditions.	
<b>Application Temperature</b>	Min -30°C / -22°F , Max 30°C / 86°F	
<b>Cure Time</b>	22°C / 72°F and 50% Rel. Hum.	
<b>Version</b>	<b>85 PRO</b>	<b>85 PRO XT</b>
Working time	25 min	30 min
Tack Free	55 min	60 min
Recoat	55 min - 24 h	60 min - 24 h
Dry Through	5 h	5 h
Foot Traffic	24 h	24 h
Light Traffic	48 h	48 h
Full Cure	2 weeks	2 weeks
<b>Pot Life</b> 250 ml	20 min	20 min
Larger Volume	30 min	30 min

## Technical Properties

Hardness ASTM D2240 Shore D at maturity	70
Abrasion Resistance ASTM D4060 (Taber Abraser, Wheel CS 17/ 1000 g (2.2 lbs) / 1000 cycles)	25 mg loss
DRY Coefficient of Friction (Smooth coating) ASTM E303	1.2
Pull Off Test ASTM D7234	>3 Mpa
Elongation at break ASTM D638	150%
Tensile Strength ASTM D412	6700 psi
Compressive Strength ASTM D695	8275 psi (57 MPa)
Impact resistance (Direct) ASTM D2794 ft lb	>9
Solids Content by Volume	85%
Viscosity	100 - 200 cps
VOC Content	145 g/l
DE 500 hr ASTM D3424	<2.0
Gardner Impact (Dir/Rev)	>140 lbs

## Surface Preparation

Concrete should be clean, dry and free of grease, oil, paint, curing agents or any contaminants that may inhibit proper adhesion. Concrete should be cured at least 28 days before applying the coating system. If the concrete slab has been installed within 28 days, the LABPOX® MVB FAST moisture mitigation system could be considered system (refer to the LABPOX® MVB FAST technical data sheet for application details).

Proper testing procedures should be practiced with regards to moisture vapor transmission. Use a Tramex® CME / CMEexpert to measure the moisture content of the concrete slab. Moisture content must be below 4% before applying the product. It is necessary to take several measurements at various places on the slab. If the reading is higher than 4%, steps will be required to neutralize the soil moisture. The first thing to do is to make sure that the floor is completely dry before application. Floors with higher results can receive the LABPOX® MVB FAST moisture mitigation.

Surface must be shot blasted or prepared with an equivalent mechanical means in line with CSP-2 or more depending on the application. Ensure the surface is free of contaminants, and the pores are open to allow the product to penetrate.

If the product is applied to an existing LABFAST®/LABSHIELD® ECO flake flooring system that has been cured for more than 24

hours (at 22°C / 72°F), the floor surface should be sanded properly until a matte appearance is reached above and between the flakes. To achieve this result, we recommend the use of a sander equipped with a sponge pad which will follow the profile of the surface and allow the sandpaper to reach the low points between the flakes. It is necessary to sand in a multidirectional way. Repeat until a matte finish is achieved on the entire floor. It is also necessary to use xylene to remove all dust after sanding and to soften the existing layer so that it can bond with the new layer. The use of xylene for this task is mandatory as it will soften the previous coat for better adhesion. The xylene must be completely evaporated before applying the next coat.

If the product is applied over an existing LABPOX® flooring system that has been cured for a period longer than 24 hours, it should be sanded with a proper floor machine. A mechanical bond to a sanded surface is required and the pores of the existing coating must be opened for better adhesion. Vacuum dust and properly wipe the surface with alcohol or solvent prior applying the LABFAST® 85 PRO. The alcohol or solvent must be completely evaporated before applying the product. This preparation is necessary to ensure proper adhesion. Conduct adhesion tests if there is a doubt about surface preparation.

**IMPORTANT:** Adhesion of LABFAST® 85 PRO to LABPOX® MVB FAST can only be achieved on a full silica broadcast-to-rejection LABPOX® MVB FAST surface, EVEN WITHIN THE 24 HOUR RE-COAT WINDOW. We recommend using silica sand grade #32.

Once cured, the base coat with the flakes should be scraped and cleaned after appropriate hardness is reached prior applying the topcoat.

## Mixing

Before final mixing, pre-mix part A at low speed using a Jiffy® or an Exomixer® mixer blade. Special attention must be paid to colored versions of the product since pigments may have separated from the rest of the formulation during storage. Mixing should be done until the color is uniform.

Use the same batch number when working with pre-tinted products. In the event that different batch numbers have to be used for a same job, we recommend pre-mixing all part A's individually, then mix together part A's from the different batch numbers for two minutes until homogenous color.

Then, using a Jiffy® or an Exomixer® mixer blade, mix one part of A and one part of B together at low speed in a separate container. The mixing container must be clean and free of any outside particle. Mix thoroughly for a minimum of three minutes, until a completely homogeneous mixture is obtained. Use a low-speed drill (300-450 rpm) to minimize the entrapping of air. It is recommended to activate the mixer in the reverse mode after 90 se-



conds for the liquid to mix from the bottom of the mixing can to the top. Make sure to scrap sides and bottom of mixing container so no unmixed material remains. Mix only the necessary quantity to be used according to the specified pot life / working time.

## Application

Best results will be obtained between -10°C / 14°F et 30°C / 86°F and with a relative humidity of less than 80%. This product will also cure at temperatures well below -10°C / 14°F. If a heated floor is installed, ensure that the system is turned off during application and for the full duration of the cure. The product has been specially designed to adhere on concrete surfaces.

Once the surface has been properly prepared, squeegee and back roll the product. It is recommended to apply the product in a multi-directional (north-south, east-west) motion to ensure proper coating thickness.

The following flake systems can be considered:

2-Coats System		3-Coats System		
Base Coat + LABTEC Chips	Topcoat	Base Coat 1	Base Coat 2 + LABTEC Chips	Topcoat
8-13 mils	8-13 mils	4-9 mils	4-9 mils	8-13 mils

We recommend the LABTEC Vinyl Chips when installing a flake system. Do not exceed a thickness of 30 mils for the entire system as solvent entrapment or lingering odors may occur following the installation. The color of the base coat should match the type of flake blend used. With that regards, Labsurface has made recommendations in the LABTEC Vinyl Chips section of this document.

It is also possible to use the LABFAST® 85 PRO as a protective coat over epoxy. In addition to the superior chemical resistance and cleanability, the LABFAST® 85 PRO also provides additional UV protection that will significantly slow the yellowing of epoxy over time. When used as a protective layer on epoxy, a thickness of 10 mils is recommended.

Proper tests should be conducted prior application. Contact a Labsurface representative for additional information.

## Recoat

If the product is applied to an existing LABFAST®/LABSHIELD® ECO flooring system that has been cured for more than 24 hours (at 22°C / 72°F), the floor surface should be sanded properly until a matte appearance is reached above and between the flakes. To achieve this result, we recommend the use of a sanding machine equipped with a soft sanding pad which will follow the profile of the surface and allow the sandpaper to reach the low points between the flakes. It is necessary to sand in a multidirectional way. Repeat until a matte finish is achieved on the entire floor. It is also necessary to use xylene to remove all dust after sanding and

to soften the existing layer so that it can bond with the new layer. The use of xylene for this task is mandatory. Make sure the solvent is completely evaporated and there are no residues. In case there are remaining residues, wipe the surface using a dry rag or swab.

**IMPORTANT:** Adhesion of LABFAST® 85 PRO to LABPOX® MVB FAST can only be achieved on a full silica broadcast-to-rejection LABPOX® MVB FAST surface, EVEN WITHIN THE 24 HOUR RECOAT WINDOW. We recommend using silica sand grade #32.

## Limitations

Requires a dry substrate. Moisture content of the substrate must be measured with a Tramex® CME / CMExpert at must be below 4% before applying the product. This product should not be applied to concrete substrates that show high levels of moisture/humidity unless a moisture a LABPOX® MVB FAST moisture mitigation system is used. Adhesion to LABPOX® MVB FAST can only be achieved on a full silica broadcast-to-rejection LABPOX® MVB FAST surface, EVEN WITHIN THE 24 HOUR RECOAT WINDOW. Do not exceed a thickness of 30 mils for the entire system as solvent entrapment may occur above those levels. It is recommended to use 100% solids products and avoid solvent-based products for installations beyond those normal thickness levels. It is also recommended to do proper testing if a nonconventional installation is considered. Everything else being equal, thicker is the film, longer is the curing time. Drying time will be faster in a hot and/or humid environment. Conversely, the drying time will be longer in a cold and/or dry environment. Do not clean the finished surface during the week following installation. Keeping the product stored at room temperature.

In the event that dew point conditions lead to condensation persisting above the concrete surface, and for which the grinding process fails to eliminate this condensation, it is crucial to thoroughly dry the surface before installation. Neglecting this step may result in shortened working times and/or issues with adhesion.

The usage of direct-fired, unvented and certain other heat sources are not recommended as they emit byproducts that may negatively impact the curing process of the resin and lead to defects such as amine blush, whitening, loss of adhesion, or other surface imperfections.

Labsurface stands behind the quality of its products. However, Labsurface cannot guarantee results since Labsurface has no control over surface preparation, operating conditions and application procedures. Clients are solely responsible to test Labsurface's products to determine if they perform as expected. Although Labsurface makes reasonable efforts to control the quality of the finished product and its components, ASTM results may vary depending on the quality of the inputs delivered to Labsurface.

To meet our strict requirements, we are continuously testing our coatings and on occasion, formulations may be modified to improve certain properties within each coating. Information and data included in this reference document may not be up to date as of the date of reference. Contact Labsurface for further information regarding the limitations of this product.

This product is not immune to transfers of plasticizers contained in rubber, including car tires. Although the transfer of plasticizers phenomenon is very rare, under specific circumstances combining high tire temperature with i) high levels of plasticizers, and/or (ii) certain plasticizer types and/or (iii) certain tire types, it is possible for plasticizers to transfer from the tire rubber to the floor coating. This phenomenon is irreversible and can cause staining of the coated area. Tires should therefore cool down prior to the parking of the vehicle in the coated area.

Pressure washing and power washing (power washing involves water heating while pressure washing uses cold water) must be used with caution. Extreme pressure could damage the coating. Using hot water could also cause irreversible damage. When used to clean polymer coatings, water temperature must not exceed 49°C / 120°F and should be ideally between 32°C and 43°C / 90°F and 110°F.

Exposure to certain chemicals may cause reactions similar to those experienced with allergies. Chemicals that may cause sensitivity include synthetic and natural substances found in the Part A or the Part B of flooring or casting products. Once cross linked and completely cured, those substances are inert and therefore should not result in allergic reactions. Raw materials used by Labsurface do not differ significantly from comparable products manufactured by our competitors.

**Refer to the most recent Material Safety Data Sheet prior using this product.**

## Available Colors

**Clear**


**Pre-tint: Grey, Tan, Black, White**

## LABTEC Vinyl Flakes

### Marble LABTEC Chips



### Terrazzo LABTEC Chips



### ....AND MORE

To explore our full range of options, including all **Signature LABTEC Chips 1/4" and 1/16"**, we invite you to visit our website and browse through the available samples.

### EXAMPLES



Terrazzo **ARMADILLO** Flooded      Terrazzo **ARMADILLO** with **LABFENDER 240**



Terrazzo **DENALI** Flooded      Terrazzo **DENALI** with **LABFENDER 240**



Signature **1/16" NIGHTFALL**      Signature **1/16" NIGHTFALL** with **LABFENDER**



Signature **1/4" NIGHTFALL**

## Labsurface

2250, Louis-Blériot, Mascouche, QC, Canada J7K 3C1  
Phone: 450-966-9000 / Fax : 450-621-3135  
Labsurface.com